Accepted Manuscript

Recent developments in recycling of polystyrene based plastics

Sourbh Thakur, Ankit Verma, Bhawna Sharma, Jyoti Chaudhary, Sigita Tamulevicius, Vijay Kumar Thakur

PII: S2452-2236(18)30024-5

DOI: [10.1016/j.cogsc.2018.03.011](https://doi.org/10.1016/j.cogsc.2018.03.011)

Reference: COGSC 136

To appear in: *Current Opinion in Green and Sustainable Chemistry*

Received Date: 1 February 2018

Revised Date: 16 March 2018

Accepted Date: 22 March 2018

Please cite this article as: S. Thakur, A. Verma, B. Sharma, J. Chaudhary, S. Tamulevicius, V.K. Thakur, Recent developments in recycling of polystyrene based plastics, *Current Opinion in Green and Sustainable Chemistry* (2018), doi: 10.1016/j.cogsc.2018.03.011.

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

Recent developments in recycling of polystyrene based plastics

Sourbh Thakur^{a,b*}, Ankit Verma^b, Bhawna Sharma^b, Jyoti Chaudhary^b, Sigita Tamulevicius^a, Vijay Kumar Thakur^{c*}

^a*Institute of Materials Science of Kaunas University of Technology, Barsausko 59, LT-51423 Kaunas, Lithuania*

^b*School of Chemistry, Shoolini University, Solan 173212, Himachal Pradesh, India*

^c*Enhanced Composites and Structures Center, School of Aerospace, Transport and Manufacturing, Cranfield University, Bedfordshire MK43 0AL, UK*

Abstract

Due to their superior properties, plastics derived from petroleum have been extensively used almost in everyday life since last few decades. Because of lack in the manageability of plastic solid waste, their volume is increasing steadily in the natural world. Unfortunately, the disposal of plastics wastes in the oceans and land filling has led to a global issue. To effectively and efficiently deal with plastic solid waste is becoming a great challenge for the society as plastic solid waste creates big threat to our environment. Recycling of plastics solid waste should be performed to produce products having same quality to original plastics. This review article gives an overview of plastics solid waste with particular emphasis on the recent progress in polystyrene based plastics.

Keywords: Plastic solid waste; land filling; recycling; polystyrene; polystyrene based plastics

*Corresponding authors Email: vijay.kumar@cranfield.ac.uk, sourbh.sourbh@ktu.lt, thakursourbh@gmail.com

Introduction

The 20th Century has got topping achievements in petroleum-based plastics and plastic has gained important role in human life as well. The use of plastic in everyday life is growing with significant rate [1] i.e. 1.65 to 311 million tons worldwide [2] from 1950 to 2014 respectively. Due to various promising characteristics such as low density, durability, low cost and easily moldable, plastics have found useful applications in human life including electronics, packaging materials, farming, automobile and building construction to name a few [3]. According to one of report, worldwide output of 322 million tons for plastics has achieved in 2015 [3]. In Europe, plastics of 39.9%, 19.7% and 8.9% are due to packaging, building construction and automotive respectively. Above 80% of plastics in Europe are composed from polystyrene, polyethylene, polyurethane, polyvinyl chloride, polypropylene, polyethylene terephthalate and fossil-based plastics [3,4]. This review briefly sums up the issues regarding the plastics solid waste. The polystyrene based plastics have been reviewed in detail in this article.

Plastic solid waste: global issue

As many products of plastics are being utilized with the growth of world, plastic solid waste is becoming a global issue [5]. Hazardous effects are created on the environment due to nonbiodegradable nature of plastic. This results landfilling of plastic waste and leads to the hard environmental issues [6]. Pigment of plastic waste comprises of numerous toxic elements[7].The groundwater has been contaminated from the release of toxic chemicals in plastic waste [8]. Plastics solid wastes to landfills can enter the environments of marine, approximately 12 million

tons of plastics waste was found to move into the seas in 2010 [9]. Marine mammals are being tangled in plastic detritus and are adversely affected by plastics contamination [10–12].

The presentation on the treatment of plastics waste was given by European Union in 2012 [13,14]. Out of entire plastics wastes, percentages of 26, 0.3 and 35.6 were reported for mechanically recycled, feedstock recycling and energy generation respectively in 2012, disposal percentage was 38.1. As polymers have prominent energy value, plastic wastes were used as fuel by incineration. The average value of energy generation rate for 29 countries was 36% in which 19 countries had less value than average value [14]. Energy generation by recycling of plastics wastes is at the moment one of the most eco-efficient method because of bulk process, follow almost every strict emission rules and energy requirement [15,16]. However, many hazardous chemicals such as gases and dioxins can be evolved from the incomplete combustion of solid wastes, leading to severe environment pollution. Hence, combustion of solid wastes should be according to environmental standards defined by European Union [14,17].

Table 1 shows the characters and amounts of plastic used by USA in 2012 [14,18]. A quantity of 31.7 million tons of plastics was produced and 12.7% was accounted for plastics wastes in municipal solid wastes in 2012, out of 12.7%, 8.8% of plastic waste was recycled and rest was disposed. Recycling rate of 20% and 15% were reported for polyethylene terephthalate (resins) and polyethylene respectively but negligible amount of solid wastes composed of polyvinyl chloride, poly lactic acid, polypropylene and polystyrene were recycled [14]. It was found that approximate 80 times more production of plastic solid wastes in 2012 as compared to in 1960 [18] and till 1980, there was 0 % recycling of plastic waste. Hence, recycle rate of plastic waste enhanced to just 8.8% for time period of 30 years i.e. from 1980 to 2012.

Table 1. Plastics used by USA [14,18]

Plastic polymers	Generation (1000t)	Recovery		Discards (1000t)
		(1000t)	Rate (%)	
Poly-ethylene terephthalate	4520	880	19.5	3640
High-density polyethylene	5530	570	10.3	4960
Polyvinyl chloride	870	Neg.	Neg.	870
Low-density polyethylene/linear lowdensity polyethylene	7350	390	5.3	6960
Poly lactic acid	50	Neg.	Neg.	50
Polypropylene	7190	40	0.6	7150
Polystyrene	2240	20	0.9	2220
Other resins	4000	900	22.5	3100
Total plastic in municipal solid waste	31,750	2800	8.8	28,950

Recycling of plastic solid waste

Recycling of plastic wastes to construction industry is regarded as one of the best disposal method for plastics solid wastes (**Figure 1**). Plastics wastes can be handled by using following methods [19]: (a) land-filling, (b) incineration, (c) chemical recycling and (d) mechanical recycling. Land filling requires lots of space and pollutes the environment. Land filling of plastic wastes is not preferable and the European Commission has set the goal for zero land filling by 2025 [16]. No waste is left and high calorific values of plastic waste polymer are the advantages of incineration, however carbon dioxide, toxic chemicals, harmful ash are formed. Mechanical recycling is also known as physical recycling. Mechanical recycling is used to reuse the plastic

solid waste to form the product with same inherent characteristics [16,20] whereas in chemical recycling, plastic waste is converted into fuels and chemical feedstocks by using various treatment such as pyrolysis and hydrothermal [21,22]. By using chemical recycling, polyolefin's can be converted into oil/hydrocarbon, polyesters and polyamides can be turned back into respective monomers [23].

Figure 1. Schematic representation for recycling of plastic solid waste.

Polystyrene based plastics

Recently, polystyrene based plastics have been used in various applications [24–81]. Polystyrene-based plastic wastes of electrical and electronic equipment consist of acrylonitrilebutadiene styrene and high impact polystyrene [82]. Mainly 30-50% of plastic waste

is because of the electrical field and electronic equipments [83]. Truc and Lee reported the separation of plastic waste of acrylonitrile-butadiene-styrene as well as high impact polystyrene by using froth floating technique after the coating of zinc oxide and microwave treatment [36] (Figure 2).

Figure 2. (a) Froth flotation and ZnO coating-microwave (MW) treatment for the separation of plastics mixture of acrylonitrile-butadiene-styrene (ABS) and high impact polystyrene (HIPS), (b,c,d) presentation of surface changes in acrylonitrile-butadiene-styrene (ABS) and high impact polystyrene (HIPS) before and after ZnO coating-microwave (ZnO-MW) treatment [36]. Reprinted with permission [36]. Copyright 2017 Springer.

The hydrophilicity of acrylonitrile-butadiene-styrene on coating of zinc oxide and microwave treatment was more enhanced as compared to treated high impact polystyrene (**Figure 2b,c,d**) which resulted in the sinking of acrylonitrile-butadiene-styrene in the flotation cell [84]. The treated high impact polystyrene floated over the solution (**Figure 2a**) and after 2, 3, 4 and 5 minutes, the floating recoveries were 100 %, 95.2 %, 80.4 %, and 81 % respectively. Thus, after 2 minutes, zinc oxide coated acrylonitrile-butadiene-styrene (100% sinking) and high impact polystyrene (100% floating) became completely separated from the plastic mixture (**Figure 2a**). In another work, froth flotation method was used to separate the toxic poly(vinyl chloride) from mixture of plastic wastes including polystyrene [35] (**Figure 3**). The surface of plastics was treated with calcium hypochlorite for separation process. Poly(vinyl chloride) was effectively distinguished from mixture of plastics wastes with 0.37 % residue (**Figure 3**). Another plastics, mainly poly(acrylonitrile-co-butadiene-co-styrene) (8.04%) and poly(methyl methacrylate) (8.37%) were also collected with purified poly(vinyl chloride). The polarity and surface roughness of poly(vinyl chloride) were increased by treating with calcium hypochlorite, that led to enhanced surface wettability [85]. The different molecular structure of plastics was responsible for the different floating characteristics of plastics. Wang and Wang developed an environment-friendly froth flotation technique with Fenton treatment for the separation of polyvinyl chloride from plastic mixture consisting of polystyrene and polycarbonate [33]. On Fenton treatment, the floating capability of polystyrene and polycarbonate was decreased selectively but it remained unaffected in case of polyvinyl chloride. The wettability of substance was evaluated by measuring contact angle. The contact angle for polyvinyl chloride showed very small change after Fenton treatment but it was decreased for polystyrene and polycarbonate from 92.87° to 76.32° and 91.14° to 78.87° respectively. The surface wettability was increased

because of reduction in contact angle [86]. According to FT-IR and XPS analysis, due to the introduction of polar groups on Fenton treatment, hydrophilicity of polystyrene and polycarbonate was increased [87]. The surface roughness of treated polystyrene and polycarbonate was enhanced as confirmed by SEM morphology. The reported purity and recovery of separated polyvinyl chloride were 99.26 % and 100 % respectively.

Figure 3. Separation of plastic mixture [35]. PS: polystyrene, PC: polycarbonate, PET: poly(ethylene terephthalate), ABS: poly(acrylonitrile-co-butadiene-co-styrene), PMMA: poly(methyl methacrylate), PVC: poly(vinyl chloride). Reprinted with permission [35]. Copyright 2017 Springer.

Marta Vila-Cortavitarte and co-workers explored the various benefits that came through the substitution of bitumen with polystyrene in the asphalt mixture [26]. They have used three different types of recycled polystyrene wastes: general purpose polystyrene, high impact

polystyrene and polystyrene from hangers as additives in the concrete mixture. The core motive of this work was to reduce the concentration of bitumen in asphalt mixtures since emissions of carbon from bitumen can pollute the environment. The replacement rates of 1% and 2% by polystyrene in asphalt mixture corresponded to the 23% and 46% of total bitumen. The mixture with 2 % was discarded because of cohesion problem. Every sample was passed through a set of tests to compare the modified mechanical properties. A mixture having 1 % of replaced bitumen by polystyrene showed the higher number of voids with improved mechanical properties. The results showed that replacement of bitumen by polystyrene reduced the environmental issue, contributed to the life cycle assessment [88].

The proper development of the catalyst leads to obtain desirable products with low cost [89]. Tertiary recycling is being used to get most profit of plastic wastes, hydrocarbons are being produced [90]. Metal as catalyst for decline of polystyrene was decorated with montmorillonite [31]. Polystyrene solid waste was converted into ethylbenzene, toluene, α -methylstyrene and styrene by using 5 % Al/ montmorillonite and 20 % Fe/montmorillonite as catalyst [31]. The amount of 8.49 % (wt./wt.), 5.13 % (wt./wt.), 49.28 % (wt./wt.) and 2.80 % (wt./wt.) was reported for toluene, ethylbenzene, styrene and α -methylstyrene respectively utilizing 5% Al/ montmorillonite and 10.15 % (wt./wt.), 6.42 % (wt./wt.), 50.93 % (wt./wt.) and 2.31 % (wt./wt.) respectively utilizing 20% Fe/montmorillonite. Tuffi et al. investigated the thermal degradation for mixed plastics wastes of polystyrene, polypropylene, polyethylene film and poly(ethylene terephthalate) [25]. The Kissinger-Akahira-Sunose technique was used to perform the kinetic study. The activation energy for pyrolytic of polystyrene, poly(ethylene terephthalate), polypropylene and polyethylene was found in the range of $0.25 < \alpha < 0.85$. Thermal degradation of mixture with more polypropylene was performed through single step. The temperature,

composition and structure were the factors that influenced the thermal behavior of mixed plastics waste. The risk of fire can be reduced by introducing flame retardants into inflammable materials [91]. Plastic samples can be evaluated for their flame retardants content in regard to reduce the risk from fire [92]. In one of work, amount of 26,000,000 ng bromophenols (tetrabromobisphenol A)/g was reported in acrylonitrile butadiene styrene whereas it was 330,000 ng Σ hexabromocyclododecane stereoisomers/g for polystyrene [34].

Outline

For a greener environment as well as to reduce the plastic waste disposal, petroleum based materials need to be replaced with biodegradable, recyclable and renewable polymers. Recycling of plastics wastes will minimize the global warming and enhance the sustainability. Recycling of plastics is the need of closed loop cycle that should meet the rules of circular economy. Mechanical recycling is the shortest track to reuse the plastics waste. From economy point of view, chemical recycling is not suitable for petroleum based plastics because petrochemical feedstocks are cheaper as compared to process. Biological recycling produces mainly carbon dioxide and water as final products that can be used in life cycle through photosynthesis. Thus biological recycling is the longest track and can only be applied if mechanical cycling and chemical cycling are not usable.

Acknowledgement

Sourbh Thakur acknowledges financial support by ESF program Postdoctoral Fellowship project No 09.3.3-LMT-K-712-02-0180.

References

* of special interest

* * of outstanding interest

- [1] R. Narayan, Carbon footprint of bioplastics using biocarbon content analysis and life-cycle assessment, *MRS Bull.* 36 (2011) 716–721.
- [2]** X. Zhang, M. Fevre, G.O. Jones, R.M. Waymouth, Catalysis as an Enabling Science for Sustainable Polymers, *Chem. Rev.* (2017).
- [3] R. Wei, W. Zimmermann, Microbial enzymes for the recycling of recalcitrant petroleum-based plastics: how far are we?, *Microb. Biotechnol.* (2017).
- [4] J. Hopewell, R. Dvorak, E. Kosior, Plastics recycling: challenges and opportunities, *Philos. Trans. R. Soc. Lond. B Biol. Sci.* 364 (2009) 2115–2126.
- [5]** N. Singh, D. Hui, R. Singh, I.P.S. Ahuja, L. Feo, F. Fraternali, Recycling of plastic solid waste: A state of art review and future applications, *Compos. Part B Eng.* 115 (2017) 409–422.
- [6] B. Gewert, M.M. Plassmann, M. MacLeod, Pathways for degradation of plastic polymers floating in the marine environment, *Environ. Sci. Process. Impacts.* 17 (2015) 1513–1521.
- [7] M.A. Gondal, M.N. Siddiqui, Identification of different kinds of plastics using laser-induced breakdown spectroscopy for waste management, *J. Environ. Sci. Health Part A.* 42 (2007) 1989–1997.
- [8] E.J. North, R.U. Halden, Plastics and environmental health: the road ahead, *Rev. Environ. Health.* 28 (2013) 1–8.
- [9] J.R. Jambeck, R. Geyer, C. Wilcox, T.R. Siegler, M. Perryman, A. Andrady, R. Narayan, K.L. Law, Plastic waste inputs from land into the ocean, *Science.* 347 (2015) 768–771.

- [10] S.E. Nelms, E.M. Duncan, A.C. Broderick, T.S. Galloway, M.H. Godfrey, M. Hamann, P.K. Lindeque, B.J. Godley, Plastic and marine turtles: a review and call for research, *ICES J. Mar. Sci.* 73 (2015) 165–181.
- [11] C. Wilcox, E. Van Sebille, B.D. Hardesty, Threat of plastic pollution to seabirds is global, pervasive, and increasing, *Proc. Natl. Acad. Sci.* 112 (2015) 11899–11904.
- [12] A.L. Andrady, Plastics in the Oceans, *Plast. Environ. Sustain.* (2015) 295–318.
- [13]* P. Europe, Plastics-The Facts 2013: An analysis of European latest plastics production, demand and waste data, *Plast. Eur.* (2013) 1–40.
- [14] L. Gu, T. Ozbakkaloglu, Use of recycled plastics in concrete: A critical review, *Waste Manag.* 51 (2016) 19–42.
- [15] J. Vehlow, B. Bergfeldt, H. Hunsinger, K. Jay, F.E. Mark, L. Tange, D. Drohmann, H. Fisch, Recycling of bromine from plastics containing brominated flame retardants in state-of-the-art combustion facilities, APME Forschungszentrum Karlsr. EBFRIAP APME Rep. 8040 (2002).
- [16]** C. Ma, J. Yu, B. Wang, Z. Song, J. Xiang, S. Hu, S. Su, L. Sun, Chemical recycling of brominated flame retarded plastics from e-waste for clean fuels production: A review, *Renew. Sustain. Energy Rev.* 61 (2016) 433–450.
- [17] P. UNION, Directive 2008/50/EC of the European Parliament and of the Council of 21 May 2008 on ambient air quality and cleaner air for Europe, 2008.
- [18] U. EPA, Municipal solid waste generation, recycling, and disposal in the United States: facts and figures for 2012, (2014).
- [19] J. Gertsakis, H. Lewis, Sustainability and the waste management hierarchy, Retrieved January. 30 (2003) 2008.

- [20] K. Hamad, M. Kaseem, F. Deri, Recycling of waste from polymer materials: An overview of the recent works, *Polym. Degrad. Stab.* 98 (2013) 2801–2812.
- [21] S.L. Wong, N. Ngadi, T.A.T. Abdullah, I.M. Inuwa, Current state and future prospects of plastic waste as source of fuel: A review, *Renew. Sustain. Energy Rev.* 50 (2015) 1167–1180.
- [22] C. Wu, M.A. Nahil, N. Miskolczi, J. Huang, P.T. Williams, Processing real-world waste plastics by pyrolysis-reforming for hydrogen and high-value carbon nanotubes, *Environ. Sci. Technol.* 48 (2013) 819–826.
- [23] F. Sasse, G. Emig, Chemical recycling of polymer materials, *Chem. Eng. Technol.* 21 (1998) 777–789.
- [24] D. Hirayama, C. Saron, Morphologic and mechanical properties of blends from recycled acrylonitrile-butadiene-styrene and high-impact polystyrene, *Polymer*. 135 (2018) 271–278.
- [25] R. Tuffi, S. D’Abramo, L.M. Cafiero, E. Trinca, S.V. Cipriotti, Thermal behavior and pyrolytic degradation kinetics of polymeric mixtures from waste packaging plastics., *Express Polym. Lett.* 12 (2018).
- [26]** M. Vila-Cortavitarte, P. Lastra-González, M.Á. Calzada-Pérez, I. Indacoechea-Vega, Analysis of the influence of using recycled polystyrene as a substitute for bitumen in the behaviour of asphalt concrete mixtures., *J. Clean. Prod.* 170 (2018) 1279–1287.
- [27]** T.P. Wagner, Reducing single-use plastic shopping bags in the USA, *Waste Manag.* 70 (2017) 3–12.
- [28] M. Jang, W.J. Shim, G.M. Han, M. Rani, Y.K. Song, S.H. Hong, Widespread detection of a brominated flame retardant, hexabromocyclododecane, in expanded polystyrene marine

- debris and microplastics from South Korea and the Asia-Pacific coastal region, *Environ. Pollut.* 231 (2017) 785–794.
- [29] J.M. Campolina, C.S.L. Sigrist, J.M.F. de Paiva, A.O. Nunes, V.A. da Silva Moris, A study on the environmental aspects of WEEE plastic recycling in a Brazilian company, *Int. J. Life Cycle Assess.* (2017) 1–12.
- [30] M. Râpă, E. Matei, P.N. Ghioca, E. Grosu, L. Iancu, B. Spurcaci, A.R. Trifoi, T. Gherman, A. Pica, A.M. Predescu, IMPROVEMENT OF SOME POST-CONSUMER POLYPROPYLENE (rPP) BY MELT MODIFICATION WITH STYRENE-DIENE BLOCK COPOLYMERS., *Environ. Eng. Manag. J. EEMJ.* 16 (2017).
- [31] J. Shah, M.R. Jan, Metal decorated montmorillonite as a catalyst for the degradation of polystyrene, *J. Taiwan Inst. Chem. Eng.* 80 (2017) 391–398.
- [32]* K. Ragaert, L. Delva, K. Van Geem, Mechanical and chemical recycling of solid plastic waste, *Waste Manag.* (2017).
- [33]* J. Wang, H. Wang, Fenton treatment for flotation separation of polyvinyl chloride from plastic mixtures, *Sep. Purif. Technol.* 187 (2017) 415–425.
- [34]* K. Pivnenko, K. Granby, E. Eriksson, T.F. Astrup, Recycling of plastic waste: Screening for brominated flame retardants (BFRs), *Waste Manag.* 69 (2017) 101–109.
- [35]** J. Wang, H. Wang, C. Wang, L. Zhang, T. Wang, L. Zheng, A novel process for separation of hazardous poly (vinyl chloride) from mixed plastic wastes by froth flotation, *Waste Manag.* 69 (2017) 59–65.
- [36]* N.T.T. Truc, B.-K. Lee, Combining ZnO/microwave treatment for changing wettability of WEEE styrene plastics (ABS and HIPS) and their selective separation by froth flotation, *Appl. Surf. Sci.* 420 (2017) 746–752.

- [37] M. Poletto, Mechanical, dynamic mechanical and morphological properties of composites based on recycled polystyrene filled with wood flour wastes, *Maderas Cienc. Tecnol.* (2017) 0–0.
- [38] C. Deng, Y. Li, J. Li, Y. Chen, H. Li, Emission characteristics of PBDEs during flame-retardant plastics extruding process: field investigation and laboratorial simulation, *Environ. Sci. Pollut. Res.* 24 (2017) 22450–22457.
- [39] S. Messal, T. Zeghloul, A. Mekhalef-Benhafssa, K. Medles, L. Dascalescu, Experimental study of a tribo-aero-electrostatic separator for finely-grinded matter, *J. Electrostat.* 89 (2017) 59–68.
- [40] O. Rozenstein, E. Puckrin, J. Adamowski, Development of a new approach based on midwave infrared spectroscopy for post-consumer black plastic waste sorting in the recycling industry, *Waste Manag.* 68 (2017) 38–44.
- [41]** S.D.A. Sharuddin, F. Abnisa, W.M.A.W. Daud, M.K. Aroua, Energy recovery from pyrolysis of plastic waste: Study on non-recycled plastics (NRP) data as the real measure of plastic waste, *Energy Convers. Manag.* 148 (2017) 925–934.
- [42] K.S. Kumar, P.V. Premalatha, K. Baskar, Evaluation of Transport Properties of Concrete Made With E-Waste Plastic, *J. Test. Eval.* 45 (2016).
- [43] J.E. Rutkowski, E.W. Rutkowski, Recycling in Brasil: Paper and Plastic Supply Chain, *Resources.* 6 (2017) 43.
- [44] N.E. Zander, M. Gillan, D. Sweetser, Composite Fibers from Recycled Plastics Using Melt Centrifugal Spinning, *Materials.* 10 (2017) 1044.
- [45] J. Shah, M.R. Jan, Recovery of Valuable Hydrocarbons from Waste Polystyrene Using Zinc Supported Catalysts, *J. Polym. Environ.* 25 (2017) 759–769.

- [46] Y.V. Vazquez, S.E. Barbosa, Compatibilization Strategies for Recycling Applications of High Impact Polystyrene/Acrylonitrile Butadiene Blends, *J. Polym. Environ.* 25 (2017) 903–912.
- [47] V. K. Thakur, E. Jin Tan, M.-F. Lin, P. See Lee, Polystyrene grafted polyvinylidenefluoride copolymers with high capacitive performance, *Polym. Chem.* 2 (2011) 2000–2009. doi:10.1039/C1PY00225B.
- [48] H. Li, X. Sui, X.-M. Xie, High-strength and super-tough PA6/PS/PP/SEBS quaternary blends compatibilized by using a highly effective multi-phase compatibilizer: Toward efficient recycling of waste plastics, *Polymer*. 123 (2017) 240–246.
- [49] T. Zeghloul, A.M. Benhafssa, G. Richard, K. Medles, L. Dascalescu, Effect of particle size on the tribo-aero-electrostatic separation of plastics, *J. Electrostat.* 88 (2017) 24–28.
- [50] V.K. Thakur, D. Vennerberg, M.R. Kessler, Green aqueous surface modification of polypropylene for novel polymer nanocomposites, *ACS Appl. Mater. Interfaces*. 6 (2014) 9349–9356.
- [51] K. Kositkanawuth, A. Bhatt, M. Sattler, B. Dennis, Renewable Energy from Waste: Investigation of Co-pyrolysis between Sargassum Macroalgae and Polystyrene, *Energy Fuels*. 31 (2017) 5088–5096.
- [52] S. Thakur, P.P. Govender, M.A. Mamo, S. Tamulevicius, Y.K. Mishra, V.K. Thakur, Progress in lignin hydrogels and nanocomposites for water purification: Future perspectives, *Vacuum*. 146 (2017) 342–355. doi:10.1016/j.vacuum.2017.08.011.
- [53] S. Thakur, P.P. Govender, M.A. Mamo, S. Tamulevicius, V.K. Thakur, Recent progress in gelatin hydrogel nanocomposites for water purification and beyond, *Vacuum*. 146 (2017) 396–408. doi:10.1016/j.vacuum.2017.05.032.

- [54] M.E. Tawfik, S.B. Eskander, G. Nawwar, Hard wood-composites made of rice straw and recycled polystyrene foam wastes, *J. Appl. Polym. Sci.* 134 (2017).
- [55] J. Cui, S. Tan, R. Song, Universal Ni-Mo-Mg catalysts combined with carbon blacks for the preparation of carbon nanotubes from polyolefins, *J. Appl. Polym. Sci.* 134 (2017).
- [56] T.A. Bayoumi, M.E. Tawfik, Immobilization of sulfate waste simulate in polymer-cement composite based on recycled expanded polystyrene foam waste: Evaluation of the final waste form under freeze-thaw treatment, *Polym. Compos.* 38 (2017) 637–645.
- [57] J.A. Salbidegoitia, E.G. Fuentes, M.P. González-Marcos, J.R. González-Velasco, Recycle of plastic residues in cellular phones through catalytic hydrocracking to liquid fuels, *J. Mater. Cycles Waste Manag.* 19 (2017) 782–793.
- [58] J. Garcia-Ivars, X. Wang-Xu, M.-I. Iborra-Clar, Application of post-consumer recycled high-impact polystyrene in the preparation of phase-inversion membranes for low-pressure membrane processes, *Sep. Purif. Technol.* 175 (2017) 340–351.
- [59] E. Esmacili, F. Deymeh, S.A. Rounaghi, Synthesis and characterization of the electrospun fibers prepared from waste polymeric materials, *Int. J. Nano Dimens.* 8 (2017) 171–181.
- [60] J. Savoldelli, D. Tomback, H. Savoldelli, Breaking down polystyrene through the application of a two-step thermal degradation and bacterial method to produce usable byproducts, *Waste Manag.* 60 (2017) 123–126.
- [61] S.R. Mallampati, B.H. Lee, Y. Mitoma, C. Simion, Selective sequential separation of ABS/HIPS and PVC from automobile and electronic waste shredder residue by hybrid nano-Fe/Ca/CaO assisted ozonisation process, *Waste Manag.* 60 (2017) 428–438.
- [62] S.R. Mallampati, B.H. Lee, Y. Mitoma, C. Simion, Heterogeneous nano-Fe/Ca/CaO catalytic ozonation for selective surface hydrophilization of plastics containing brominated

- and chlorinated flame retardants (B/CFRs): separation from automobile shredder residue by froth flotation, *Environ. Sci. Pollut. Res.* 24 (2017) 4469–4479.
- [63] N.T.T. Truc, C.-H. Lee, B.-K. Lee, S.R. Mallampati, Development of hydrophobicity and selective separation of hazardous chlorinated plastics by mild heat treatment after PAC coating and froth flotation, *J. Hazard. Mater.* 321 (2017) 193–202.
- [64] B.A. Herki, J.M. Khatib, Valorisation of waste expanded polystyrene in concrete using a novel recycling technique, *Eur. J. Environ. Civ. Eng.* 21 (2017) 1384–1402.
- [65] W. Li, S. Ma, Y. Hu, X. Shen, HYDRATION AND MICROSTRUCTURE OF BLENDED CEMENT WITH SODIUM POLYSTYRENE SULFONATE, *Ceramics–Silikáty.* 61 (2017) 172–177.
- [66] Y.V. Vazquez, S.E. Barbosa, Process Window for Direct Recycling of Acrylonitrile-Butadiene-Styrene and High-Impact Polystyrene from Electrical and Electronic Equipment Waste, *Waste Manag.* 59 (2017) 403–408.
- [67] B. Beccagutti, L. Cafiero, M. Pietrantonio, S. Pucciarmati, R. Tuffi, S. Vecchio Cipriotti, Characterization of Some Real Mixed Plastics from WEEE: A Focus on Chlorine and Bromine Determination by Different Analytical Methods, *Sustainability.* 8 (2016) 1107.
- [68] S. Honus, S. Kumagai, O. Němček, T. Yoshioka, Replacing conventional fuels in USA, Europe, and UK with plastic pyrolysis gases–Part I: Experiments and graphical interchangeability methods, *Energy Convers. Manag.* 126 (2016) 1118–1127.
- [69] L.D. Silvarrey, A.N. Phan, Kinetic study of municipal plastic waste, *Int. J. Hydrog. Energy.* 41 (2016) 16352–16364.

- [70] E. Franco-Urquiza, H.E. Ferrando, D.P. Luis, M. MasPOCH Rulduà, Mechanical recycling of plastic wastes. Case of study: high impact polystyrene for manufacturing TV components shelf, *Afinidad Rev. Quím. Teórica Apl.* 73 (2016) 227–236.
- [71] G.-L. Zhuang, H.-H. Tseng, M.-Y. Wey, Feasibility of using waste polystyrene as a membrane material for gas separation, *Chem. Eng. Res. Des.* 111 (2016) 204–217.
- [72] Y.V. Vazquez, S.E. Barbosa, Recycling of mixed plastic waste from electrical and electronic equipment. Added value by compatibilization, *Waste Manag.* 53 (2016) 196–203.
- [73] P. Lastra-González, M.A. Calzada-Pérez, D. Castro-Fresno, Á. Vega-Zamanillo, I. Indacoechea-Vega, Comparative analysis of the performance of asphalt concretes modified by dry way with polymeric waste, *Constr. Build. Mater.* 112 (2016) 1133–1140.
- [74] P.F. Sommerhuber, T. Wang, A. Krause, Wood–plastic composites as potential applications of recycled plastics of electronic waste and recycled particleboard, *J. Clean. Prod.* 121 (2016) 176–185.
- [75] A. Shalbafan, J.T. Benthien, H. Lerche, Biological Characterization of Panels Manufactured from Recycled Particleboards using Different Adhesives, *BioResources.* 11 (2016) 4935–4946.
- [76] C. Wang, H. Wang, G. Gu, Q. Lin, L. Zhang, L. Huang, J. Zhao, Ammonia modification for flotation separation of polycarbonate and polystyrene waste plastics, *Waste Manag.* 51 (2016) 13–18.
- [77] M.R.M. Hasan, B. Colbert, Z. You, A. Jamshidi, P.A. Heiden, M.O. Hamzah, A simple treatment of electronic-waste plastics to produce asphalt binder additives with improved properties, *Constr. Build. Mater.* 110 (2016) 79–88.

- [78] F. Pita, A. Castilho, Influence of shape and size of the particles on jigging separation of plastics mixture, *Waste Manag.* 48 (2016) 89–94.
- [79] A. Demirbas, O. Taylan, Recovery of gasoline-range hydrocarbons from petroleum basic plastic wastes, *Pet. Sci. Technol.* 33 (2015) 1883–1889.
- [80] W. Aksa, K. Medles, M. Rezoug, R. Ouiddir, A. Bendaoud, L. Dascalescu, Modeling and optimization of a separator for granular mixtures composed of multiple insulating materials, *IEEE Trans. Ind. Appl.* 51 (2015) 4743–4751.
- [81] V. Ramesh, S. Mohanty, M. Biswal, S.K. Nayak, Effect of Reprocessing and Accelerated Weathering on Impact-Modified Recycled Blend, *J. Mater. Eng. Perform.* 24 (2015) 5046–5053.
- [82] X. Yang, L. Sun, J. Xiang, S. Hu, S. Su, Pyrolysis and dehalogenation of plastics from waste electrical and electronic equipment (WEEE): A review, *Waste Manag.* 33 (2013) 462–473.
- [83] G. Martinho, A. Pires, L. Saraiva, R. Ribeiro, Composition of plastics from waste electrical and electronic equipment (WEEE) by direct sampling, *Waste Manag.* 32 (2012) 1213–1217.
- [84] H. Wang, X. Chen, Y. Bai, C. Guo, L. Zhang, Application of dissolved air flotation on separation of waste plastics ABS and PS, *Waste Manag.* 32 (2012) 1297–1305.
- [85] T. Carvalho, F. Durão, C. Ferreira, Separation of packaging plastics by froth flotation in a continuous pilot plant, *Waste Manag.* 30 (2010) 2209–2215.
- [86] E. Chamarro, A. Marco, S. Esplugas, Use of Fenton reagent to improve organic chemical biodegradability, *Water Res.* 35 (2001) 1047–1051.

- [87] Y. Zou, J.N. Kizhakkedathu, D.E. Brooks, Surface modification of polyvinyl chloride sheets via growth of hydrophilic polymer brushes, *Macromolecules*. 42 (2009) 3258–3268.
- [88] R. Yang, H. Ozer, I.L. Al-Qadi, Regional upstream life-cycle impacts of petroleum products in the United States, *J. Clean. Prod.* 139 (2016) 1138–1149.
- [89] J. Sokółowski, G. Rokicki, M. Marczewski, K. Szewczyk, Thermal-catalytic recycling of polyolefins and polystyrene, *Czas. Tech. Chem.* 105 (2008) 311–321.
- [90] N. Miskolczi, L. Bartha, A. Angyal, High energy containing fractions from plastic wastes by their chemical recycling, in: *Macromol. Symp.*, Wiley Online Library, 2006: pp. 599–606.
- [91] W.H. Organization, Flame retardants: a general introduction., *Environ. Health Criteria*. (1997).
- [92] L.S. Birnbaum, D.F. Staskal, Brominated flame retardants: cause for concern?, *Environ. Health Perspect.* 112 (2004) 9.

Highlights

- Plastic solid waste is a burning global issue.
- Recycling of plastic solid waste is useful from economic and environmental points of view
- Polystyrene based plastics are useful in numerous applications.

Graphical Abstract

2018-03-27

Recent developments in recycling of polystyrene based plastics

Thakur, Sourbh

Elsevier

Thakur S, Verma A, Sharma B, et al., (2018) Recent developments in recycling of polystyrene based plastics. *Current Opinion in Green and Sustainable Chemistry*, Volume 13, October 2018, pp. 32-38

<https://doi.org/10.1016/j.cogsc.2018.03.011>

Downloaded from Cranfield Library Services E-Repository