Recent progress in sodium alginate based sustainable hydrogels for environmental applications

Sourbh Thakur^{a,b*}, Bhawna Sharma^b, Ankit Verma^b, Jyoti Chaudhary^b, Sigita Tamulevicius^a, Vijay Kumar Thakur^{c*}

^a*Institute of Materials Science of Kaunas University of Technology, K. Barsausko Str. 59, LT-51423 Kaunas, Lithuania*

^b*School of Chemistry, Shoolini University, Solan 173212, Himachal Pradesh, India*

^c*Enhanced Composites and Structures Center, School of Aerospace, Transport and Manufacturing, Cranfield University, Bedfordshire MK43 0AL, UK*

ABSTRACT

Recently, there is a growing research interest in the applications and development of novel sustainable hydrogel materials in waste water treatment because of radically distinctive chemical and physical characteristics of hydrogels such as hydrophilicity, swell ability and modifiability to name a few. Hydrogels have exposed the hypernym functioning in the removal of a wide range of aqueous pollutants containing toxic dyes and heavy metal ions. A large amount of water gets incorporated in the three dimensional networks of hydrophilic structures of hydrogels. The prime objective of this review article is to render a presentation on the recent advances in the modifications of sodium alginate based hydrogels for the adsorptive removal of toxic pollutants. In addition, article also briefly gives the classification and properties of hydrogels and alginate.

Keywords: Alginate; sodium alginate based hydrogel; dye and metal removal; water purification.

*Corresponding authors Email: thakursourbh@gmail.com, sourbh.sourbh@ktu.lt,
vijay.kumar@cranfield.ac.uk

1. Introduction

Recently, there has been a noticeable growth in the development of hydrogels composite and their applications in various fields including environmental remediation (Khan and Lo, 2016a; Li et al., 2013; Sahiner and Seven, 2014; Thakur et al., 2015, 2017b, 2017a). In regard to wastewater treatment, hydrogels based composites have exhibited superior performance in the adsorptive removal of different types of inorganic pollutants as well as organic pollutants (Mahdavinia et al., 2016; Ngah and Fatinathan, 2008; rights are reserved by Shivani and Shetye, n.d.). In many studies, hydrogels composites have clearly outcompeted the conventional adsorbents especially in terms of adsorption capacity (Burkert et al., 2007). Hydrogels are three-dimensional, polymeric networks capable of absorbing large amount of water (Zhao et al., 2013). Hydrogels based composites have been tailored to grab most of the applications to get more functional features such as maximum equilibrium swelling, high rate of absorption, less residual content, porosity, uniformly soft, high durability, odorless, photo-stability (Ahmed, 2015; Gao et al., 2011). Hydrogels composites are chemically and physically stable, smooth, flexible polymeric network, reusable and multi-functional in nature. These flexible polymeric materials upholds the ability to swell and retain a consequential amount of water within their structure, but without being dissolved in water (Shetye et al., 2015). In the past 50 years, hydrogels have received appreciable attention from worldwide research community, due to their wide-ranging research interest moreover, many application holdings make this field more acceptable (Khan and Lo, 2016a). Research interest in the field of environmental science has been increasing with emphasis on use of bio-based hydrogels for advanced applications (Khan and Lo, 2016a). One of

1
2
3
4 the major challenges is the recovery of hydrogel from solution after the completion of the
5
6 adsorption or desorption process, especially in micro or nano-sized hydrogel (Izawa and
7
8 Kadokawa, 2010). The selective removal and recovery of a targeted pollutants are the challenges
9
10 because the co-present ingredients in wastewater often create unwanted competition and
11
12 interference (F. Zhao et al., 2015). Furthermore, there have been some stability concerns for
13
14 hydrogels composites which affect their fate and reusability (Roy et al., 2010).
15
16

17
18 It's been about many decades since research work is going on hydrogels and this field may come
19
20 up with the dream of drought-free planet by purifying waste water (Fane et al., 2015). Although
21
22 water purification by hydrogels is well set up by the various adsorption techniques but it quietly
23
24 necessitates further improvements concerning degradability, intrinsic cellular interactions and
25
26 strong mechanical properties in the different dynamic environment (Du et al., 2015). After
27
28 acknowledging different research works of this field, we can define the ideal characteristics of
29
30 hydrogels, along with the novel advancements in the material science (Vermonden et al., 2012a).
31
32 Moreover, by overcoming the limitations of hydrogels in water treatment domain, we may build
33
34 faith of society on water purification technologies because it promises the most practical and
35
36 economic option for water purification from industrial and laboratory waste. In this article, we
37
38 have made a platform for the upgraded hydrogel networks in relevance to the water treatment
39
40 mission. In addition, template hydrogel materials stands up with many benefits in different fields
41
42 like chemical catalysis, nano-engineering, nano-medicines, nano-energy and especially for
43
44 reactions occurring in aqueous media (**Figure 1**) (Sahiner, 2013). The proven efficiencies of
45
46 different chemical modifications has now been attracting the researchers to redesign and
47
48 synthesize hydrogels with metal nano-particles *in situ* or *ex situ* (Lee and Mooney, 2001). Most
49
50 of the work that has been done in one dimensional or two dimensional materials like surfactants
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 or film, here is the applicable approach to generate three dimensional material with exterior and
5
6 interior porous topography offers multifunctional utility. Recently, *in situ* approach of metal
7
8 nano-particles with hydrogels is opening a new era on account of its fabulous properties such as
9
10 optical, chemical, electronic and magnetic properties (Sahiner, 2013). Although many alternates
11
12 may come out in future to solve the problem of aggregation of metal nano-particles and also their
13
14 non-symmetrical behaviour in-between flexible hydrogel network. Despite the unique
15
16 characteristics of these polymeric networks, science is yet not able to predict the quantitative
17
18 mechanical response of the hydrogels based on their physico-chemical properties which limits
19
20 our research ability to design something new (Wang et al., 2017). This review article focuses on
21
22 the recent developments in sodium alginate based hydrogels and composites for water
23
24 purification. The classification of hydrogels, synthesis of hydrogels and composites along with
25
26 the properties of alginate have been discussed in this article.
27
28
29
30
31
32

33 **2. Method**

34
35
36 Potential adsorption from bio-renewable resources involves development of the most commercial
37
38 polymers based products for environmental application. The bio-based polymeric hydrogels have
39
40 proved their efficiencies many times and also have added an advantage of bio-degradation in an
41
42 aqueous media. Among numerous hydrogels, sodium alginate based hydrogels have allured the
43
44 research interest for number of applications due to their inbuilt physico-chemical nature. But this
45
46 research field is still in an early stage of development with bounded information regarding
47
48 literature of sodium alginate based hydrogels for water remediation. In this article, the data
49
50 collection involved several steps, started from the classification, preparation, utilization and
51
52 reusability of hydrogels to the recent advancements in sodium alginate loaded hydrogels for the
53
54 removal of organic and inorganic pollutants. The development of “Sodium Alginate based
55
56
57
58
59
60
61
62
63
64
65

Hydrogels” initiatives, require inclusive knowledge on alginate based materials and different sustainable materials for new tailored properties and applications. The synthesis and applications of novel innovative materials from alginate will improve the horizon of sustainable hydrogels as well as possibly address the problem of lack of human friendly/biocompatible tissues and scaffolds materials. Therefore, we summarize various efforts of researchers all around the globe to develop new sustainable hydrogel materials for environmental applications from alginate based polymers in the present manuscript. This perspective article in tends to show that developed hydrogels from bio-renewable resources can be efficiently prepared and executed as potential environmental friendly, biodegradable and economic materials. This reviews some important questions about the potential use of “Sustainable Biomaterials” in advanced applications including environmental engineering.

3. Classification of Hydrogels

Hydrogel products can be classified on several bases (Ahmed, 2015):

3.1. Based onSource

Source means a thing or person from which something is obtained. So, on the basis of source, these polymeric materials can be classified into two categories: synthetic or natural source (Nayak et al., 2010). The natural polymeric materials show profitable bio-compatibility, bio-degradability but these are far behind in case of mechanical properties. However, on the other hand, there is a lack of bio-active properties in synthetic polymeric material.

3.2. According to Polymeric Composition

Composition simply means “act of combining of elements to form a whole”. On the basis of this, hydrogel products have been categorized into the following: (a) hydrogels belong to the polymer network consisting of basic structural monomer unit formed via homo-polymerization (Qiu and

1
2
3
4 Park, 2001). Homo-polymer hydrogels are those polymer systems which emerge from single unit
5
6 of monomers and comprises of normal auxiliary segment of any polymer framework. There
7
8 might be some possibility of having cross-linked skeletal structures, which depends upon the
9
10 polymerization technique as well as nature of the monomer being used; **(b)** co-polymeric
11
12 hydrogels are the chemical compounds of high molecular weight made up of two or more
13
14 different monomer subunits with not less than one hydrophilic component organized in a
15
16 random, block or alternating configuration across the chain of the polymer network (Thakur,
17
18 2016); **(c)** multi-polymer interpenetrating polymeric hydrogels, the salient class of hydrogels that
19
20 consist of two different cross-linked components of synthetic or natural polymer, arranged in a
21
22 network form (Shetye et al., 2015). This class is further split up into semi-interpenetrating
23
24 polymeric hydrogel in which one of the hydrogel component is non-cross-linked another is
25
26 cross-linked polymer or monomer.
27
28
29
30
31
32

33 **3.3. Based on Configuration**

34
35 These are generally based on the physical arrangement and reactant (chemical) composition of
36
37 the hydrogel and can be classified as: **(a)** amorphous (no apparent organization), **(b)** semi-
38
39 crystalline (imperfectly crystalline) (Thoniyot et al., 2015a); it is a mixture of distinct as well as
40
41 indistinct (amorphous) phases, **(c)** crystalline (regular arrangement of atoms in space lattice), **(d)**
42
43 hydrogen bonded hydrogels.
44
45
46
47

48 **3.4. Based on Type of Cross-linking**

49
50 This class has two different division of cross-linked network of hydrogels based on their
51
52 chemical /physical nature (Caló and Khutoryanskiy, 2015). Physical networks have been found
53
54 to exhibit temporary junctions that appear from physical relations like ionic interactions,
55
56 hydrogen bonds, or hydrophobic interactions (L. Z. Zhao et al., 2015) whereas, chemically cross-
57
58
59
60
61
62
63
64
65

1
2
3
4 linked networks have unchanging junctions. This is generally achieved by using physical
5
6 activities like coalition, conglomeration, connection, crystallization, difficulty and hydrogen
7
8 bonding. Conversely, a chemical procedure is a process in which incorporated bivalent cross-
9
10 linking is idolized to assemble a synthetic hydrogel. Physical hydrogels are
11
12 convertible/reversible in nature due to the in-formational augmentations, while synthetic
13
14 hydrogels are unchangeable/long lasting in nature. Cross-linking makes the network viscoelastic
15
16 which provides hardness and stickiness to the structure.
17
18
19
20

21 **3.5. Based on Physical Appearance**

22
23 The outward composition of hydrogel film or microsphere depends on the technique of
24
25 polymerization, cross-linking or any other preparation process.
26
27

28 **3.6. Classification According to Network Electrical Charge**

29
30 This classification is divided into four main types based on the presence/absence of electrical
31
32 charge pointed on the double cross-linked chains (Ahmed, 2015): **(a)** neutral (non-ionic) gels; **(b)**
33
34 ionic gels (including anionic or cationic); **(c)** amphoteric electrolyte (containing both acidic as
35
36 well as basic groups); **(d)** zwitter-ionic (having anionic and cationic groups together in each
37
38 structural repeating unit).
39
40
41
42

43 **4. Preparation of Hydrogels**

44
45 Hydrogels are commonly defined as semi-solid, three-dimensional, polymeric networks obtained
46
47 from a class of synthetic or natural polymers (collagen, gelatin, starch, alginate etc.) which can
48
49 retain significant amount of water and biological fluids (Shi et al., 2011). During the hydration
50
51 process, the structure of polymeric network is created by the domains or hydrophilic groups
52
53 (Talaat et al., 2008). Preparation of hydrogels is based on hydrophilic monomers (polar part first
54
55 to be hydrated) and hydrophobic monomers (forms hydrophobically-bounded water) are
56
57
58
59
60
61
62
63
64
65

sometimes used to control the properties for specific applications (Can et al., 2007), (Thoniyot et al., 2015a). Traditionally, chemical polymerization techniques are used in case of synthetic polymers that form hydrogels. The mechanical strength of the synthetic polymers has been reported to cause slow degradation rate, but on the other hand, it provides the durability as well (Mehrali et al., 2017). Hydrogels are mainly synthesized using polar monomers and their preparation starts from initiation reaction and ends up at termination. In addition, three fundamental parts (**Figure 2**) of the hydrogels preparation are monomer, cross-linker and initiator (Ahmed, 2015). For example, Thakur et al., prepared sodium alginate based hydrogels by a polymerization technique employing acrylic acid as monomer, N,N'-methylenebisacrylamide and potassium persulphate as cross-linker and initiator respectively (Thakur and Arotiba, n.d.). Diluents like water and biological fluids can be used to control the final hydrogel properties and the heat of polymerization (Ma et al., 2010). Starting materials can be optional and is divided into synthetic polymers, natural polymers or combination of both. A number of polymerization methods can be adopted to form hydrogels: **(a)** Bulk polymerization means two or more monomers are combined with the help of suitable initiator for the formation of hydrogel. In this polymerization, monomers make homogeneous composition of hydrogels. **(b)** Solution polymerization/cross-linking means ionic and neutral monomers are reacted together with suitable cross-linking agent. The reaction is initiated with the help of UV-irradiation or using a redox initiator system. **(c)** Suspension polymerization or inverse-suspension polymerization means monomers as well as initiator are diffused as a homogenous mixture in the hydrocarbon phase. **(d)** Polymerization by irradiation means high energy radiations such as like electron beams/gamma rays etc are employed as an initiator to prepare the hydrogel (Karadağ et

al., 2001) and (e) grafting to a support means for increases the mechanical properties of the hydrogel, hydrogels are coated with the strong grafting agents.

5. Preparation of Hydrogels Composite

Hydrogels composite have been advanced by adding a wide range of nano-materials (metallic, polymeric, carbon-based) (Merino et al., 2015; Shin et al., 2011; Zuo et al., 2015). Nano-materials can be incorporated within the bulk hydrogel framework. Five basic methods have been used to obtain a uniform distribution (Thoniyot et al., 2015a): (a) preparation of hydrogel in a nano-particle suspension, (b) addition of the nano-particles into hydrogel matrix after gelation, (c) reactive nano-particle preparation within a preformed hydrogel, (d) hydrogels nano-composite via cross-linking and (e) development of hydrogel nano-composite using polymers, metallic nano-particles and different gelator molecules (Khan and Lo, 2016a).

5.1. Preparation of Hydrogel in Nano-particle Suspension

The perfect technique to build hydrogel composites is the gelation of nano-particles suspension in hydrogel matrix. Through this technique, hydrogel composites becomes optically and mechanically responsive (Omidian et al., 2006). In this technique, monomers, cross-linkers and nano-particles are combined to form hydrogel composites through gelation (Thakur et al., 2016). This technique is the easiest technique for the synthesis of hydrogel composites. Serksen et al., synthesized optomechanically N-isopropyl acrylamide/acrylamide hydrogel matrix by adding gold nano-particles through gelation using initiator ammonium persulfate and accelerator tetramethylethylenediamine (Serksen et al., 2002). The hydrogel applications in the mechanical field can be enhanced by adding the nano-particles into the hydrogel matrix.

5.2. Addition of Nano-particles into Hydrogel Matrix after Gelation

1
2
3
4 In this method, nano-particles are added in the hydrogel matrix after the gelation process. Yissar
5 et al., added gold nano-particles into polymer hydrogel matrix after the electro polymerization
6
7 (Pardo-Yissar et al., 2001). Electro polymerization cannot be achieved in the presence of the
8
9 gold nano-particles because of aggregation of gold nano-particles in electric field (Kim and
10
11 Randall Lee, 2006). In this work, cross-linked polyacrylamide gels were prepared on gold-wire
12
13 electrodes by the electro-polymerization of acrylamide along with ZnCl_2 and N, N'
14
15 methylenebisacrylamide.
16
17
18
19
20

21 **5.3. Reactive Nano-particle Preparation within Preformed Hydrogel**

22
23 Langer's group formulated this technique, which consists of precursors loading into a hydrogel
24
25 matrix, rather than formed nano-particles (Wang et al., 2004). For example, hydrogel network
26
27 containing embedded Au (III) ions with thiol groups was produced. Hydrogel matrix containing
28
29 thiol group was able to modulate gold nano-particles formation on the addition of a reducing
30
31 agent. This prompted the arrangement of hydrogel composites with un-collected nano-particles
32
33 (Thoniyot et al., 2015a; Wu et al., 2013). A modified technique of nano-particle synthesis within
34
35 hydrogel matrix in the absence of thiol group was developed by Saravanan et al., (Saravanan et
36
37 al., 2007). Ag nano-particle/polyacrylamide composite was synthesised by free-radical cross-
38
39 linking polymerization using acrylamide and Ag (II) ions aqueous solution. Comparison between
40
41 the non-Ag-loaded polyacrylamide gel and Ag-loaded polyacrylamide nano-composite hydrogels
42
43 showed remarkable enhancement in the properties of swelling along with the electron transfer
44
45 resistance. These properties were found to depend on the amount of Ag nano-particles in the
46
47 hydrogel.
48
49
50
51
52
53

54 **5.4. Hydrogel nano-composites via Cross-linking**

55
56
57
58
59
60
61
62
63
64
65

Hydrogel composites can be synthesized by using semiconductor nano-particle as a cross-linker. Zhang et al., prepared semiconductor hydrogel nano-composites by self-polymerization in the presence of light (Zhang et al., 2013). In this technique, mainly four parts were used: **(a)** H₂O, **(b)** semiconductor nano-particles of zinc oxide, titanium dioxide, Fe₂O₃, tin dioxide, cadmium selenide or cadmium telluride, all nano-particles were water soluble, **(c)** N, N-dimethyl acrylamide and **(d)** clay nano-sheets. Semiconductor nano-particles were used to initiate the self-polymerization of N, N-dimethyl acrylamide (Paddon et al., 2013). Authors mentioned that cadmium selenide and cadmium telluride were capable to synthesize strong hydrogel even in the presence of visible light. They also recommended that valuable nano-particles can be immobilized in hydrogels for their aggregate application in the sake of joining their mechanical and physiochemical properties. Additionally, the declared result for this hydrogel demonstrated superb mechanical quality (most noteworthy compressive nature of 4.153 MPa and inflexibility 1.535 MPa) and high adaptability (most extraordinary protracting of 2784 %).

5.5. Hydrogel Composites Formation using Nano-particles, Polymers and Distinct Gelator Molecules

Wu et al., 2013 prepared silicon based anodes by adding silicon nano-particles into a conducting polymer hydrogel (Wu et al., 2013). A well-developed three-dimensional structure of conducting polymer hydrogel with silicon nano-particles was produced through *in situ* polymerization. The following interactions were described in the synthesis of this hydrogel: **(a)** hydrogen bonding between silicon surface and phytic acid, **(b)** electrostatic interaction among silicon surface and positively charged aniline polymer. The viscous hydrogel mixture became dark green because of phytic acid gelator (C. Wang et al., 2013). Such a hierarchical hydrogel system merges with different important characteristics including persistent electrically conductive polyaniline

1
2
3
4 network, binding with the Si surface through either the cross-linker hydrogen bonding with
5
6 phytic acid or electrostatic interaction with the positively charged polymer and porous space for
7
8 volume development of Si particles. The developed materials demonstrated cycle life of 5,000
9
10 cycles with more than 90% limits maintenance at current thickness of 6.0A g⁻¹.
11
12
13

14 **6. Biodegradability of Hydrogels**

15
16 To nullify the environmental effects of solid wastes, bio-degradable polymers are now emerging
17
18 as an alternate for non-biodegradable polymeric materials (Li et al., 2012). For the fabrication of
19
20 any bio-degradable material such as bio-plastics, the material is designed to develop some
21
22 changes in its chemical behaviour under fixed environmental conditions (Kaith et al., 2015). Bio-
23
24 degradability is one of the environment-friendly responses of the hydrogels that ensures its utility
25
26 in target drug delivery applications as hydrogels degraded by simple aqueous breakdown are
27
28 extensively used for drug distribution. However, the hydrogels degraded by enzymes are
29
30 regarded as site specific transporting carriage materials. This is due to the fact that enzymes lie
31
32 over the restricted sites of the body (Bouhadir et al., 2001). Usually, hydrogels are degraded by
33
34 different types of methods (**Figure 3**) for example, a novel approach was developed by Kaith et
35
36 al., using composting method and soil burial to degrade hydrogels within 77 days of contact
37
38 (Kaith et al., 2015). In another work, Jeon et al., developed bio-degradable alginate based photo
39
40 cross-linked hydrogels for tissue engineering application. They have designed the material with
41
42 the ester linkages which was hydrolytically degradable during photo polymerization reaction
43
44 (Jeon et al., 2009). Similarly, bio-degradable oligopeptide cross-linked polymethacrylic acid
45
46 based hydrogel was developed by Knipe et al., which was used to deliver protein in small
47
48 intestine. The enzymatic degradation was catalyzed by the trypsin enzymes present inside the
49
50 small intestine (Knipe et al., 2015). In conclusion, because of better bio-degradability of
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

hydrogels, they can be considered as the pioneer material for fulfilling various targets of the medical line.

7. Reusability of Hydrogels

From the economic point of view, hydrogels are most appropriate as their adsorption limit doesn't reduce after a couple of recoveries and reuses (Pakdel and Peighambaroust, 2018). In hydrogels, high adsorption limit, fast adsorption rate, high mechanical quality, biodegradability, broad pH values and reusability are sensible for significant metals and dye removal. (Pakdel and Peighambaroust, 2018). The ordinary reusability of the hydrogel has also been shown demonstrated by rehashing the adsorption–desorption procedure (Vivek and Prasad, 2015), while keeping up an adequate execution (Chiew et al., 2016). Hydrogel has been found to show an incredible degree of extraordinary characteristics for reusability. Upto five adsorption-desorption cycle hydrogel were found to give good results (Yi et al., 2018). Reusability of adsorbent is one of the fundamental parameter in the functional applications of wastewater treatment (Awual et al., 2015, 2014). Yi et al. examined the reusability of sodium alginate/polyvinyl alcohol/graphene oxide hydrogel with five cycle's tests (Yi et al., 2018). It was concluded from the detailed analysis that the adsorptive property for Cu(II) and UO₂(II) was diminished after the main sorption-desorption cycle and afterward without tremendous assortment until the fifth cycle, showing that sodium alginate/polyvinyl alcohol/graphene oxide microspheres can be reused in numerous cycles without basic adversity in its adsorption characteristics (Yi et al., 2018). Recovery and reusability of the hydrogel were considered utilizing methyl orange as adsorbate by Balachandran and Edamana in 2015 (Vivek and Prasad, 2015). The approximate time period of 20 minute was reported for desorption process and 97 % of the colour was recovered. The execution of the hydrogel for five cycles was incredible (90-98

1
2
3
4 %). Chiew et al. have explored the mechanical stability of calcium alginate and alginate-
5
6 halloysite nano-composite beads for the removal of Pb(II) ions. Reusability was summarized up
7
8 to ten successive cycles and percentage desorption was continued to exist at 94 % for both type
9
10 of composite beads (Chiew et al., 2016).
11
12

13 14 **8. Utilization of Hydrogel Products**

15
16 Hydrogels have been utilized in the field of target drug delivery applications due to their
17
18 distinctive physical properties. The sponge like porous network of hydrogels makes them
19
20 compatible for filling multiple types of drugs inside their three dimensional matrix (Vermonden
21
22 et al., 2012b). The percentage drug release is managed by the diffusion coefficient of the micro
23
24 and macromolecules. Hydrogels have been leading as candidate material for tissue engineering
25
26 because of their uncommon structural resemblances with the extracellular matrix (Kim et al.,
27
28 2015; Yang et al., 2014). Based on the innovative research worldwide, new opportunities are
29
30 coming to conquer the challenges of this field due to their capability to command the surface
31
32 morphology and shapes during cell transplantation. It has attended numerous examinations
33
34 focused on explorations transporting carriage material for bio-active substances or as a platform
35
36 for organizing the cells and to certain the growth of targeted tissues (Kamata et al., 2015;
37
38 Seliktar, 2012). In addition to all leading properties of hydrogels, it can also be changed into
39
40 defined geometries and purpose of this is to control cell shape and to bring specified biomimetic
41
42 design. The physico-chemical properties of the hydrogels can be changed in accordance to the
43
44 specified natural cells or tissue by controlling its cross-linking and polymer chemistry in order to
45
46 bring out required biological results (Rosales and Anseth, 2016; Uto et al., 2017). The success of
47
48 stem cell culture exclusively depends upon targeted differentiation and it is believed that
49
50 homogenous hydrogel surfaces are convenient for the differentiation of stem cells (Higuchi et al.,
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

2013). Flexible and soft conductors are valuable parts of bioelectronics that are useful in biomedical applications. Conductive hydrogels can be effectively used as soft conductors because of their molecular resemblance to soft tissues and high water absorption ability. Recently, hydrogels have been utilized in supercapacitors, energy storage, human health monitoring and electronic skin to name a few (Han et al., 2017; Oh et al., 2016). The adsorption mechanism of hydrogels is now emerging as feasible option to acquire sustainable approach towards water treatment mission. The reusability of hydrogels has been revealed by regaining the adsorption capacity by many consecutive cycles (Khan and Lo, 2016b; Liu et al., 2017) and this property makes it as economical material for challenging rest of the developing techniques.

9. Alginate (Natural Polysaccharide)

Alginate comprises of 30-60% of brown algae. In account of its chemical and physical properties, it has been extensively studied due to its ability to form gels and micro-particles (Goh et al., 2012; Khotimchenko et al., 2001; Lee and Mooney, 2012; Pawar and Edgar, 2012; Pereira et al., 2013; Thakur, 2016, 20016). For example, Pereira et al prepared alginate based film for bio-medical applications. The alginate based hydrogel thin film composed of alginate and aloe vera gel was used for the treatment of skin. Alginate mixtures are considered to be bio-compatible, safe, perishable and non-immunogenic (Paques et al., 2014). It can be marked as anionic biopolymer consisting of mannuronic and guluronic acid units in the irregular blocks (You et al., 2001). The mannuronic acid forms β (1 $\rightarrow$ 4) linkages and guluronic acid forms α (1 $\rightarrow$ 4) linkages. The mannuronic and guluronic acid units are joined by glycosidic linkages. Guluronic acid segments exhibit rigid and bended conformations that provides stiffness to the molecular chains (de Vos et al., 2006).

9.1. Alginate Hydrogels

1
2
3
4 Alginate hydrogels can be designed via cross-linking the polymer chains. The physical and
5
6 chemical properties of the alginate hydrogels are dependent on cross-linking density, type of
7
8 cross-linking along with the molecular weight (Franklin and Ohman, 2002). For example, Chan
9
10 et al., synthesized alginate cross linked network based on external and internal gelation method.
11
12 The prepared sample was utilized for coating and drug delivery of living system (Chan et al.,
13
14 2006). One of the suitable method for the formation of alginate hydrogels is inter-molecular
15
16 cross-linking in which only guluronic groups of alginate participate with divalent cation such as
17
18 calcium (El-Sherbiny, 2010). Numerous divalent cations show distinctive affinity towards
19
20 alginate but calcium is more often used for alginate gelation. The properties of alginate
21
22 hydrogels such as solubility, hydrophobicity and biological activity can be improved by
23
24 modifying alginate through their available hydroxyl and carboxyl groups (Zimmermann et al.,
25
26 1992).
27
28
29
30
31
32

33 **9.2. Alginate Modification**

34
35
36 Molecular adaptations generally depends on three imperative factors namely reactivity, solubility
37
38 and characterization (Pawar and Edgar, 2012a) as shown in **Figure 4**.
39
40

41 **9.2.1. Solubility**

42
43 The dissolvability of alginates in water is represented by three parameters: **(a)** pH of the
44
45 dissolvable, **(b)** ionic quality of the medium and **(c)** nearness of gelling particles in the
46
47 dissolvable. The solvency of alginates depends emphatically on the condition of the spine
48
49 carboxylic acid groups. For derivatization, alginate mixtures can be dissolved in natural aqueous
50
51 and organic or combined aqueous-organic media. The possibility of solvent system can impose
52
53 the variety of reagents which can be used for modification (Galant et al., 2006).
54
55
56
57

58 **9.2.2. Reactivity**

59
60
61
62
63
64
65

The two secondary -OH positions (C-2 and C-3) or the one carboxylic group at C-6 position can be modified in alginate mixtures. The reactivity difference between these two functionalities can be useful for selective modifications (Donati et al., 2003). Because of little reactivity differences, selection for the modification is challenging for both positions. The reaction can be controlled in terms of selective modification of the mannuronic and guluronic block residues. The action of alginates towards acids, bases and diminishing agents cannot be ignored when performing derivatization responses. Aggressive degradation responses can cause quick sub-atomic weight reduction in short periods (Yang et al., 2011).

9.2.3. Characterization

In order to realize the chemical substitution configurations in the alginate derivatives, there is always a need of various alginate samples within a range of mannuronic/guluronic value. For the detailed understanding of the substitution patterns, (Kim et al., 2000) derivatization of alginate mixture is required in mannuronic and guluronic blocks. More facilitated analytical techniques are often required to study the complex nature of the alginate co-polysaccharide backbone. Because of the unpredictable nature of the alginate co-polysaccharide backbone, utilization of cutting edge investigative methods is most vital.

10. Sodium Alginate

Sodium alginate is a product of many unprocessed sugars. It has the capability to be dissolved in both cold and hot water with strong stirring. In presence of divalent calcium ion, sodium alginate builds a gel without any need of heat. In modern food technology, sodium alginate is used to create spheres in which sodium alginate is blended with calcium salts (Eghbalifam et al., 2015). In food industry, sodium alginate is used to increase viscous nature of liquids, as an emulsifier (Mahdavinia et al., 2016) as well as making tasteless indigestion tablets (Park and Kim, 2001).

11. Sodium Alginate based Hydrogels for Water Purification

Sodium alginate based hydrogels have been used in wastewater treatment (Belhouchat et al., 2017; Bhattacharyya and Ray, 2015; Fan et al., 2013; Fatin-Rouge et al., 2006; Gao et al., 2011; Hosseinzadeh and Abdi, 2017; Karthiga Devi et al., 2016; Lakouraj et al., 2014; Lam et al., 2017; Lu et al., 2015; Mahdavinia et al., 2013; Ngah and Fatinathan, 2008; Rashidzadeh et al., 2015; Ren et al., 2016; Tally and Atassi, 2016; Thakur, 2016; Thakur et al., 2016; Thakur and Arotiba, 2017, n.d.; W. Wang et al., 2013b, 2013a; Wu et al., 2017; Zhuang et al., 2016) (**Table 1**), (**Table 2**). Mahdavinia et al., prepared kappa-carrageenan-sodium alginate/montmorillonite (CarAlg/MMt) hydrogel nano-composite by using acrylamide as monomer (Mahdavinia et al., 2013). The synthesized hydrogel nano-composite was utilized for the adsorption of cationic crystal violet dye from water. The maximum adsorption capacity obtained was found to be 88.8 mg g⁻¹. The basic Na-montmorillonite (Na-MMt) clay and hydrogel nano-composite containing 0.25 g and 0.5 g of basic Na-MMt (CarAlg/MMt0.25, CarAlg/MMt0.5) were characterized by XRD. A sharp diffraction peak at $2\theta = 7.6^\circ$ with d-spacing of 11.61 Å confirmed the basic Na-MMt. The peak at $2\theta = 7.6^\circ$ vanished due to the intercalation of Na-MMt clay in the matrix of nano-composite. In the TEM image of CarAlg/MMt0.25, the black and fine lines correspond to Na-MMt layers. The surface of hydrogel without clay (CarAlg) was found to be smooth and tight. The surface became porous after the addition of Na-MMt nanoclay into the hydrogel. The adsorption kinetics was used to measure the expected equilibrium time for adsorption of crystal violet dye (Mahdavinia et al., 2013). The adsorption of crystal violet dye was sharply increased at the beginning and then became constant. The equilibrium time of 2 hours was reported for dye adsorption. The dye adsorption capacity was increased by adding Na-MMt clay in hydrogel. The rate of adsorption of dye was increased with the amount of clay in hydrogel. The formation of

active centers because of porosity was the cause of increase in speed of crystal violet adsorption by the hydrogel nano-composite (Wang et al., 2008). The maximum adsorption capacity of 88.8 mg g⁻¹ was achieved by the CarAlg/MMt0.5 sample.

Sodium alginate-g-poly(acrylic acid-co-acryl amide)/clinoptilolite hydrogel nano-composite was synthesized through free radical polymerization technique (Rashidzadeh et al., 2015). The developed hydrogel nano-composite was utilized for the removal of methylene blue dye and 94.34 mg g⁻¹ was the maximum adsorption capacity. FTIR spectrum of sodium alginate-g-poly(acrylic acid-co-acryl amide)/clinoptilolite, sodium alginate-g-poly(acrylic acid-co-acryl amide) and methylene blue adsorbed sodium alginate-g-poly(acrylic acid-co-acryl amide)/clinoptilolite are given in **Figure 5a-c**. In **Figure 5a** and **5b**, the absorption bands at 1650 cm⁻¹ and 1450 cm⁻¹ were due to sodium alginate and carboxylate stretching respectively. Broad band at 3000-3500 cm⁻¹ was due to the stretching of hydroxyl groups of the polysaccharide. The shift in the -COOH, -OH adsorption band in the spectrum of methylene blue adsorbed sodium alginate-g-poly(acrylic acid-co-acryl amide)/clinoptilolite (**Figure 5c**) indicated the adsorption of methylene blue dye onto sodium alginate-g-poly(acrylic acid-co-acryl amide)/clinoptilolite hydrogel nano-composite. The sodium alginate-g-poly(acrylic acid-co-acryl amide)/clinoptilolite hydrogel nano-composite was composed of pores with size of ten microns as indicated in SEM morphology (**Figure 5d**). Adsorption mechanism was explained on the basis of change in colour of sodium alginate-g-poly(acrylic acid-co-acryl amide) hydrogel (**Figure 6a,c**) and sodium alginate-g-poly(acrylic acid-co-acryl amide)/clinoptilolite hydrogel nano-composite (**Figure 6b,d**) after the adsorption of methylene blue dye. The electrostatic attraction between amide and carboxylic of sodium alginate-g-poly(acrylic acid-co-acryl amide)/clinoptilolite hydrogel nano-composite and imine groups of methylene blue dye was responsible for adsorption of dye.

1
2
3
4 Wu et al., prepared sodium alginate/ β -cyclodextrin/graphene oxide hydrogel nano-composite
5
6 adsorbent for the adsorption of methylene blue dye (Wu et al., 2017). The graphene oxide used
7
8 for the synthesis of hydrogel nano-composite was produced by an improved Hummers method.
9
10 The highest adsorption capacity of synthesized adsorbent was 133.24 mg g⁻¹. The thickness of 1
11
12 to 2 nm and micro meter-sized planes of graphene oxide was confirmed by atomic force
13
14 microscopy analysis (**Figure 7a**). TEM image of graphene oxide with broken surface is shown in
15
16 **Figure 7f**. The colour of sodium alginate/ β -cyclodextrin/graphene oxide hydrogel nano-
17
18 composite was faint yellow whereas colour of methylene blue loaded sodium alginate/ β -
19
20 cyclodextrin/graphene oxide hydrogel nano-composite was dark blue black (**Figure 7b**). The
21
22 faint yellow colour of sodium alginate/ β -cyclodextrin/graphene oxide hydrogel nano-composite
23
24 was due to the presence of graphene oxide. The porous and honeycomb-like structure of sodium
25
26 alginate/ β -cyclodextrin/graphene oxide adsorbent was confirmed by SEM morphology (**Figure**
27
28 **7c-e**). The adsorption of methylene blue onto sodium alginate/ β -cyclodextrin/graphene oxide
29
30 hydrogel nano-composite was explained via hydrogen bonding, π - π interaction and electrostatic
31
32 attraction (Heidarizad and Şengör, 2016) as represented in **Figure 8**.
33
34
35
36
37
38
39
40

41 Thakur et al., prepared titania incorporated sodium alginate/acrylic acid hydrogel nano-
42
43 composite for the adsorption of methylene blue dye from aqueous solution (Thakur et al., 2016).
44
45 The reported maximum adsorption capacity was 2257.36 mg g⁻¹. The synthesis of hydrogel
46
47 nano-composite was explained by free radical polymerization of acrylic acid onto sodium
48
49 alginate using potassium persulphate and N,N'-methylenebisacrylamide as initiator and cross-
50
51 linker respectively. The adsorption mechanism of methylene blue dye was explained by
52
53 electrostatic attraction (between TiO₂ or COO⁻ and cationic dye) and hydrogen bonding
54
55 (between OH and imines groups of dye) (Pourjavadi et al., 2014) (**Figure 9**).
56
57
58
59
60
61
62
63
64
65

1
2
3
4 Ternary hydrogel nano-composite of graphene oxide/sodium alginate/polyacrylamide has been
5
6 synthesized for the adsorption of cationic as well as anionic dyes (Fan et al., 2013). The
7
8 developed ternary hydrogel nano-composite was ionically cross-linked by using Ca(II) ion. On
9
10 applying stress, the pure polyacrylamide hydrogel was destroyed (**Figure 10a-c**). However,
11
12 graphene oxide/sodium alginate/polyacrylamide hydrogel nano-composite was not destroyed on
13
14 applying stress (**Figure 10d-f**). On the removal of stress, graphene
15
16 oxide/sodiumalginate/polyacrylamide hydrogel nano-composite regained its original shape. The
17
18 possible scheme for graphene oxide/sodium alginate/polyacrylamide ternary hydrogel nano-
19
20 composite is shown in **Figure 10g**. Intercalation of layered structure graphene oxide with
21
22 hydrogel network was presented. The mechanical stability of hydrogel nano-composite was
23
24 improved by the exchange of load among graphene oxide nanosheets and polymer chains.
25
26 Ionically cross-linked as well as covalently cross-linked polymers were presented in hydrogel
27
28 network. Also, polymer chains of hydrogel interacted with graphene oxide nanosheets through
29
30 hydrogen bonding. The sponge-like morphology was reported for hydrogel samples as shown in
31
32 **Figure 11**. The structure of polyacrylamide and sodium alginate/polyacrylamide hydrogels
33
34 contained holes with uniform size (**Figure 11a-c**). The lamellar and dense structures were
35
36 formed after the addition of graphene oxide into the hydrogel network (**Figure 11d-f**). The
37
38 change in colour of different dyes after the adsorption by sodium alginate/polyacrylamide
39
40 hydrogel nano-composite is represented in **Figure 12**. The following interactions were used to
41
42 explain the adsorption mechanism: (a) amino and azo functional group of dye with carboxylic
43
44 functional groups of hydrogel nano-composite, (b) π - π interactions between aromatic groups.
45
46
47
48
49
50
51
52
53
54
55

56 Sodium alginate based silver hydrogel nano-composite was developed by one step green method
57
58 (Karthiga Devi et al., 2016). Devi et al., have used this hydrogel nano-composite for methylene
59
60
61
62
63
64
65

1
2
3
4 blue dye removal and 213.7 mg g^{-1} was the maximum adsorption capacity reported. Synthesis of
5
6 silver nano-particles was performed by reduction with *M. maderaspatna* extract. Silver nano-
7
8 particles were characterized by using UV-vis-spectrophotometric analysis. The band at 443 nm
9
10 confirmed the formation of silver nano-particles (A Bhosale and M Bhanage, 2015). Hydrogel
11
12 beads were synthesized by gelation process of sodium alginate and carbopol 937. Finally, silver
13
14 nano-particles introduced into the hydrogel beads led to the formation of silver nano-composite
15
16 for dye adsorption studies. The crystalline structure and size of silver nano-composite was
17
18 analyzed by XRD, diffraction peaks at 28° , 32° , 38° , 46° , 54° , 57° , 76° with planes (1 1 1), (2 0
19
20 0), (2 1 0), (2 2 0), (3 1 1), (2 2 2), (4 2 0) corresponded to crystalline silver nano-particles. TEM
21
22 analysis was used to verify the size and shape of the silver nano-particles containing carbopol-
23
24 alginate hydrogel beads. The reported average crystal size was about 19.3 nm with uniform
25
26 shape.
27
28
29
30
31
32

33
34 The emulsion micelle has been incorporated into the vinyl-functionalized sodium alginate-co-
35
36 methyl acrylic acid-co-italic acid hydrogel for the formation of nano-porous hydrogel (W. Wang
37
38 et al., 2013b). This synthesized nano-porous hydrogel was used for the removal of Pb(II) ion
39
40 from aqueous solution. Three dimensional network of vinyl-functionalized sodium alginate-co-
41
42 methyl acrylic acid-co-italic acid hydrogel was developed through free radical polymerization
43
44 reaction (**Figure 13**). The reaction between sodium alginate and glycidyl methacrylate led to the
45
46 introduction of vinyl groups on sodium alginate. The sulfate anion radicals were produced by
47
48 hemolytic breakage of ammonium persulfate (Buchholz and Graham, 1998). The chain
49
50 propagation step was carried out in between radicals, vinyl-functionalized sodium alginate chain
51
52 and monomers. Different chains of sodium alginate were cross-linked through methyl acrylic
53
54 acid and italic acid polymer chains. Emulsion micelles were formed by sodium dodecyl sulfonate
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 and n-Octane, which were introduced into the cross-linked hydrogel network. Nano porous
5
6 hydrogel was formed after the removal of emulsion micelles as shown in **Figure 13**. The peaks
7
8 at δ 3.55–4.01 and δ 4.86 were due to the non-anomeric and anomeric protons in the ^1H NMR
9
10 spectrum of sodium alginate (**Figure 14a**). New peaks were represented in the vinyl-
11
12 functionalized sodium alginates hydrogel due to presence of methyl protons and methacryloyl
13
14 double bonded hydrogen's at δ 1.80 ppm and δ 5.60, δ 6.02 ppm, respectively. In ^{13}C NMR
15
16 spectrum of sodium alginate, peaks in the range of δ 63.5–102.18 ppm were due to the sugar
17
18 carbons of sodium alginate (**Figure 14b**). The following new peaks were observed in the ^{13}C
19
20 NMR spectrum of vinyl-functionalized sodium alginate: (a) δ 19.46 ppm due to methyl carbon,
21
22 (b) δ 129.28 and δ 138.31 ppm assigned to vinyl carbons, (c) δ 171.86 ppm due to carbonyl
23
24 carbon. Hence, modification of sodium alginate with glycidyl methacrylate and incorporation of
25
26 vinyl groups on the sodium alginate matrix were confirmed by these NMR results. The ^1H NMR
27
28 and ^{13}C NMR spectrum of vinyl-functionalized sodium alginate was identical to modified cashew
29
30 gum with glycidyl methacrylate, indicating mechanism of modification for sodium alginate and
31
32 cashew gum with glycidyl methacrylate was identical (Guilherme et al., 2005). Ring opening
33
34 mechanism was believed to take place between sodium alginate with glycidyl methacrylate⁹¹.
35
36 The smooth and dense surface without any pore was observed in the morphology of vinyl-
37
38 functionalized sodium alginate-co-methyl acrylic acid-co-italic acid hydrogel (**Figure 15a**).
39
40 However, structure with uniform pores (20–60 nm) was obtained after the addition of emulsion
41
42 micelle into the vinyl-functionalized sodium alginate-co-methyl acrylic acid-co-italic acid
43
44 (**Figure 15b-d**).
45
46
47
48
49
50
51
52
53
54

55 Sodium alginate-g-polyacrylic acid/polyvinylpyrrolidone/gelatin granular hydrogel was
56
57 synthesized through grafting and cross-linking using gelatin, acrylic acid and
58
59
60
61
62
63
64
65

polyvinylpyrrolidone (W. Wang et al., 2013a). The developed sodium alginate-g-polyacrylic acid/polyvinylpyrrolidone/gelatin granular hydrogel was utilized for the adsorption of heavy metal ions. The adsorption capacity for Ni(II), Cu(II), Zn(II) and Cd(II) was found to be 3.028 mmol g⁻¹, 3.146 mmol g⁻¹, 2.911 mmol g⁻¹ and 2.862 mmol g⁻¹ respectively. The sodium alginate-g-polyacrylic acid/polyvinylpyrrolidone/gelatin granular hydrogel was prepared by chemical and physical reactions (Pourjavadi et al., 2008) (**Figure 16**). The H⁺ of acrylic acid was used to generate electro positivity on polyvinylpyrrolidone and gelatin. Hence, polyvinylpyrrolidone and gelatin were interacted with sodium alginate and grafted polyacrylic chains through electrostatic and hydrogen-bonding. These interactions among polyvinylpyrrolidone, gelatin, sodium alginate and acrylic acid led to formation of granular hydrogel. **Figure 17a** shows the gel like photograph of sodium alginate-g-polyacrylic acid hydrogel. After the addition of polyvinylpyrrolidone and gelatin, shape of sodium alginate-g-polyacrylic acid hydrogel was converted into the granular (**Figure 17b**). This granular shape of hydrogel was maintained in the dry state (**Figure 17c**). Sodium alginate-g-polyacrylic acid hydrogel exhibited smooth surface (**Figure 17d**), whereas sodium alginate-g-polyacrylic acid/polyvinylpyrrolidone/gelatin granular hydrogel displayed rough and porous surface (**Figure 17e**). Adsorption capacity and recovery capability of the sodium alginate-g-polyacrylic acid/polyvinylpyrrolidone/gelatin granular hydrogel for various metal ions were investigated. The adsorption capacity of sodium alginate-g-polyacrylic acid/polyvinylpyrrolidone/gelatin granular hydrogel for Cu(II) ion was the highest. The recovery ability of sodium alginate-g-polyacrylic acid/polyvinylpyrrolidone/gelatin granular hydrogel was increased with increased in the hydrogel dosage. For 2.8 g L⁻¹ dosage, reported recovery percentages were 90.92 (Cu(II)), 87.70 (Ni(II)), 87.47 (Zn(II)) and 85.55 (Cd(II)).

Gao et al., have produced hydrogel composite composed of sodium alginate, sodium acrylate and medical stone (Gao et al., 2011). Various heavy metal ions (Ni(II), Cu(II), Zn(II) and Cd(II)) were removed by using sodium alginate-g-sodium acrylate/medical stone hydrogel composite. A smooth and non-porous surface was shown by sodium alginate-g-sodium acrylate hydrogel (**Figure 18a**) whereas medical stone exhibited rough and sheet surface (**Figure 18b**). The rough surface with pores and gap was formed on the addition of medical stone into sodium alginate-g-sodium acrylate hydrogen (**Figure 18c**). It was analyzed that surface roughness was increased with increase in medical stone amount in sodium alginate-g-sodium acrylate/medical stone hydrogel composite (**Figure 18d**). Equilibrium heavy metal ions adsorption capacities for active carbon, medical stone and hydrogel composite with different amounts of medical stone were examined. The adsorption capacities for hydrogel composite with different amount of medical stone were found to be higher in comparison to active carbon and medical stone. Many carboxylate groups in hydrogel composite were found to form complexes with heavy metal ions during adsorption process.

Alginate/reduced graphene oxide double network hydrogel nano-composite was developed using facile method by Zhuang et al. (Zhuang et al., 2016). An adsorption capacity of 169.5 mg g^{-1} and 72.5 mg g^{-1} was reported for Cu(II) and $\text{Cr}_2\text{O}_7^{2-}$ respectively by utilizing alginate/reduced graphene oxide double network hydrogel nano-composite. The schematic representation of hydrogel synthesis is presented in **Figure 19**. The reduced graphene oxide was formed by reduction of graphene oxide and alginate beads were developed through the addition of sodium alginate liquid into the CaCl_2 solution. Three dimensional networks of alginate and two dimensional networks of graphene oxide were produced from the alginate/graphene composite. Another three dimensional interpenetrates networks were formed by reduced graphene oxide,

1
2
3
4 which led to the formation of double network (**Figure 20**). Many particles like morphologies
5
6 were observed in the SEM image of graphene–alginate single networks (**Figure 20a**), while
7
8 alginate/reduced graphene oxide double-network has shown petal-like morphology (**Figure 20b**).
9
10 The particle morphology of graphene–alginate single networks was not in accordance with
11
12 oxygen element distribution (**Figure 20c**) whereas morphology of alginate/reduced graphene
13
14 oxide double-network was in accordance with oxygen distribution (**Figure 20d**). Hence, it was
15
16 concluded that hydrogen bonds played a crucial role in the production of three dimensional
17
18 networks by reduced graphene oxide. The hydrogen bonding between reduced graphene oxide
19
20 and alginate led to formation of uniform structure of graphene–alginate single networks, while
21
22 hydrogen bonding among the sheets of graphene led to the development of three dimensional
23
24 networks in reduced graphene oxide. In this work, the researchers have concluded that double
25
26 network structure in prepared hydrogel composite enhanced the adsorption capacity as well as
27
28 provided the evidences of repeated usage after many cycles of chemisorptions.
29
30
31
32
33
34
35

36 Tally et al., have synthesized sodium alginate-g-poly(acrylic acid-co-acrylamide) hydrogel by
37
38 utilizing microwave oven (Tally and Atassi, 2016). An adsorption capacity of 480.77 mg g^{-1} has
39
40 been reported for Pb(II) ion removal using sodium alginate-g-poly(acrylic acid-co-
41
42 acrylamide)hydrogel. Adsorption of Cd(II), Ni(II) and Cu(II) by sodium alginate-g-poly(acrylic
43
44 acid-co-acrylamide) hydrogel has been also analyzed. Sodium n-dodecyl benzenesulfonate was
45
46 used to produce pore forming micelles in sodium alginate-g-poly(acrylic acid-co-acrylamide)
47
48 hydrogel. Spherical micelles were formed by sodium n-dodecyl benzenesulfonate at fixed
49
50 concentration, which were introduced in the sodium alginate-g-poly(acrylic acid-co-acrylamide)
51
52 hydrogel network. After washing, sodium n-dodecyl benzenesulfonate micelles were removed,
53
54 which led to the formation of pores in sodium alginate-g-poly(acrylic acid-co-acrylamide)
55
56
57
58
59
60
61
62
63
64
65

hydrogel (**Figure 21**). **Figure 22** represents XRD spectra for alginate, poly(acrylic acid-co-acrylamide) and sodium alginate-g-poly(acrylic acid-co-acrylamide) hydrogel. The crystalline nature was decreased on grafting of copolymer on sodium alginate. This behavior was affirmed from the broader peak at 17° – 37° in the XRD spectra of sodium alginate-g-poly(acrylic acid-co-acrylamide) hydrogel (**Figure 22**).

In another study, blending was used to develop sodium alginate-carboxymethyl cellulose gel beads (Ren et al., 2016). The synthesized gel bead was used to remove Pb(II) ion from aqueous solution. Adsorption percentage of more than 99 was reported for Pb(II) ion by using sodium alginate-carboxymethyl cellulose gel bead. The wrinkled and low porosity structure was exhibited by the pure sodium alginate gel bead (**Figure 23a**), whereas rough and highly porous structure was shown by sodium alginate-carboxymethyl cellulose gel bead (**Figure 23b**). High surface area and porosity was displayed by cross section of sodium alginate-carboxymethyl cellulose gel bead (**Figure 23c**). Internal network of sodium alginate-carboxymethyl cellulose gel bead developed through the condensation reaction among hydroxyls groups of carboxymethyl cellulose and carboxyl groups of sodium alginate. Sodium alginate-carboxymethyl cellulose gel bead was found to be more efficient than cation exchange resin and activated carbon for lead ions removal. The lead ion removal percentages were 99.6 %, 74.8 % and 66.4 % for sodium alginate-carboxymethyl cellulose gel bead, cation exchange resin and activated carbon respectively.

12. Conclusion

In this article, we have reviewed a versatile class of sodium alginate based hydrogels that are potentially useful for creating multitasking systems intended for achieving advanced adsorption properties. Hydrogels integrated with nano-particles, which not only increase the mechanical

characteristics of the hydrogels but also modulate its adsorption behavior, appear more efficiently. Hydrogel nano-composite materials manifest stimuli-responsive properties including photo thermal activity, catalysis, target drug delivery, anti-microbial property, drug degradation, removal of aquatic pollutants, bio-sensing and many more which makes it ideal for “smart” material. Our prime emphasis has been to bring potential design parameters useful for adsorption of pollutants. The systematic investigation on hydrogel composites for water purification application can persuade more research efforts to label the challenges and upgrade an area of interest for the general study of hydrogels. There is still a need for further investigations targeting on the intrinsic interactions of nano-particles with polymer matrix in order to alter their properties to explore more scientific research.

Acknowledgement

Dr Sourbh Thakur acknowledges financial support by Postdoctoral Fellowship project No 09.3.3-LMT-K-712-02-0180 and project 09.3.3-LMT-K-712 ‘Development of Scientific Competences of Scientists, other Researchers and Students through Practical Research Activities’ (Funding instrument – European Social Fund). Dr Sourbh Thakur is also thankful to Kaunas University of Technology.

References

- A Bhosale, M., M Bhanage, B., 2015. Silver nanoparticles: Synthesis, characterization and their application as a sustainable catalyst for organic transformations. *Current Organic Chemistry* 19, 708–727.
- Ahmed, E.M., 2015. Hydrogel: Preparation, characterization, and applications: A review. *Journal of advanced research* 6, 105–121.

- 1
2
3
4 Awual, M.R., Hasan, M.M., Ihara, T., Yaita, T., 2014. Mesoporous silica based novel conjugate
5
6 adsorbent for efficient selenium (IV) detection and removal from water. Microporous and
7
8 Mesoporous Materials 197, 331–338.
9
- 10
11 Awual, M.R., Hasan, M.M., Khaleque, M.A., 2015. Efficient selenium (IV) detection and
12
13 removal from water by tailor-made novel conjugate adsorbent. Sensors and Actuators B:
14
15 Chemical 209, 194–202.
16
17
- 18
19 Belhouchat, N., Zaghouane-Boudiaf, H., Viseras, C., 2017. Removal of anionic and cationic dyes
20
21 from aqueous solution with activated organo-bentonite/sodium alginate encapsulated
22
23 beads. Applied Clay Science 135, 9–15.
24
25
- 26
27 Bhattacharyya, R., Ray, S.K., 2015. Adsorption of industrial dyes by semi-IPN hydrogels of
28
29 acrylic copolymers and sodium alginate. Journal of Industrial and Engineering Chemistry
30
31 22, 92–102.
32
- 33
34 Bouhadir, K.H., Lee, K.Y., Alsberg, E., Damm, K.L., Anderson, K.W., Mooney, D.J., 2001.
35
36 Degradation of partially oxidized alginate and its potential application for tissue
37
38 engineering. Biotechnology progress 17, 945–950.
39
40
- 41
42 Buchholz, F.L., Graham, A.T., 1998. Modern superabsorbent polymer technology. John! Wiley
43
44 & Sons, Inc, 605 Third Ave, New York, NY 10016, USA, 1998. 279.
45
- 46
47 Burkert, S., Schmidt, T., Gohs, U., Dorschner, H., Arndt, K.-F., 2007. Cross-linking of poly (N-
48
49 vinyl pyrrolidone) films by electron beam irradiation. Radiation Physics and Chemistry
50
51 76, 1324–1328.
52
- 53
54 Caló, E., Khutoryanskiy, V.V., 2015. Biomedical applications of hydrogels: A review of patents
55
56 and commercial products. European Polymer Journal 65, 252–267.
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Can, V., Abdurrahmanoglu, S., Okay, O., 2007. Unusual swelling behavior of polymer–clay
5
6 nanocomposite hydrogels. *Polymer* 48, 5016–5023.
7
8
9 Chan, L.W., Lee, H.Y., Heng, P.W., 2006. Mechanisms of external and internal gelation and
10
11 their impact on the functions of alginate as a coat and delivery system. *Carbohydrate*
12
13 *Polymers* 63, 176–187.
14
15
16 Chiew, C.S.C., Yeoh, H.K., Pasbakhsh, P., Poh, P.E., Tey, B.T., Chan, E.S., 2016. Stability and
17
18 reusability of alginate-based adsorbents for repetitive lead (II) removal. *Polymer*
19
20 *Degradation and Stability* 123, 146–154.
21
22
23 de Vos, P., Faas, M.M., Strand, B., Calafiore, R., 2006. Alginate-based microcapsules for
24
25 immunoisolation of pancreatic islets. *Biomaterials* 27, 5603–5617.
26
27
28 Donati, I., Vetere, A., Gamini, A., Skjåk-Brek, G., Coslovi, A., Campa, C., Paoletti, S.,
29
30 2003. Galactose-substituted alginate: preliminary characterization and study of gelling
31
32 properties. *Biomacromolecules* 4, 624–631.
33
34
35 Du, X., Zhou, J., Shi, J., Xu, B., 2015. Supramolecular hydrogelators and hydrogels: from soft
36
37 matter to molecular biomaterials. *Chem. Rev* 115, 13165–13307.
38
39
40 Eghbalifam, N., Frounchi, M., Dadbin, S., 2015. Antibacterial silver nanoparticles in polyvinyl
41
42 alcohol/sodium alginate blend produced by gamma irradiation. *International Journal of*
43
44 *Biological Macromolecules* 80, 170–176.
45
46
47 El-Sherbiny, I.M., 2010. Enhanced pH-responsive carrier system based on alginate and
48
49 chemically modified carboxymethyl chitosan for oral delivery of protein drugs:
50
51 preparation and in-vitro assessment. *Carbohydrate Polymers* 80, 1125–1136.
52
53
54
55
56
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Fan, J., Shi, Z., Lian, M., Li, H., Yin, J., 2013. Mechanically strong graphene oxide/sodium
5
6 alginate/polyacrylamide nanocomposite hydrogel with improved dye adsorption capacity.
7
8 Journal of Materials Chemistry A 1, 7433–7443.
9
- 10
11 Fane, A.G., Wang, R., Hu, M.X., 2015. Synthetic membranes for water purification: status and
12
13 future. Angewandte Chemie International Edition 54, 3368–3386.
14
15
- 16 Fatin-Rouge, N., Dupont, A., Vidonne, A., Dejeu, J., Fievet, P., Foissy, A., 2006. Removal of
17
18 some divalent cations from water by membrane-filtration assisted with alginate. Water
19
20 Research 40, 1303–1309.
21
22
- 23 Franklin, M.J., Ohman, D.E., 2002. Mutant analysis and cellular localization of the AlgI, AlgJ,
24
25 and AlgF proteins required for O acetylation of alginate in *Pseudomonas aeruginosa*.
26
27 Journal of bacteriology 184, 3000–3007.
28
29
- 30 Galant, C., Kjøniksen, A.-L., Nguyen, G.T., Knudsen, K.D., Nyström, B., 2006. Altering
31
32 associations in aqueous solutions of a hydrophobically modified alginate in the presence
33
34 of β -cyclodextrin monomers. The Journal of Physical Chemistry B 110, 190–195.
35
36
- 37 Gao, T., Wang, W., Wang, A., 2011. A pH-sensitive composite hydrogel based on sodium
38
39 alginate and medical stone: synthesis, swelling, and heavy metal ions adsorption
40
41 properties. Macromolecular research 19, 739–748.
42
43
- 44 Goh, C.H., Heng, P.W.S., Chan, L.W., 2012. Alginates as a useful natural polymer for
45
46 microencapsulation and therapeutic applications. Carbohydrate Polymers 88, 1–12.
47
48
- 49 Guilherme, M.R., Reis, A.V., Takahashi, S.H., Rubira, A.F., Feitosa, J.P.A., Muniz, E.C., 2005.
50
51 Synthesis of a novel superabsorbent hydrogel by copolymerization of acrylamide and
52
53 cashew gum modified with glycidyl methacrylate. Carbohydrate Polymers 61, 464–471.
54
55
56
57 <https://doi.org/10.1016/j.carbpol.2005.06.017>
58
59
60
61
62
63
64
65

- 1
2
3
4 Han, L., Lu, X., Wang, M., Gan, D., Deng, W., Wang, K., Fang, L., Liu, K., Chan, C.W., Tang,
5
6 Y., 2017. A Mussel-Inspired Conductive, Self-Adhesive, and Self-Healable Tough
7
8 Hydrogel as Cell Stimulators and Implantable Bioelectronics. *Small* 13.
9
10
11 Heidarizad, M., Şengör, S.S., 2016. Synthesis of graphene oxide/magnesium oxide
12
13 nanocomposites with high-rate adsorption of methylene blue. *Journal of Molecular*
14
15 *Liquids* 224, 607–617.
16
17
18 Higuchi, A., Ling, Q.-D., Chang, Y., Hsu, S.-T., Umezawa, A., 2013. Physical cues of
19
20 biomaterials guide stem cell differentiation fate. *Chemical reviews* 113, 3297–3328.
21
22
23 Hosseinzadeh, H., Abdi, K., 2017. Efficient Removal of Methylene Blue Using a Hybrid
24
25 Organic–Inorganic Hydrogel Nanocomposite Adsorbent Based on Sodium Alginate–
26
27 Silicone Dioxide. *Journal of Inorganic and Organometallic Polymers and Materials* 27,
28
29 1595–1612.
30
31
32
33 Izawa, H., Kadokawa, J., 2010. Preparation and characterizations of functional ionic liquid-gel
34
35 and hydrogel materials of xanthan gum. *Journal of Materials Chemistry* 20, 5235–5241.
36
37
38 Jeon, O., Bouhadir, K.H., Mansour, J.M., Alsberg, E., 2009. Photocrosslinked alginate hydrogels
39
40 with tunable biodegradation rates and mechanical properties. *Biomaterials* 30, 2724–
41
42 2734.
43
44
45 Kaith, B.S., Jindal, R., Kumar, V., 2015. Biodegradation of Gum tragacanth acrylic acid based
46
47 hydrogel and its impact on soil fertility. *Polymer Degradation and Stability* 115, 24–31.
48
49
50 Kamata, H., Li, X., Chung, U., Sakai, T., 2015. Design of hydrogels for biomedical applications.
51
52 *Advanced healthcare materials* 4, 2360–2374.
53
54
55
56
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Karadağ, E., Saraydın, D., Güven, O., 2001. Radiation induced superabsorbent hydrogels.
5
6 Acrylamide/itaconic acid copolymers. *Macromolecular Materials and Engineering* 286,
7
8 34–42.
9
- 10
11 Karthiga Devi, G., Senthil Kumar, P., Sathish Kumar, K., 2016. Green synthesis of novel silver
12
13 nanocomposite hydrogel based on sodium alginate as an efficient biosorbent for the dye
14
15 wastewater treatment: prediction of isotherm and kinetic parameters. *Desalination and*
16
17 *Water Treatment* 57, 27686–27699.
18
19
- 20
21 Khan, M., Lo, I.M., 2016a. A holistic review of hydrogel applications in the adsorptive removal
22
23 of aqueous pollutants: Recent progress, challenges, and perspectives. *Water research* 106,
24
25 259–271.
26
27
- 28
29 Khan, M., Lo, I.M., 2016b. A holistic review of hydrogel applications in the adsorptive removal
30
31 of aqueous pollutants: recent progress, challenges, and perspectives. *Water research* 106,
32
33 259–271.
34
35
- 36
37 Khotimchenko, Y.S., Kovalev, V.V., Savchenko, O.V., Ziganshina, O.A., 2001. Physical–
38
39 chemical properties, physiological activity, and usage of alginates, the polysaccharides of
40
41 brown algae. *Russian Journal of Marine Biology* 27, S53–S64.
42
- 43
44 Kim, D.Y., Kwon, D.Y., Kwon, J.S., Kim, J.H., Min, B.H., Kim, M.S., 2015. Stimuli-responsive
45
46 injectable in situ-forming hydrogels for regenerative medicines. *Polymer Reviews* 55,
47
48 407–452.
49
- 50
51 Kim, J.-H., Randall Lee, T., 2006. Discrete thermally responsive hydrogel-coated gold
52
53 nanoparticles for use as drug-delivery vehicles. *Drug development research* 67, 61–69.
54
55
56
57
58
59
60
61
62
63
64
65

- Kim, Y.-J., Yoon, K.-J., Ko, S.-W., 2000. Preparation and properties of alginate superabsorbent filament fibers crosslinked with glutaraldehyde. *Journal of Applied Polymer Science* 78, 1797–1804.
- Knipe, J.M., Chen, F., Peppas, N.A., 2015. Enzymatic biodegradation of hydrogels for protein delivery targeted to the small intestine. *Biomacromolecules* 16, 962–972.
- Lakouraj, M.M., Mojerlou, F., Zare, E.N., 2014. Nanogel and superparamagnetic nanocomposite based on sodium alginate for sorption of heavy metal ions. *Carbohydrate polymers* 106, 34–41.
- Lam, W.-H., Chong, M.N., Horri, B.A., Tey, B.-T., Chan, E.-S., 2017. Physicochemical stability of calcium alginate beads immobilizing TiO₂ nanoparticles for removal of cationic dye under UV irradiation. *Journal of Applied Polymer Science* 134.
- Lee, K.Y., Mooney, D.J., 2012. Alginate: properties and biomedical applications. *Progress in polymer science* 37, 106–126.
- Lee, K.Y., Mooney, D.J., 2001. Hydrogels for tissue engineering. *Chemical reviews* 101, 1869–1880.
- Li, Y., Huang, G., Zhang, X., Li, B., Chen, Y., Lu, T., Lu, T.J., Xu, F., 2013. Magnetic hydrogels and their potential biomedical applications. *Advanced Functional Materials* 23, 660–672.
- Li, Y., Rodrigues, J., Tomas, H., 2012. Injectable and biodegradable hydrogels: gelation, biodegradation and biomedical applications. *Chemical Society Reviews* 41, 2193–2221.
- Liu, J., Su, D., Yao, J., Huang, Y., Shao, Z., Chen, X., 2017. Soy protein-based polyethylenimine hydrogel and its high selectivity for copper ion removal in wastewater treatment. *Journal of Materials Chemistry A* 5, 4163–4171.

- Lu, T., Xiang, T., Huang, X.-L., Li, C., Zhao, W.-F., Zhang, Q., Zhao, C.-S., 2015. Post-crosslinking towards stimuli-responsive sodium alginate beads for the removal of dye and heavy metals. *Carbohydrate polymers* 133, 587–595.
- Ma, M., Kuang, Y., Gao, Y., Zhang, Y., Gao, P., Xu, B., 2010. Aromatic- aromatic interactions induce the self-assembly of pentapeptidic derivatives in water to form nanofibers and supramolecular hydrogels. *Journal of the American Chemical Society* 132, 2719–2728.
- Mahdavinia, G.R., Aghaie, H., Sheykhloie, H., Vardini, M.T., Etemadi, H., 2013. Synthesis of CarAlg/MMt nanocomposite hydrogels and adsorption of cationic crystal violet. *Carbohydrate polymers* 98, 358–365.
- Mahdavinia, G.R., Mousanezhad, S., Hosseinzadeh, H., Darvishi, F., Sabzi, M., 2016. Magnetic hydrogel beads based on PVA/sodium alginate/laponite RD and studying their BSA adsorption. *Carbohydrate polymers* 147, 379–391.
- Mehrali, M., Thakur, A., Pennisi, C.P., Talebian, S., Arpanaei, A., Nikkhah, M., Dolatshahi-Pirouz, A., 2017. Nanoreinforced Hydrogels for Tissue Engineering: Biomaterials that are Compatible with Load-Bearing and Electroactive Tissues. *Advanced Materials* 29.
- Merino, S., Martín, C., Kostarelos, K., Prato, M., Vázquez, E., 2015. Nanocomposite hydrogels: 3D polymer–nanoparticle synergies for on-demand drug delivery. *ACS nano* 9, 4686–4697.
- Nayak, A.K., Malakar, J., Sen, K.K., 2010. Gastroretentive drug delivery technologies: Current approaches and future potential. *Journal of Pharmaceutical Education and Research* 1, 1.
- Ngah, W.W., Fatinathan, S., 2008. Adsorption of Cu (II) ions in aqueous solution using chitosan beads, chitosan–GLA beads and chitosan–alginate beads. *Chemical Engineering Journal* 143, 62–72.

- Oh, J.Y., Rondeau-Gagné, S., Chiu, Y.-C., Chortos, A., Lissel, F., Wang, G.-J.N., Schroeder, B.C., Kurosawa, T., Lopez, J., Katsumata, T., 2016. Intrinsically stretchable and healable semiconducting polymer for organic transistors. *Nature* 539, 411.
- Omidian, H., Rocca, J.G., Park, K., 2006. Elastic, superporous hydrogel hybrids of polyacrylamide and sodium alginate. *Macromolecular bioscience* 6, 703–710.
- Paddon, C.J., Westfall, P.J., Pitera, D.J., Benjamin, K., Fisher, K., McPhee, D., Leavell, M.D., Tai, A., Main, A., Eng, D., 2013. High-level semi-synthetic production of the potent antimalarial artemisinin. *Nature* 496, 528–532.
- Pakdel, P.M., Peighambaroust, S.J., 2018. A review on acrylic based hydrogels and their applications in wastewater treatment. *Journal of environmental management* 217, 123–143.
- Paques, J.P., van der Linden, E., van Rijn, C.J., Sagis, L.M., 2014. Preparation methods of alginate nanoparticles. *Advances in colloid and interface science* 209, 163–171.
- Pardo-Yissar, V., Gabai, R., Shipway, A.N., Bourenko, T., Willner, I., 2001. Gold Nanoparticle/Hydrogel Composites with Solvent-Switchable Electronic Properties. *Advanced Materials* 13, 1320–1323.
- Park, J.H., Kim, D., 2001. Study on foaming water-swelling EPDM rubber. *J Appl Polym Sci* 80, 115–21.
- Pawar, S.N., Edgar, K.J., 2012a. Alginate derivatization: a review of chemistry, properties and applications. *Biomaterials* 33, 3279–3305.
- Pawar, S.N., Edgar, K.J., 2012b. Alginate derivatization: A review of chemistry, properties and applications. *Biomaterials* 33, 3279–3305.
<https://doi.org/10.1016/j.biomaterials.2012.01.007>

- Pereira, R., Carvalho, A., Vaz, D.C., Gil, M.H., Mendes, A., Bártolo, P., 2013. Development of novel alginate based hydrogel films for wound healing applications. *International journal of biological macromolecules* 52, 221–230.
- Pourjavadi, A., Doulabi, M., Doroudian, M., 2014. Adsorption characteristics of malachite green dye onto novel kappa-carrageenan-g-polyacrylic acid/TiO₂-NH₂ hydrogel nanocomposite. *Journal of the Iranian Chemical Society* 11, 1057–1065.
- Pourjavadi, A., Farhadpour, B., Seidi, F., 2008. Synthesis and investigation of swelling behavior of grafted alginate/alumina superabsorbent composite. *Starch-Stärke* 60, 457–466.
- Qiu, Y., Park, K., 2001. Environment-sensitive hydrogels for drug delivery. *Advanced drug delivery reviews* 53, 321–339.
- Rashidzadeh, A., Olad, A., Salari, D., 2015. The effective removal of methylene blue dye from aqueous solutions by NaAlg-g-poly (acrylic acid-co-acryl amide)/clinoptilolite hydrogel nanocomposite. *Fibers and Polymers* 16, 354–362.
- Reis, A.V., Fajardo, A.R., Schuquel, I.T., Guilherme, M.R., Vidotti, G.J., Rubira, A.F., Muniz, E.C., 2009. Reaction of glycidyl methacrylate at the hydroxyl and carboxylic groups of poly (vinyl alcohol) and poly (acrylic acid): is this reaction mechanism still unclear? *The Journal of organic chemistry* 74, 3750–3757.
- Ren, H., Gao, Z., Wu, D., Jiang, J., Sun, Y., Luo, C., 2016. Efficient Pb (II) removal using sodium alginate–carboxymethyl cellulose gel beads: preparation, characterization, and adsorption mechanism. *Carbohydrate polymers* 137, 402–409.
- rights are reserved by Shivani, A., Shetye, P., n.d. *Hydrogels: Introduction, Preparation, Characterization and Applications*.

- 1
2
3
4 Rosales, A.M., Anseth, K.S., 2016. The design of reversible hydrogels to capture extracellular
5
6 matrix dynamics. *Nature Reviews Materials* 1, 15012.
7
8
9 Roy, D., Cambre, J.N., Sumerlin, B.S., 2010. Future perspectives and recent advances in stimuli-
10
11 responsive materials. *Progress in Polymer Science* 35, 278–301.
12
13
14 Sahiner, N., 2013. Soft and flexible hydrogel templates of different sizes and various
15
16 functionalities for metal nanoparticle preparation and their use in catalysis. *Progress in*
17
18 *Polymer Science* 38, 1329–1356.
19
20
21 Sahiner, N., Seven, F., 2014. The use of superporous p (AAc (acrylic acid)) cryogels as support
22
23 for Co and Ni nanoparticle preparation and as reactor in H₂ production from sodium
24
25 borohydride hydrolysis. *Energy* 71, 170–179.
26
27
28 Saravanan, P., Raju, M.P., Alam, S., 2007. A study on synthesis and properties of Ag
29
30 nanoparticles immobilized polyacrylamide hydrogel composites. *Materials chemistry and*
31
32 *physics* 103, 278–282.
33
34
35
36 Seliktar, D., 2012. Designing cell-compatible hydrogels for biomedical applications. *Science*
37
38 336, 1124–1128.
39
40
41 Sershen, S.R., Westcott, S.L., Halas, N.J., West, J.L., 2002. Independent optically addressable
42
43 nanoparticle-polymer optomechanical composites. *Applied Physics Letters* 80, 4609–
44
45 4611.
46
47
48 Shetye, S.P., Godbole, A., Bhilegaokar, S., Gajare, P., 2015. Hydrogels: Introduction,
49
50 Preparation, Characterization and Applications. *Hum. J* 1, 47–71.
51
52
53 Shi, J., Gao, Y., Yang, Z., Xu, B., 2011. Exceptionally small supramolecular hydrogelators based
54
55 on aromatic–aromatic interactions. *Beilstein journal of organic chemistry* 7, 167.
56
57
58
59
60
61
62
63
64
65

- Shin, S.R., Bae, H., Cha, J.M., Mun, J.Y., Chen, Y.-C., Tekin, H., Shin, H., Farshchi, S., Dokmeci, M.R., Tang, S., 2011. Carbon nanotube reinforced hybrid microgels as scaffold materials for cell encapsulation. *ACS nano* 6, 362–372.
- Talaat, H.A., Sorour, M.H., Aboulmour, A.G., Shaalan, H.F., Ahmed, E.M., Awad, A.M., Ahmed, M.A., 2008. Development of a multi-component fertilizing hydrogel with relevant techno-economic indicators. *Am-Euras J Agric Environ Sci* 3, 764–70.
- Tally, M., Atassi, Y., 2016. Synthesis and characterization of pH-sensitive superabsorbent hydrogels based on sodium alginate-g-poly (acrylic acid-co-acrylamide) obtained via an anionic surfactant micelle templating under microwave irradiation. *Polymer Bulletin* 73, 3183–3208.
- Thakur, M.K., Thakur, V.K., Gupta, R.K., Pappu, A., 2015. Synthesis and applications of biodegradable soy based graft copolymers: a review. *ACS Sustainable Chemistry & Engineering* 4, 1–17.
- Thakur, S., 2016. Sodium alginate, xanthan gum biopolymer composites: synthesis, characterisation and application in organic dye removal from water (PhD Thesis). University of Johannesburg.
- Thakur, S., Arotiba, O., 2017. Synthesis, characterization and adsorption studies of an acrylic acid-grafted sodium alginate-based TiO₂ hydrogel nanocomposite. *Adsorption Science & Technology* 0263617417700636.
- Thakur, S., Arotiba, O.A., n.d. Synthesis, swelling and adsorption studies of a pH-responsive sodium alginate–poly (acrylic acid) superabsorbent hydrogel. *Polymer Bulletin* 1–20.
- Thakur, S., Arotiba, O.A., n.d. Synthesis, swelling and adsorption studies of a pH-responsive sodium alginate–poly (acrylic acid) superabsorbent hydrogel. *Polymer Bulletin* 1–20.

- 1
2
3
4 Thakur, S., Govender, P.P., Mamo, M.A., Tamulevicius, S., Mishra, Y.K., Thakur, V.K., 2017a.
5
6 Progress in lignin hydrogels and nanocomposites for water purification: Future
7
8 perspectives. *Vacuum* 146, 342–355.
9
10
11 Thakur, S., Govender, P.P., Mamo, M.A., Tamulevicius, S., Thakur, V.K., 2017b. Recent
12
13 progress in gelatin hydrogel nanocomposites for water purification and beyond. *Vacuum*
14
15 146, 396–408.
16
17
18 Thakur, S., Pandey, S., Arotiba, O.A., 2016. Development of a sodium alginate-based
19
20 organic/inorganic superabsorbent composite hydrogel for adsorption of methylene blue.
21
22 *Carbohydrate polymers* 153, 34–46.
23
24
25 Thoniyot, P., Tan, M.J., Karim, A.A., Young, D.J., Loh, X.J., 2015a. Nanoparticle–hydrogel
26
27 composites: Concept, design, and applications of these promising, multi-functional
28
29 materials. *Advanced Science* 2.
30
31
32 Thoniyot, P., Tan, M.J., Karim, A.A., Young, D.J., Loh, X.J., 2015b. Nanoparticle–hydrogel
33
34 composites: Concept, design, and applications of these promising, multi-functional
35
36 materials. *Advanced Science* 2.
37
38
39 Uto, K., Tsui, J.H., DeForest, C.A., Kim, D.-H., 2017. Dynamically tunable cell culture
40
41 platforms for tissue engineering and mechanobiology. *Progress in polymer science* 65,
42
43 53–82.
44
45
46 Vermonden, T., Censi, R., Hennink, W.E., 2012a. Hydrogels for protein delivery. *Chemical*
47
48 *Reviews* 112, 2853–2888.
49
50
51 Vermonden, T., Censi, R., Hennink, W.E., 2012b. Hydrogels for protein delivery. *Chemical*
52
53 *Reviews* 112, 2853–2888.
54
55
56
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Vivek, B., Prasad, E., 2015. Reusable self-healing hydrogels realized via in situ polymerization.
5
6 The Journal of Physical Chemistry B 119, 4881–4887.
7
8
9 Wang, C., Flynn, N.T., Langer, R., 2004. Controlled structure and properties of
10
11 thermoresponsive nanoparticle–hydrogel composites. Advanced Materials 16, 1074–
12
13 1079.
14
15
16 Wang, C., Wu, H., Chen, Z., McDowell, M.T., Cui, Y., Bao, Z., 2013. Self-healing chemistry
17
18 enables the stable operation of silicon microparticle anodes for high-energy lithium-ion
19
20 batteries. Nature chemistry 5, 1042–1048.
21
22
23 Wang, L., Zhang, J., Wang, A., 2008. Removal of methylene blue from aqueous solution using
24
25 chitosan-g-poly (acrylic acid)/montmorillonite superadsorbent nanocomposite. Colloids
26
27 and Surfaces A: Physicochemical and Engineering Aspects 322, 47–53.
28
29
30 Wang, W., Kang, Y., Wang, A., 2013a. One-step fabrication in aqueous solution of a granular
31
32 alginate-based hydrogel for fast and efficient removal of heavy metal ions. Journal of
33
34 Polymer Research 20, 101.
35
36
37 Wang, W., Zhang, Y., Liu, W., 2017. Bioinspired fabrication of high strength hydrogels from
38
39 non-covalent interactions. Progress in Polymer Science 71, 1–25.
40
41
42 Wang, W., Zong, L., Wang, A., 2013b. A nanoporous hydrogel based on vinyl-functionalized
43
44 alginate for efficient absorption and removal of Pb ²⁺ ions. International journal of
45
46 biological macromolecules 62, 225–231.
47
48
49
50 Wu, H., Yu, G., Pan, L., Liu, N., McDowell, M.T., Bao, Z., Cui, Y., 2013. Stable Li-ion battery
51
52 anodes by in-situ polymerization of conducting hydrogel to conformally coat silicon
53
54 nanoparticles. Nature communications 4, 1943.
55
56
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Wu, Y., Qi, H., Shi, C., Ma, R., Liu, S., Huang, Z., 2017. Preparation and adsorption behaviors
5
6 of sodium alginate-based adsorbent-immobilized β -cyclodextrin and graphene oxide.
7
8 RSC Advances 7, 31549–31557.
9
- 10
11 Yang, J.-A., Yeom, J., Hwang, B.W., Hoffman, A.S., Hahn, S.K., 2014. In situ-forming
12
13 injectable hydrogels for regenerative medicine. Progress in Polymer Science 39, 1973–
14
15 1986.
16
17
- 18
19 Yang, J.-S., Xie, Y.-J., He, W., 2011. Research progress on chemical modification of alginate: A
20
21 review. Carbohydrate polymers 84, 33–39.
22
- 23
24 Yi, X., Sun, F., Han, Z., Han, F., He, J., Ou, M., Gu, J., Xu, X., 2018. Graphene oxide
25
26 encapsulated polyvinyl alcohol/sodium alginate hydrogel microspheres for Cu (II) and U
27
28 (VI) removal. Ecotoxicology and environmental safety 158, 309–318.
29
- 30
31 You, J.-O., Park, S.-B., Park, H.-Y., Haam, S., Chung, C.-H., Kim, W.-S., 2001. Preparation of
32
33 regular sized Ca-alginate microspheres using membrane emulsification method. Journal
34
35 of microencapsulation 18, 521–532.
36
37
- 38
39 Zhang, D., Yang, J., Bao, S., Wu, Q., Wang, Q., 2013. Semiconductor nanoparticle-based
40
41 hydrogels prepared via self-initiated polymerization under sunlight, even visible light.
42
43 Scientific Reports 3, 1399.
44
- 45
46 Zhao, F., Yao, D., Guo, R., Deng, L., Dong, A., Zhang, J., 2015. Composites of polymer
47
48 hydrogels and nanoparticulate systems for biomedical and pharmaceutical applications.
49
50 Nanomaterials 5, 2054–2130.
51
- 52
53 Zhao, L.Z., Zhou, C.H., Wang, J., Tong, D.S., Yu, W.H., Wang, H., 2015. Recent advances in
54
55 clay mineral-containing nanocomposite hydrogels. Soft Matter 11, 9229–9246.
56
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Zhao, W., Jin, X., Cong, Y., Liu, Y., Fu, J., 2013. Degradable natural polymer hydrogels for
5
6 articular cartilage tissue engineering. *Journal of Chemical Technology and Biotechnology*
7
8 88, 327–339.
9
- 10
11 Zhuang, Y., Yu, F., Chen, H., Zheng, J., Ma, J., Chen, J., 2016. Alginate/graphene double-
12
13 network nanocomposite hydrogel beads with low-swelling, enhanced mechanical
14
15 properties, and enhanced adsorption capacity. *Journal of Materials Chemistry A* 4,
16
17 10885–10892.
18
19
- 20
21 Zimmermann, U., Klöck, G., Federlin, K., Hannig, K., Kowalski, M., Bretzel, R.G., Horcher, A.,
22
23 Entenmann, H., Sieber, U., Zekorn, T., 1992. Production of mitogen-contamination free
24
25 alginates with variable ratios of mannuronic acid to guluronic acid by free flow
26
27 electrophoresis. *Electrophoresis* 13, 269–274.
28
29
- 30
31 Zuo, Y., Liu, X., Wei, D., Sun, J., Xiao, W., Zhao, H., Guo, L., Wei, Q., Fan, H., Zhang, X.,
32
33 2015. Photo-cross-linkable methacrylated gelatin and hydroxyapatite hybrid hydrogel for
34
35 modularly engineering biomimetic osteon. *ACS applied materials & interfaces* 7, 10386–
36
37 10394.
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

Figure 1. Various applied applications of alginate based hydrogels

Figure 2. Schematic diagram of hydrogel preparation.

Figure 3. Different modes of degradation of hydrogel.

1. Need to have multiple alginate samples in M/G ratios.
2. Use of advanced analytical techniques.

Characterization

Solubility

1. May dissolve in aqueous, organic or mixed (org-aq.) media.
2. Depends upon choice of solvents.

Reactivity

1. Can be modified at C-2 & C-3 or one COOH positions.
2. Controlled by selective modification Of M and G residues.

Figure 4. Parameters governing alginate derivatization. Adopted from (Pawar and Edgar, 2012).

Figure 5. FTIR spectrum (a) sodium alginate-g-poly(acrylic acid-co-acrylamide)/clinoptilolite, (b) sodium alginate-g-poly(acrylic acid-co-acrylamide) and (c) methylene blue adsorbed sodium alginate-g-poly(acrylic acid-co-acrylamide)/clinoptilolite, (d) SEM morphology of sodium alginate-g-poly(acrylic acid-co-acrylamide)/clinoptilolite (Rashidzadeh et al., 2015). Reprinted with permission from (Rashidzadeh et al., 2015). Copyright 2015 Springer.

Figure 6. Images of sodium alginate-g-poly(acrylic acid-co-acryl amide) hydrogel and sodium alginate-g-poly(acrylic acid-co-acryl amide)/clinoptilolite hydrogel nano-composite samples before (a, b) adsorption of methylene blue dye and after (c, d) adsorption of methylene blue dye solution (Rashidzadeh et al., 2015). Reprinted with permission from (Rashidzadeh et al., 2015). Copyright 2015 Springer.

Figure 7. (a) Atomic force microscopy image of graphene oxide, (b) image of sodium alginate/ β -cyclodextrin/graphene oxide hydrogel nano-composite and methylene blue loaded sodium alginate/ β -cyclodextrin/graphene oxide hydrogel nano-composite, (c-e) SEM images of sodium alginate/ β -cyclodextrin/graphene oxide hydrogel nano-composite and (f) TEM image of graphene oxide (Wu et al., 2017). Reproduced from (Wu et al., 2017). Published by Royal Society of Chemistry.

Figure 8. Proposed mechanism for methylene blue adsorption onto sodium alginate/β-cyclodextrin/graphene oxide hydrogel nano-composite (Wu et al., 2017). Reproduced from (Wu et al., 2017). Published by Royal Society of Chemistry.

Figure 9. Possible mechanism for interaction of cationic methylene blue (MB) dye with titania incorporated sodium alginate cross-linked acrylic acid hydrogel nano-composite (Alg-cl-poly(AA)-TiO₂) (Thakur et al., 2016). Reprinted with permission from (Thakur et al., 2016). Copyright 2016 Elsevier.

Figure 10. (a-c) Photographs of pure polyacrylamide hydrogel under compression, (d-f) photographs of graphene oxide/sodium alginate/polyacrylamide hydrogel nano-composite under compression, (g) general representation for graphene oxide/sodium alginate/polyacrylamide ternary hydrogel nano-composite (Fan et al., 2013). Reprinted with permission from (Fan et al., 2013). Copyright 2013 Royal Society of Chemistry.

Figure 11. (a) SEM images of (a) pure polyacrylamide hydrogel, (b, c) sodium alginate/polyacrylamide hydrogel, (d-f) graphene oxide/sodium alginate/polyacrylamide ternary hydrogel nano-composite (Fan et al., 2013). Reprinted with permission from (Fan et al., 2013). Copyright 2013 Royal Society of Chemistry.

Figure 12. Different dye solutions before and after the adsorption by graphene oxide/sodium alginate/polyacrylamide ternary hydrogel nano-composite. brilliant green (BG), methylene blue (MB), malachite green (MG), rhodamine 6G (R6G), methyl orange (MO), bordeaux red (BR), calcein (CA) and rose bengal sodium salt (RB) (Fan et al., 2013).Reprinted with permission from (Fan et al., 2013). Copyright 2013 Royal Society of Chemistry.

Figure 13. Potential mechanism for the formation of nano-porous vinyl-functionalized sodium alginate-co-methyl acrylic acid-co-itaic acid hydrogel (Wang et al., 2013b). Reprinted with permission from (Wang et al., 2013b). Copyright 2013 Elsevier.

Figure 14. (a) ^1H NMR spectra of glycidyl methacrylate, sodium alginate and vinyl-functionalized sodium alginate, (b) ^{13}C NMR spectra of glycidyl methacrylate, sodium alginate and vinyl-functionalized sodium alginate (Wang et al., 2013b). Reprinted with permission from (Wang et al., 2013b). Copyright 2013 Elsevier.

Figure 15. FESEM images of (a) non porous vinyl-functionalized sodium alginate-co-methyl acrylic acid-co-italic acid hydrogel, (b-d) nano-porous vinyl-functionalized sodium alginate-co-methyl acrylic acid-co-italic acid hydrogel at different magnification (Wang et al., 2013b). Reprinted with permission from (Wang et al., 2013b). Copyright 2013 Elsevier.

Figure 16. Proposed scheme for the synthesis of sodium alginate-g-polyacrylic acid/polyvinylpyrrolidone/gelatin granular hydrogel (Wang et al., 2013a). Reprinted with permission from (Wang et al., 2013a). Copyright 2013 Springer.

Figure 17. Digital images of (a) sodium alginate-g-polyacrylic acid hydrogel, (b) sodium alginate-g-polyacrylic acid/polyvinylpyrrolidone/gelatin granular hydrogel, (c) sodium alginate-g-polyacrylic acid/polyvinylpyrrolidone/gelatin granular hydrogel in dry state. SEM images of (d) sodium alginate-g-polyacrylic acid hydrogel, (e) sodium alginate-g-polyacrylic acid/polyvinylpyrrolidone/gelatin granular hydrogel (Wang et al., 2013a). Reprinted with permission from (Wang et al., 2013a). Copyright 2013 Springer.

Figure 18. FESEM images of (a) sodium alginate-g-sodium acrylate hydrogel, (b) medical stone (c) sodium alginate-g-sodium acrylate/medical stone hydrogel composite with 0.93 g medical stone, (d) sodium alginate-g-sodium acrylate/medical stone hydrogel composite with 3.57 g medical stone (Gao et al., 2011). Reprinted with permission from (Gao et al., 2011). Copyright 2011 Springer.

Figure 19. Formation of (a) reduced graphene (RGO) hydrogel, (b) beads of alginate hydrogel, (c) hydrogel bead of graphene/alginate composite (Zhuang et al., 2016). Reproduced from (Zhuang et al., 2016). Published by Royal Society of Chemistry.

Figure 20. SEM micrograph of (a) graphene/alginate single network and (b) graphene/alginate double network, elemental mapping of (c) graphene/alginate single network, (d) graphene/alginate double network, with insets of mapping of oxygen element (Zhuang et al., 2016). Reproduced from (Zhuang et al., 2016). Published by Royal Society of Chemistry.

Figure 21. Schematic presentation for the synthesis of sodium alginate-g-poly(acrylic acid-co-acrylamide)hydrogel (Tally and Atassi, 2016). Reprinted with permission from (Tally and Atassi, 2016). Copyright 2016 Springer.

Figure 22. XRD spectra of (a) sodium alginate, (b) poly(acrylic acid-co-acrylamide), (c) sodium alginate-g-poly(acrylic acid-co-acrylamide) hydrogel(Tally and Atassi, 2016). Reprinted with permission from (Tally and Atassi, 2016). Copyright 2016 Springer.

Figure 23. SEM images of (a) pure sodium alginate gel bead, (b) sodium alginate-carboxymethyl cellulose gel bead, (c) cross section of sodium alginate-carboxymethyl cellulose gel bead (Ren et al., 2016). Reprinted with permission from (Ren et al., 2016). Copyright 2016 Elsevier.

Table 1. Sodium alginate based hydrogels for removal of organic pollutants.

Sr. No.	Hydrogel Composites	Organic Pollutants	References
1.	Sodium alginate–poly(acrylic acid) superabsorbent hydrogel	Victoria blue R and Rhodamine 6G	(Thakur and Arotiba, n.d.)
2.	Sodium alginate and silicone dioxide based organic/inorganic nano-composite hydrogel	Methylene blue	(Hosseinzadeh and Abdi, 2017)
3.	Sodium alginate based titanium dioxide hydrogel beads	Cationic dyes	(Lam et al., 2017)
4.	Sodium alginate based β -cyclodextrin/graphene oxide nano-composite hydrogel	Methylene blue	(Wu et al., 2017)
5.	Sodium alginate based TiO ₂ nano-composite hydrogel	Methyl violet	(Thakur and Arotiba, 2017)
6.	Sodium alginate/ polyacrylic acid/ TiO ₂ nano-composite hydrogel	Methylene blue	(Thakur et al., 2016)
7.	Sodium alginate based silver nano-composite hydrogel	Methylene blue	(Karthiga Devi et al., 2016)
8.	Sodium alginate-g-poly (acrylic acid-co-acryl amide)/clinoptilolite nano-composite hydrogel	Methylene blue	(Rashidzadeh et al., 2015)
9.	Sodium alginate based kappa-carrageenan/sodium montmorillonite nano-composite hydrogel	Crystal violet	(Mahdavinia et al., 2013)
10.	Sodium alginate based graphene oxide/polyacrylamide nano-composite hydrogel	Cationic and anionic dyes	(Fan et al., 2013)
11.	Sodium alginate based semi-IPN/ acrylic copolymer nano-composite hydrogel	Methyl violet	(Bhattacharyya and Ray, 2015)
12.	Sodium alginate based organo-bentonite nano-composite hydrogel	Methylene blue and Methyl orange	(Belhouchat et al., 2017)

Table 2. Sodium alginate based hydrogels for removal of inorganic pollutants.

Sr. No.	Hydrogel Composites	Inorganic Pollutant	References
1.	Sodium alginate based carboxymethyl cellulose hydrogel beads	Pb(II)	(Ren et al., 2016)
2.	Sodium alginate-g-poly (acrylic acid-co-acrylamide) nano-composite hydrogel	Pb(II), Cd(II), Ni(II) and Cu(II)	(Tally and Atassi, 2016)
3.	Alginate/reduced graphene double-network hydrogel beads and Alginate/reduced graphene single-network hydrogel beads	Cu(II) and $\text{Cr}_2\text{O}_7^{2-}$	(Zhuang et al., 2016)
4.	Vinyl-functionalized sodium alginate-co-methyl acrylic acid-co-italic acid nano-composite hydrogel	Pb(II)	(Wang et al., 2013b)
5.	Sodium alginate based granular nano-composite hydrogel	Ni(II), Cu(II), Zn(II) and Cd(II)	(Wang et al., 2013a)
6.	Sodium alginate-g-poly (sodium acrylate)/medical stone nano-composite hydrogel	Ni(II), Cu(II), Zn(II) and Cd(II)	(Gao et al., 2011)
7.	Tetra sodium thiacalix [4] arenetetrasulfonate-sorption-sodium alginate nano-composite hydrogel	Ni(II), Cu(II), Pb(II), Cd(II), Co(II) and Cr(III)	(Lakouraj et al., 2014)
8.	Sodium alginate hydrogel beads by post cross-linking	Ag(I), Cu(II) and Fe(III)	(Lu et al., 2015)
9.	Sodium alginate based membrane - filtration	Ca(II) and Mg(II)	(Fatin-Rouge et al., 2006)
10.	Chitosan-alginate hydrogel beads and chitosan-glycolic acid hydrogel beads	Cu(II)	(Nghah and Fatinathan, 2008)

2018-06-27

Recent progress in sodium alginate based sustainable hydrogels for environmental applications

Thakur, Sourbh

Elsevier

Thakur S, Sharma B, Verma A, et al., (2018) Recent progress in sodium alginate based sustainable hydrogels for environmental applications. *Journal of Cleaner Production*, Volume 198, October 2018, pp. 143-159

<https://doi.org/10.1016/j.jclepro.2018.06.259>

Downloaded from Cranfield Library Services E-Repository