

High dielectric tunability, electrostriction strain and electrocaloric strength at a tricritical point of tetragonal, rhombohedral and pseudocubic phases

Biaolin Peng^{1,2,3}, Qi Zhang^{4,5}, Xing Li³, Tiejun Sun³, Shanming Ke¹, Mao Ye^{1,2}, Yu Wang³, Wei Lu³, Hanben Niu², Xierong Zeng^{1*}, Huiqing Fan^{5*}, Haitao Huang^{3*}

¹Shenzhen Key Laboratory of Special Functional Materials, College of Materials Science and Engineering, Shenzhen University, Shenzhen 518060, PR China

²Key Laboratory of Optoelectronic Devices and Systems of Ministry of Education and Guangdong Province, College of Optoelectronic Engineering, Shenzhen University, Shenzhen, 518060, China

³Department of Applied Physics, The Hong Kong Polytechnic University, Kowloon, Hong Kong SAR

⁴Department of Manufacturing and Materials, Cranfield University, Cranfield, Bedfordshire, MK43 0AL, United Kingdom

⁵State Key Laboratory of Advanced Technology for Materials Synthesis and Processing, Wuhan University of Technology, Wuhan 430070, Hubei, PR China

⁶State Key Laboratory of Solidification Processing School of Materials Science and Engineering Northwestern Polytechnical University, Xi'an 710072, China

Abstract

A relaxor ferroelectric $\text{Pb}(\text{Ni}_{1/3}\text{Nb}_{2/3})_{0.5}\text{Zr}_{0.15}\text{Ti}_{0.35}\text{O}_3$ (PNNZT) ceramic was reported, designed upon an idea that the composition is selected to near a tricritical point of tetragonal, rhombohedral and pseudocubic phases. High dielectric tunability of 67%,

* Author to whom correspondence should be addressed. Electronic mail: zengxier@szu.edu.cn, hqfan3@163.com, & haitao.huang@polyu.edu.hk

simultaneously with high electrostriction strain of 0.319% and high electrocaloric strength ($\Delta T/\Delta E$) of 32.5 mK cm/kV are achieved, which make it a promising multifunctional material for applications in dielectric tunable, precisely controlled and electric refrigeration devices. This is endowed by the low energy barrier among the transitions of phases and strong relaxor ferroelectric activities around the tricritical point. This work provides a guide for the design of multifunctional ferroelectric materials and can promote the development of other multifunctional ferroic materials.

Keywords: Dielectric tenability; Electrostriction; Electrocaloric; Relaxor; Morphotropic phase boundary

1. Introduction

Recently, there has been an increasing interest on relaxor ferroelectric materials that possess high performance in dielectric tunability, electrostriction strain, electrocaloric effect, etc., due to the potential applications in tunable devices, electromechanical actuators, solid state cooling systems, etc[1-7]. Usually, for dielectric tunable devices, the applications demand materials owning not only high dielectric tunability but also high figure-of-merit (*FOM*) [8]. For electromechanical actuators, a large electrostriction strain with a high electrostriction coefficient is required[4]. For solid state cooling systems, a large electrocaloric effect with a high electrocaloric strength is also required[9].

To accomplish these requirements, most research efforts have been made. For example, to improve the *FOM* of titanium-containing perovskite dielectric tunable ferroelectric materials such as (Ba,Sr)TiO₃ (Pb,Sr)TiO₃, etc. [10, 11], due to the oxidation state of titanium being easily reduced from Ti⁴⁺ to Ti³⁺, strategies with doping various oxides (MgO, etc.) and ions (Mn²⁺ etc.) were often adopted[12]. To obtain high linear electrostrictive strain with large electrostrictive coefficient, a formula scheme “coexistence of a normal ferroelectric and a relaxor ferroelectric” was proposed, and a large electrostrictive strain (0.1%) with an electrostrictive coefficient Q of 0.02 m⁴/C² was observed in the (Sr,Bi,Na)TiO₃ solid solution[4]. Furthermore, a large electrocaloric effect with large electrocaloric strength was expected to be realized near the ferroelectric Curie temperature, such as a large ΔT of 12 K with an electrocaloric strength of 24 mK cm/kV was observed in the

antiferroelectric $\text{PbZr}_{0.95}\text{Ti}_{0.05}\text{O}_3$ thin film near the antiferroelectric to paraelectric phase transition temperature[5], and also a ΔT of 12.6 K with an electrocaloric strength of 6 mK cm/kV in the relaxor ferroelectric polymer P(VDF-TrFE) [7]. However, so far, to our knowledge, the above mentioned performances were rarely simultaneously reported and achieved in the same composition.

In this work, a relaxor ferroelectric $\text{Pb}(\text{Ni}_{1/3}\text{Nb}_{2/3})_{0.5}\text{Zr}_{0.15}\text{Ti}_{0.35}\text{O}_3$ (PNNZT) ceramic was prepared by using a two-stage solid state reaction method. The composition was deliberately selected to near a tricritical point of tetragonal, rhombohedra and pseudocubic phases in the PNN-PT-PZ ternary system[13], as shown in Figure 1. It is found that high dielectric tunability (66.4%) with a large *FOM* of 180, simultaneously a high electrostriction strain of 0.319% with a large *Q* value of 0.028 m^4/C^2 and high electrocaloric strength ($\Delta T/\Delta E$) of 32.5 mK cm/kV can be achieved. It is expected that the idea that the composition with multiphase coexisting can provide a guide for rapid positioning and design of multifunctional ferroelectric materials and will open new perspectives for exploitation of other multifunctional ferroic materials.

2. Experimental procedure

$\text{Pb}(\text{Ni}_{1/3}\text{Nb}_{2/3})_{0.5}\text{Zr}_{0.15}\text{Ti}_{0.35}\text{O}_3$ (PNNZT) ceramics was fabricated using high-purity (99.9%) oxides via a columbite route. To avoid the formation of pyrochlore phases, the precursor of NiNb_2O_6 powder was synthesized from analytical grade powders of NiO and Nb_2O_5 by calcinating at 900 °C for 2 h. PbO with excess lead of 5%, TiO_2 , ZrO_2 , and Nb_2O_5 powders were mixed, milled and calcined at

900°C for 2 h. After grinding for 2 h in an agate mortar, the calcined powders were then compacted into pellets with 10 mm in diameter and 1 mm in thickness under a 300 MPa cold isostatic pressing and were sintered at 1225 °C for 2 h in air, and then cooled naturally to room temperature. To reduce the loss of lead oxide during sintering, all pellets were buried in the same composition.

The crystal structures of the sintered pellets were monitored by X-ray diffraction (XRD, Rigaku 9 KW Smartlab, Japan) on a diffractometer, using Cu K α radiation ($\lambda = 1.5406 \text{ \AA}$). The Raman scattering spectra were acquired by Raman spectrometer (Horiba HR800) with excitation source of 488 nm laser. The surface image was examined by scanning electron microscope (SEM, Model JEOL-6700F) operated at 20 kV/cm. The microstructure was studied by transmission electron microscopy (TEM; JEOL JEM-2100F) operated at 300 kV/cm. The density of all the pellets was measured by the Archimedes method. For the measurements of electrical properties, silver paste was painted on the polished pellets as the electrodes and fired at 550°C for 30 min. Dielectric permittivity measurements were carried out using an impedance analyzer (4294A, Agilent) with a measuring voltage $V_{ac} = 500 \text{ mV}$ at a heating rate of 3°C /min. The thermal stimulated current density was collected with a High Resistance Meter (4339B, Agilent) under the “zero-field-heating after 10 kV/cm field-cooling above the temperature of dielectric permittivity maximum” condition. The dc electric field dependence of the dielectric permittivity was measured at 10 kHz and room temperature. The longitudinal strain-electric field (S - E) and the polarization-electric field (P - E) hysteresis loops were obtained by means of a

ferroelectric tester (TF-2000, aix-ACCT) at 1 HZ. The electrostriction and the electrocaloric performances were calculated according to the $S-E$ and $P-E$ results, respectively. It should be pointed out that all measurements were performed by the same sample.

3. Result and discussions

Fig. 2(a) shows the XRD patterns of the PNNZT ceramics at three different polarization states of the as prepared, poled and depoled. All polarization states exhibited single perovskite phase and no traces from other impurity phases (pyrochlore phases, etc.) can be detected, indicating that the solid solution is formed. To investigate the coexistence of typical rhombohedral and tetragonal phases, the characteristic peaks between 43.9° and 45.5° can be well fitted into three peaks of $r(002)$, $t(002)$ and $t(200)$ by multi-peak fitting method, as shown in the inset of Fig. 2(a). The $r(200)$ peak is corresponding to a rhombohedral symmetry [14-16], while the $t(002)$ and $t(200)$ peaks are corresponding to a tetragonal symmetry. Moreover, the tetragonal phase can be transformed to the rhombohedral phase when poled, and the induced tetragonal phase can be reverted to the rhombohedral phase when depoled, as shown by the changes of intensities and positions of the three characteristic peaks. This is the benefit of the mobility and polarization of ferroelectric active ions near the MPB with a mixed phase region rather than a critical line, where the structural energies of the coexisted ferroelectric phases are nearly equal.

In order to understand the structure change of the PNNZT relaxor ferroelectric ceramics, Raman scattering spectrum was measured from 100 cm^{-1} to 900 cm^{-1} at 10

K interval in the temperature range between 293 K and 453 K. Representative plots of them are shown in **Fig. 2(b)**. Previous research work suggests that the polar $[\text{ZrO}_6]$ and especially $[\text{TiO}_6]$ clusters are responsible for the $A_1(\text{LO}_3)/E(\text{LO}_4)$ modes (around 718 cm^{-1}) and the presence of dissimilar ions at the centre of the octahedral creating asymmetry is responsible for the breathing-like mode A_{1g} (around 800 cm^{-1}).^[17] Obviously, the $A_1(\text{LO}_3)/E(\text{LO}_4)$ modes are activated by the structural distortion of the lattice, while the Raman active A_{1g} mode is driven by the chemical nature. It can be seen that the scattering intensity of all modes except the $A_1(\text{LO}_3)/E(\text{LO}_4)$ and A_{1g} modes decreased sharply first and then degraded gradually with the increase of temperature, as shown by the curve of the scattering intensity versus temperature of the representative mode $A_1(\text{LO}_2)$ (see the inset of Fig. 2(b)) ^[18]. Different to that of the representative mode $A_1(\text{LO}_2)$, there are three obvious peaks appeared on the curve of the scattering intensity versus temperature for the $A_1(\text{LO}_3)/E(\text{LO}_4)$ and A_{1g} modes. Their positions are about at 333 K, 373 K and 413 K, respectively. Moreover, the scattering intensity of the $A_1(\text{LO}_3)/E(\text{LO}_4)$ modes is stronger than that of the A_{1g} modes in the whole measuring temperature range, indicating that the contribution from the structural distortion of the lattice is much larger than that from the chemical nature.

Fig. 2(c) shows the SEM surface image of the PNNZT ceramics sintered at 1225 °C. The sample exhibits a well crystallized and dense microstructure, as well as a wide grain size of 1.5 to 5 μm . Meanwhile, terraced stripes can be observed on its surface of each grain, indicating that a step growth mode is employed. The EDS

results show that the composition of the sample is consistent with its chemical formula, as shown in the inset of Fig. 2(c).

To further get an insight into the microstructure of the PNNZT ceramics, TEM analysis was carried out, as shown in **Fig. 2(d)**. Tetragonal twin-like 90 ° domains with light or dark contrast can be readily seen, as marked by arrow 2 and 3[19]. A complex herringbone domain structure derived from the coexistence of tetragonal and rhombohedral phases can also be observed, as signed by arrow 1[19]. Furthermore, a small amount of nanodomains originated from the coexistence of pseudocubic and rhombohedral can also be detected near the junction of triple grain boundary, as shown by arrow 4[19]. Based on the above analyses and combined with the analysis result of XRD, it can be believed that the composition of the designed PNNZT ceramic is in a region of three phases coexisted. Therefore, it should be pointed that the phase transition induced by the electric field in Fig. 2(a) for the PNNZT ceramic not only originated from the contribution of tetragonal phase to rhombohedral phase, but also some of them maybe come from the contribution of pseudocubic phase to rhombohedral phase. In a word, it is very complex phase transition process.

Fig. 3 shows the dependence of the dielectric permittivity ($\epsilon(T)$), the dielectric losses ($\tan \delta(T)$) and the thermal stimulated current $J(T)$ vs. temperature of PNNZT ceramic. The sample exhibited a typical relaxor behavior, namely the temperature (T_m) of dielectric permittivity maximum as well as the temperature (T_m^δ) of maximum dielectric losses are shifted towards higher temperatures with increasing frequency. Meanwhile, dielectric dispersion appears in the vicinity and below T_m , whereas the

maximum values of dielectric losses increase with increasing frequency[20-22]. The relaxor behavior is considered to be closely related to the response of polar nanoregions (PNRs) which are characterized by the nano-sized polar islands with multiple homogeneities embedded in an average cubic matrix[23]. Furthermore, on the curve of the $J(T)$, a thermal depolarization temperature (T_d) with a current maximum of 0.35 mA/m^2 was observed at 398 K, which is slightly higher than the temperature of the dielectric losses maximum. It has been well documented that the gap between T_m and T_d (T_m-T_d) reflects the degree of the electric dipole order in relaxor ferroelectric ceramics[24]. The smaller T_m-T_d is, the greater the degree of the electric dipole order is. The value of the T_m-T_d at 10 kHz is only 10 K, indicating that a large electric dipole order or strong ferroelectric activities is accompanied with the PNNZT ceramic.

Fig. 4 shows the dependence of the ϵ and $\tan \delta$ vs. dc bias electric field at room temperature and 10 kHz. It can be seen that both the ϵ and the $\tan \delta$ decrease sharply with the increase of the bias dc electric field, indicating that there is a high dielectric non-linear electric field dependence. Dielectric tunability (η) and Figure-of-merit (FOM) can be defined as follows: $(\epsilon(0)-\epsilon(E))/\epsilon(0)$, and $\text{tunability}/\tan\delta$, respectively[25]. They both increase with increasing electric field, as shown in the inset of Fig. 4. A high tunability of 67% and a large FOM of 180 are achieved at $E = 15.9 \text{ kV/cm}$, which are comparable to those (tunability of 12% and FOM of 200 at $E = 30 \text{ kV/cm}$) of the $\text{Ba}_{0.4}\text{Sr}_{0.6}\text{TiO}_3$ ceramics[26], those of (tunability of 45% and FOM of 225 at $E = 40 \text{ kV/cm}$) of the $\text{BaZr}_{0.3}\text{Ti}_{0.7}\text{O}_3$ ceramic[27], indicating that the PNNZT

ceramic is a very promising for the application in dielectric tunable devices. Furthermore, the $\varepsilon(E)$ of the PNNZT relaxor ferroelectric ceramic can be described by the following equation[28].

$$\varepsilon(E) = \varepsilon_r(0) / \{1 + \lambda[\varepsilon_0 \varepsilon_r(0)^3 E^2]\}^{1/3} + (P_r x / \varepsilon_0) [\cosh(Ex)]^{-2}, x = P_r L^3 / (2k_B T) \quad (1)$$

where ε_0 is the dielectric permittivity of free space, λ a temperature-independent coefficient, $\varepsilon_r(0)$ the relative dielectric permittivity at zero field, P_r the polarization of a polar nanocluster, L the cluster size (or correlation length), k_B the Boltzmann's constant. The first term in Eq. (1) represents the polarization contribution from lattice phonons (Johnson contribution), and the second stands for the re-orientation contribution from polar nanoregions (Langevin contribution). The black solid line fitted according to Eq. (1) agrees quite well with the experimental data. Obviously, the nanoclusters make a significant contribution to ε below ~ 6 kV/cm, which decreases quickly with increasing E and almost disappears at an electric field above 9 kV/cm. It can also be seen that the dielectric permittivity contributed by the nanoclusters ($\varepsilon_{cluster}$) is 1144 under zero bias, about 20.06% of the total dielectric permittivity (ε_{total}). The size of polar nanoregions, according to the fitting, is $L = 12.6$ nm.

Fig. 5 shows the electric field dependence of the strain ($S_{strain}(E)$) of PNNZT ceramic at selected temperatures. A high strain level of 0.319% is obtained at room temperature and 40 kV/cm. This strain level is comparable with those of other lead-containing system[29-32]. For the linearity between S_{strain} and E , the piezoelectric constants (d_{33}^*) is calculated as 1197 pm/V from the slope of the origin of the S_{strain} - E curve, as shown by the red solid line in Fig. 5. Also, the high piezoelectric activities

(d_{33}) of the sample can be measured after dc electric field poling, and the obtained d_{33} value is about 608 pC/N, as shown in the inset (a) of Fig. 5. With the increase of the temperature, the $S_{strain}(E)$ become more and more hysteresis free, indicating an increase of the relaxor contribution from the polar nanoregions[33].

It is known that the electrostrictive strain follows the theoretically derived quadratic relation[30, 34, 35]:

$$S_{strain} = QP^2 \quad (2)$$

where Q is the electrostriction coefficient. The strain versus polarization squared (P^2) is plotted in the inset (b) of Fig. 5. It can be seen that the profile of S versus P^2 can be fitted well to a straight line in the whole electric-field range, as well as the measured temperature range. This indicates that the electrostriction coefficient does not depend on the strength of electric field and on temperature. From the fitting of the above branch of the S - P^2 at 308 K shown by the red solid line in the inset (b) of Fig. 5, a large Q value of $0.028 \text{ m}^4/\text{C}^2$ is obtained for the sample, which is also comparable with those of other lead-containing system[29-32]. Furthermore, it can be observed that the slope of the S - P^2 remains almost unchanged with the increase of the temperature, indicating that a high thermal stability of the Q is obtained. The excellent electrostriction performance of the PNNZT ceramic may make it an attractive material for application in precisely controlled devices.

In order to evaluate the electrocaloric effect (ECE) in the PNNZT ceramic, the electric field dependence of the polarization (P - E) loops at 1 Hz were measured at a 10 K interval in the temperature range between 308 K and 447 K. Representative

plots of P - E loops are shown in **Fig. 6**. Obviously, the shape of P - E loop becomes more and more slender with the increase of temperature. The temperature dependence of the polarization ($P(T)$) at selected electric field values is extracted from the upper branches of the P - E hysteresis loops in $E > 0$ and presented in the inset (a) of Fig. 6. The solid lines in the inset (a) of Fig. 6 represent cubic-spline interpolations of the raw experimental data. In order to estimate the ECE of the PNNZT ceramic, the curves of pyroelectric coefficients versus temperature $((\partial P/\partial T)_E(T))$ at selected electric field values were derived from the differential values of $P(T)$ curves and plotted in the inset (b) of Fig. 6. Assuming that the Maxwell relationship $(\partial P/\partial T)_E = (\partial S_{entropy}/\partial E)_T$ is established, reversible adiabatic changes in temperature (ΔT) and entropy ($\Delta S_{entropy}$) for a material of density ρ with heat capacity C are estimated by follows[5, 7]:

$$\Delta T = -\frac{1}{\rho} \int_{E_1}^{E_2} \frac{T}{C} \left(\frac{\partial P}{\partial T} \right)_E dE \quad (3)$$

$$\Delta S_{entropy} = -\frac{1}{\rho} \int_{E_1}^{E_2} \left(\frac{\partial P}{\partial T} \right)_E dE \quad (4)$$

Where T is the operating temperature, P is the maximum polarization at the applied electric field E , and E_1 and E_2 are the initial and final applied electric field, respectively. In the temperature range of interest for the PNNZT ceramics the heat capacity C and the density ρ are 0.3 J/(K·g) and 7.9 g/cm³, respectively. The adiabatic temperature change ΔT and entropy change $\Delta S_{entropy}$ of the PNNZT ceramic under different electric field changes ΔE are shown in **Fig. 7** and its inset (a), respectively. Peak $\Delta T = 1.3$ K at 40 kV/cm was obtained at 430 K and near the right

of the temperature of the dielectric maximum, as well as peak $\Delta S_{entropy} = 0.87 \text{ J}/(\text{K}\cdot\text{kg})$. Meanwhile, it can be found that the position of the ΔT or $\Delta S_{entropy}$ peak shifted to higher temperature with the increase of the applied electric field, in agreement with previous experimental and theoretical reports[36, 37], indicating that the zone of ferroelectric phases was extended under the induction of the applied electric field. Furthermore, it can be found that a small peak around 325 K can be observed on both ΔT and $\Delta S_{entropy}$. The appearance of the peak near room temperature may be related to the phase transition of tetragonal or pseudocubic phase to rhombohedral phase induced by the electric field, as discussed in the part of microstructure of PNNZT ceramic.

In spite of the small value of peak ΔT , however, the electrocaloric strength ($\Delta T/\Delta E = 32.5 \text{ mK cm/kV}$) of the PNNZT ceramic designed to near a tricritical point of three-phase coexistence is large, as shown by the inset (b) of Fig. 7. It is comparable to that (5 mK cm/kV) of the antiferroelectric $\text{PbZr}_{0.95}\text{Ti}_{0.05}\text{O}_3$ ceramics, that (6 mK cm/kV) of the ferroelectric polymer P(VDF-TrFE) and even that (25 mK cm/kV) of the ferroelectric single crystal $0.9\text{Pb}(\text{Mg}_{1/3}\text{Nb}_{2/3})\text{O}_3\text{-}0.1\text{PbTiO}_3$ [7, 38, 39], etc.

Moreover, by using thin-film geometry, an intrinsic *ECE* with bigger ΔT in PNNZT could be obtained due to a significant improve in its dielectric breakdown strength. Similar to the *ECE*, an elastocaloric change in temperature ΔT_σ for a material with heat capacity C_σ is determined by[40]:

$$\Delta T_\sigma = -\int_0^\sigma \frac{T}{C_\sigma} \left(\frac{\partial S_{strain}}{\partial T} \right)_{\sigma, E} d\sigma \quad (5)$$

where the Maxwell relation $(\partial S_{strain}/\partial T)_{\sigma,E} = (\partial S_{entropy}/\partial \sigma)_{E,T}$ is assumed. For a thin-film structure, the field σ stress can be regulated and controlled by using substrates with different lattice parameters. Based on the large diffused peak of the $(\partial S_{strain}/\partial T)_E(T)$, which is extracted from the polynomial fitting curve of the strain versus temperature ($S_{strain}(T)_E$) of PNNZT, as shown by the red arrow in the inset (b) of Fig. 7, it is believed that a larger *ECE* with a wide operating temperature can be achieved by coupling the elastocaloric effect[41]. Furthermore, in practical application, the peak of ΔT can be shifted to room temperature by elements doping such as La, Ba, etc[42].

4. Conclusions

A high dielectric tunability of 67% with a large *FOM* of 180, simultaneously a high electrostriction strain of 0.319% with a large *Q* value of 0.028 m⁴/C² and a high electrocaloric strength ($\Delta T/\Delta E$) of 32.5 mK cm/kV are observed in the tricritical point relaxor ferroelectric PNNZT ceramic with the coexistence of tetragonal, rhombohedral and pseudocubic phases. This is accomplished by the low energy barrier among the transitions of phases and strong relaxor ferroelectric activities around the tricritical point. The high dielectric tunability, electrostriction strain and electrocaloric strength of the relaxor ceramic may make it an attractive multifunctional material for applications in dielectric tunable, precisely controlled and electric refrigeration devices. The exploration of tricritical point in multi-component phase diagram maybe can provide a guide for the design of multifunctional ferroelectric materials, as well as other multifunctional ferroic materials.

Acknowledgements

This work was supported by the Hong Kong Polytechnic University (Project Nos.: A-PL54, G-UC69 and 1-ZVCG), the National Natural Science Foundation of China (51402196, 51272161, 51172187, 51202150), the China Postdoctoral Science Foundation (2014M552229), and the Shenzhen Science and Technology Research Foundation (CXB201005240010A), 111 Program (B08040) of MOE,.

References

- [1] L. Song, Y. Chen, G. Wang, L. Yang, T. Li, F. Gao, X. Dong, *Ceram. Int.*, 40 (2014) 12573-12577.
- [2] S.-X. Wang, J.-H. Hao, Z.-P. Wu, D.-Y. Wang, Y. Zhuo, X.-Z. Zhao, *Appl. Phys. Lett.*, 91 (2007).
- [3] Q. Li, G. Zhang, X. Zhang, S. Jiang, Y. Zeng, Q. Wang, *Adv. Mater.*, 27 (2015) 2267.
- [4] C. Ang, Z. Yu, *Adv. Mater.*, 18 (2006) 103-106.
- [5] A.S. Mischenko, Q. Zhang, J.F. Scott, R.W. Whatmore, N.D. Mathur, *Science*, 311 (2006) 1270-1271.
- [6] B. Peng, H. Fan, Q. Zhang, *Adv. Funct. Mater.*, 23 (2013) 2987-2992.
- [7] B. Neese, B. Chu, S.-G. Lu, Y. Wang, E. Furman, Q.M. Zhang, *Science*, 321 (2008) 821-823.
- [8] B. Peng, H. Fan, Q. Zhang, *J. Am. Ceram. Soc.*, 96 (2013) 1852-1856.
- [9] Y. Bai, G. Zheng, S. Shi, *Appl. Phys. Lett.*, 96 (2010).
- [10] G. Hu, F. Gao, L. Liu, B. Xu, Z. Liu, *J. Alloys Compd.*, 518 (2012) 44-50.

- [11] L. Yang, G. Wang, X. Dong, D. Remiens, *J. Am. Ceram. Soc.*, 93 (2010) 1215-1217.
- [12] Y. Somiya, A.S. Bhalla, L.E. Cross, *Integrated Ferroelectrics*, 131 (2011) 237-245.
- [13] X.H. Zhu, Z.Y. Meng, *J Mater Sci*, 31 (1996) 2171-2175.
- [14] X.P. Jiang, J.W. Fang, H.R. Zeng, G.R. Li, D.R. Chen, Q.R. Yin, *J. Mater. Res.*, 15 (2000) 2745-2749.
- [15] M.S. Yoon, H.M. Jang, S. Kim, *Jpn. J. Appl. Phys.*, 34 (1995) 1916-1921.
- [16] M.S. Yoon, H.M. Jang, *J. Appl. Phys.*, 77 (1995) 3991-4001.
- [17] V.S. Puli, A. Kumar, D.B. Chrisey, M. Tomozawa, J.F. Scott, R.S. Katiyar, *J. Phys. D: Appl. Phys.*, 44 (2011) 395403.
- [18] M. Deluca, T. Sakashita, W. Zhu, H. Chazono, G. Pezzotti, *J. Appl. Phys.*, 101 (2007) 083526.
- [19] Z. Xinhua, Z. Jianming, Z. Shunhua, L. Qi, M. Zhongyan, L. Zhiguo, M. Naiben, *J. Eur. Ceram. Soc.*, 20 (2000) 1251-1255.
- [20] A.A. Bokov, Z.G. Ye, *Appl. Phys. Lett.*, 77 (2000) 1888-1890.
- [21] A.A. Bokov, Z.G. Ye, *J Mater Sci*, 41 (2006) 31-52.
- [22] A.A. Bokov, Y. Zuo-Guang, *Journal of Advanced Dielectrics*, 2 (2012) 1241010.
- [23] F. Desheng, H. Taniguchi, M. Itoh, S.Y. Koshihara, N. Yamamoto, S. Mori, *Phys. Rev. Lett.*, 103 (2009) 207601 - 207604.
- [24] Z.-G. Ye, *Key Eng. Mater.*, 155-156 (1998) 81-122.
- [25] T.M. Correia, Q. Zhang, *J. Appl. Phys.*, 108 (2010) 044107.

- [26] J. Zhang, J. Zhai, X. Yao, *Scr. Mater.*, 61 (2009) 764-767.
- [27] X.G. Tang, K.H. Chew, H.L.W. Chan, *Acta Mater.*, 52 (2004) 5177-5183.
- [28] C. Ang, Z. Yu, *Physical Review B*, 69 (2004) 174109.
- [29] P. Kumar, C. Prakash, T.C. Goel, *Sci. Technol. Adv. Mater.*, 8 (2007) 463-468.
- [30] S.E. Park, T.R. ShROUT, P. Bridenbaugh, J. Rottenberg, G.M. Loiacono, *Ferroelectrics*, 207 (1998) 519-526.
- [31] Z. Qiming, P. Wuyi, A. Bhalla, L.E. Cross, *J. Am. Ceram. Soc.*, 72 (1989) 599-604.
- [32] S.E. Park, V. Vedula, M.J. Pan, W.S. Hackenberger, P. Pertsch, T.R. ShROUT, *Proceedings of the SPIE - The International Society for Optical Engineering*, 3324 (1998) 136-144.
- [33] R. Pirc, R. Blinc, V.S. Vikhnin, *Physical Review B*, 69 (2004) 212105.
- [34] K. Uchino, S. Nomura, L.E. Cross, S.J. Jang, R.E. Newnham, *J. Appl. Phys.*, 51 (1980) 1142-1145.
- [35] S.E. Park, T.R. ShROUT, P. Bridenbaugh, J. Rottenberg, G.M. Loiacono, *Ferroelectrics*, 207 (1998) 519-526.
- [36] Y. Bai, G.-P. Zheng, K. Ding, L. Qiao, S.-Q. Shi, D. Guo, *J. Appl. Phys.*, 110 (2011) 094103.
- [37] M.C. Rose, R.E. Cohen, *Phys. Rev. Lett.*, 109 (2012) 187604.
- [38] J. Wang, T. Yang, K. Wei, X. Yao, *Appl. Phys. Lett.*, 102 (2013) 152907.
- [39] L. Luo, H. Chen, Y. Zhu, W. Li, H. Luo, Y. Zhang, *J. Alloys Compd.*, 509 (2011) 8149-8152.

[40] Y. Liu, I.C. Infante, X. Lou, L. Bellaiche, J.F. Scott, B. Dkhil, *Adv. Mater.*, 26 (2014) 6132.

[41] M. Liu, J. Wang, *Scientific reports*, 5 (2015) 7728.

[42] X. Hao, J. Zhai, L.B. Kong, Z. Xu, *Prog. Mater Sci.*, 63 (2014) 1-57.

Figure captions

Figure 1. The selected composition used in this work and its position (the red dot) in the phase diagram of the PNN-PT-PZ ternary solid solution [13]. F_T: ferroelectric tetragonal, F_R: ferroelectric rhombohedral, F_{pc}: pseudocubic, P: paraelectric.

Figure 2. (a) XRD pattern of the PNNZT ceramics. Inset: the fitted patterns between 43.9 ° and 45.5 °. (b) Raman spectra of the PNNZT ceramic as a function of wave number at selected temperatures. Inset: the scattering intensities versus temperature for the selected A₁(LO₃)/E(LO₄), A_{1g} and A₁(LO₂) modes. (c) SEM surface image and EDS (inset). (d) TEM image. Arrow 2 and 3: tetragonal twin-like 90° domains, arrow 1: herringbone domains with coexistence of tetragonal and rhombohedral, the arrow 4: nanodomains with coexistence of pseudocubic and rhombohedral.

Figure 3. $\varepsilon(T)$, $\tan \delta(T)$ and $J(T)$ of PNNZT ceramic. J is collected under the “zero-field-heating after 10 kV/cm field-cooling above the temperature of dielectric permittivity maximum” condition.

Figure 4. $\varepsilon(E)$ and $\tan \delta(E)$ of PNNZT ceramic at room temperature and 10 kHz. Symbols: experimental data, the blue short dashed dot line: the Johnson contribution from polar nanoclusters, the red short dashed line: the Langenvin contribution from lattice phonons. Inset: $\eta(E)$ and $FOM(E)$.

Figure 5. $S_{strain}(E)$ of PNNZT ceramic at selected temperatures. Inset: (a) d_{33} at room temperature and (b) $S_{strain}(P^2)$ at selected temperatures.

Figure 6. P - E loops of PNNZT ceramic at selected temperatures. Inset: (a) $P(T)$ at selected electric field values and (b) $(\partial P/\partial T)_E(T)$ at selected electric field values.

Figure 7. $\Delta T(T)$ of PNNZT ceramic at selected electric fields. Inset: (a) $\Delta S_{entropy}(T)$ at selected electric fields. (b) $COP(T)$ and $(\partial S_{strain}/\partial T)_E(T)$ at 40 kV/cm.

2015-06-16

High dielectric tunability, electrostriction strain and electrocaloric strength at a tricritical point of tetragonal, rhombohedral and pseudocubic phases

Peng, Biaolin

Elsevier

Zeng X et al. High dielectric tunability, electrostriction strain and electrocaloric strength at a tricritical point of tetragonal, rhombohedral and pseudocubic phases, *Journal of Alloys and Compounds*, Volume 646, 15 October 2015, Pages 597-602.

<https://dspace.lib.cranfield.ac.uk/handle/1826/10654>

Downloaded from Cranfield Library Services E-Repository