

Progress in Pectin Based Hydrogels for Water Purification: Trends and Challenges

Sourbh Thakur^{a, b*}, Jyoti Chaudhary^b, Vinod Kumar^c and Vijay Kumar Thakur^{d, e*}

^a*Institute of Materials Science of Kaunas University of Technology, Barsausko 59, LT-51423
Kaunas, Lithuania*

^b*School of Chemistry, Shoolini University, Solan 173212, Himachal Pradesh, India*

^c*Centre for Bioenergy and Resource Management (CBRM), School of Water, Energy and
Environment, Cranfield University, Bedford MK43 0AL, United Kingdom*

^d*Enhanced Composites and Structures Center, School of Aerospace, Transport and
Manufacturing, Cranfield University, Bedfordshire MK43 0AL, UK*

^e*Department of Mechanical Engineering, School of Engineering, Shiv Nadar University, Uttar
Pradesh, 201314, India*

ABSTRACT

Pectin is one of the finest natural polymer which has drawn great attention because of its applications in different fields. Due to the quintessential structure of pectin, it can be transformed into variety of useful products. It can be utilized as a blend in many polymers to make a mixture or a composite material. Owing to considerable collection in chemical conformation and cross-linking mechanism, different pectin based hydrogels have been prepared for different characteristics in pharmaceutical and bio-medical sites. Inventive properties of hydrogels like volubility, swellability, solvability and hydrophilicity make them better alternative for wastewater treatment. Recently, pectin based hydrogels have demonstrated excellent performance to eliminate various metal ions and dyes from the polluted water. The adsorption

1
2
3
4 characteristics of pectin based hydrogels can be upgraded by using nanoparticles, which prompts
5
6 to the development of hydrogel nano-composites. In this review article, we have summarized a
7
8 comprehensive assessment in the direction of using pectin based hydrogels to remove toxic
9
10 pollutants from aqueous solution. Sodium acrylate-co-N-isopropylacrylamide based pectin
11
12 hydrogel has demonstrated the maximum adsorption capacities of 265.49, 137.43, 54.86, 53.86,
13
14 51.72 and 50.01 mg g⁻¹ for the adsorption of methyl violet, methylene blue, Pb(II), Cu(II), Co(II)
15
16 and Zn(II) respectively. We have also discussed the pectin structure, properties and applications
17
18 in this article.
19
20
21
22
23

24 **Keywords:** Pectin; bio-waste material; pectin based hydrogel; water pollution; heavy metal ions
25
26 and dye removal
27
28
29

30 *Corresponding authors Email: thakursourbh@gmail.com, sourbh.sourbh@ktu.lt,
31
32 vijay.kumar@cranfield.ac.uk
33
34
35

36 1. Introduction

37
38 Green chemistry gives an important requisite for sustainable addition to human society due to
39
40 deteriorating environment (Hao et al., 2018; Kaveeshwar et al., 2018; Pakdel and
41
42 Peighambaroust, 2018). It is also called defendable chemistry and used to diminish or remove
43
44 toxic components from environment (Attallah et al., 2017; Raizada et al., 2017). In our
45
46 environment, water pollution is the biggest global problem (Ji et al., 2018). Water pollution
47
48 adversely affects many living organisms creating serious health related issues (Baciak et al.,
49
50 2016). Hydrogels can find useful applications in water purification because of their specific
51
52 properties (Ali et al., 2012; Dudu et al., 2015; Li et al., 2017) (**Figure 1**). Hydrogels are branched
53
54 polymers with three dimensional structures having excellent water absorption capacity (Bian et
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 al., 2018; Li et al., 2017). Hydrogels can be represented as the binary system of any significant
5
6 polymer and fluid in which the development of sol happens when the collaboration is very
7
8 supported in polymer-fluid than that of both polymer-polymer interactions and liquid-liquid
9
10 interactions (Amini and Nair, 2012; Chenite et al., 2000; Tous et al., 2011; Zhang et al., 2013).
11
12 Super absorption properties of hydrogels are sensualized to their capability to absorb maximum
13
14 volume of liquid or water (Shahmirzadi et al., 2018; Shin et al., 2009a, 2009b; Wang et al.,
15
16 2017), approximately 10 to 20 times to the actual weight (molecular weight) of hydrogel and
17
18 after absorption of liquid or water, the hydrogel occupy swollen form (Fang et al., 2016; Kim et
19
20 al., 1992). The applications of hydrogel like pliability, flexibleness, stretchiness and porousness
21
22 are sensualized to the water absorption ability (Ji et al., 2018; Thakur and Arotiba, n.d.).
23
24 Hydrogels exhibits both partially liquid and fully solid characteristics (Jagur-Grodzinski, 2010;
25
26 Zhao et al., 2015a). A three dimensional configuration of hydrogel is normally originated via
27
28 physical and organic/chemical cross-linking (Khan et al., 2016; Pereira et al., 2011). The major
29
30 liable characteristics for the production of physically crosslinked hydrogel are (a) electrostatic
31
32 interactions (b) hydrophobic interactions (Steed, 2011) (c) co-ordination bonds and (d) hydrogen
33
34 bonding (Appel et al., 2015). The amphiphilic chemical/organic molecules (Liu et al., 2011) or
35
36 inorganic nano-composites in the form of aqueous solution are able to produce hydrogels with
37
38 super-molecular chemistry (Pakulska et al., 2012). On other hand, there are some changes in
39
40 around positional circumstances in chemically reacted hydrogels (Adesanya et al., 2014; N.
41
42 Thakur et al., 2018a) like (a) pH (Barrett et al., 2013) (b) ionic strength (Zhao et al., 2015b) (c)
43
44 temperature (Thakur et al., 2015; Xia et al., 2013) and (d) electric field (Parisi-Amon et al.,
45
46 2013) which shows the quantity phase isomerization (Yoshimura et al., 2005). Hydrogels have a
47
48 permeable nature which allow them to the retention of waste/poisons/pollutants from the
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 polluted/waste water (Thakur et al., 2018b; Peppas, 2010). The production of hydrogels have
5
6 been raised because of their excellent absorptive behavior (Buchholz and Graham, 1998; Hogan,
7
8 2010; 2013; Peppas and Khare, 1993; Rosiak and Yoshii, 1999; Teshager et al., 2016; Wandrey
9
10 et al., 2010). Durable and degradation properties are the major advantages of biopolymer
11
12 hydrogels (Adsul et al., 2016). If polymers are hydrophilic and water used as liquid, then the
13
14 product formation with strong polymer-liquid interactions are known as hydrosols. The limits of
15
16 the reaction are mainly dependent upon the various kinds of functional groups, polymer
17
18 structures and the amount of ions in polymer structure as well as the final solution, pH and
19
20 temperature. The solution of a hydrophilic polymer in the water as a fluid can be stopped by the
21
22 expansion of cross linkers by utilizing either physical or by chemical process and these
23
24 crosslinked hydrosols are called hydrogels (Fang et al., 2016; Thakur and Thakur, 2014; Thakur
25
26 and Voicu, 2016). They can swell just in the surrounding fluid to a specific swelling proportion
27
28 dependent on the concentration of used cross linkers.
29
30
31
32
33
34

35
36 Hydrogels have specific properties like excellent absorptive behavior to deal with polluted water.
37
38 Hydrogels are the three-dimensional network chain polymer that are hydrophilic in nature,
39
40 insoluble in water, sometimes found like a colloidal gel and water behave as dispersion medium
41
42 (Buchholz and Graham, 1998; Li et al., 2013; Peppas and Khare, 1993; Thakur et al., 2017).
43
44 These are also crosslinked polymer chains that soaks up tolerable quantity of water or any
45
46 aqueous solution (Thakur et al., 2018c). The network chains are possessed by the homo-
47
48 polymers or co-polymers and are unsolvable due to the existence of chemical crosslink (Bae et
49
50 al., 2015; Li et al., 2014; Ren et al., 2014; Singh and Singh, 2012; Wichterle and Lim, 1960)
51
52 (tie-points, junctions) or physical crosslink, such as involvement or crystallization. The huge
53
54 volume of water constituents of materials contributes to their bio-compatibility (Rosiak and
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 Yoshii, 1999). The double cross linking gives the network chain structure and physical rawness.
5
6 Hydrogels possess thermodynamic characteristics with water which permit them to swell in the
7
8 given medium. Hydrogels contains very huge amount of water i.e., over 90 % of water and are
9
10 known as good natural absorbent (Rosiak and Yoshii, 1999). They also possess degree of
11
12 flexibility similar to the earthy tissues due to the expressive water content. The stimuli responded
13
14 swelling hydrogels are the environmentally friendly, have the great ability to respond the
15
16 changes in their superficial environment (Ferry, 1980; Wach et al., 2002). They exhibit some
17
18 complicated substitutes in their swelling properties, network chain structure and unconscious
19
20 intensity in response to the changes in ionic strength or pH of the surrounding biological fluid or
21
22 temperature. Due to their nature, these substances shows various applications in a broad spectra,
23
24 like separation membrane, chemical valves and some drug delivery devices, etc. (Ahmed, 2015).
25
26 Mechanism of network formation; gelation deals with the connecting of macro-molecular catena
27
28 together which originally over to the successively weightier branched; up to now soluble
29
30 polymer depend up on the structure and formation of the starting constituents/components
31
32 (**Figure 2**). The composites of such poly-disperse bifid polymers are known as ‘sol’ (Gulrez et
33
34 al., 2011). In other words, this ‘eternal polymer’ is named as ‘gel’ or ‘circuitry’ and is infiltrated
35
36 with outspread polymers. The conversions from a complex with definable stretched polymer to
37
38 interminable molecules are known as ‘sol-gel conversion’ (or ‘gelation’) and the analytical point
39
40 where gel generally appears known as the ‘gel point’ (Bajpai et al., 2008; Ben-Nissan et al.,
41
42 2016). Gelation can appear either by physical coupling/linking or by chemical coupling/ linking
43
44 (Gulrez et al., 2011).
45
46
47
48
49
50
51
52
53
54
55

56 Some common elements include polyvinylalcohol (PVA), sodium poly-acrylate, acrylate-
57
58 polymers and various copolymers with the richness of water loving groups. These polymers
59
60
61
62
63
64
65

1
2
3
4 exhibit a common property of being capable to take up the huge amount of water (Bajpai et al.,
5
6 2008). In physical gels, the character of the crosslinking action is physical. This is generally
7
8 accomplished by utilizing physical actions like coalition, aggregation, affiliation, crystallization,
9
10 complication and hydrogen bonding (Gulrez et al., 2011). Conversely, a chemical process in
11
12 which synthesized bivalent crosslinking is idolized to assemble a chemical hydrogel with
13
14 superior properties. Physical hydrogels are convertible/reversible in nature due to the
15
16 informational additions and chemically cross linked hydrogels are unchangeable/permanent in
17
18 nature. More information about the hydrogels is shown in **Table 1**. Responsive hydrogels can be
19
20 categorized into various forms in response to alteration in environmental factors such as pH,
21
22 temperature, and liquid composition which partially depends upon its structure. Hydrogels can
23
24 counter to environmental alterations via reforming their size or shape as presented in **Table 2**
25
26 (Huang et al., 2004). Most dominant characteristics that activate hydrogels are pH, temperature,
27
28 and swelling medium. While for the term non-ionic hydrogels are practically inconsiderate to pH
29
30 selection, ionic hydrogels indicates generous/sensible differences in size with some modification
31
32 in pH. Until the point that the temperature is troubled, hydrogels require hydrophobic
33
34 compilations or those influences the chain collection counter to the temperature modification in
35
36 extensive scale (Satarkar and Hilt, 2008).
37
38
39
40
41
42
43
44
45

46
47 Actually the appearance of solvability and swellability/volubility are directed by alike physical
48
49 energies, the reaction of the hydrogel to the temperature variations are either constant or not. As
50
51 a result, the solvability and volubility of the hydrogel can increase with increase in temperature,
52
53 conversely checked with reverse thermo-responsive hydrogels. Hydrogels can also alter their size
54
55 and shape with the change in constituents of the swelling standard solution. Opuently, the
56
57 hydrogel reactions would be effective if the swelling medium occupies salt and a non-solvent.
58
59
60
61
62
63
64
65

1
2
3
4 Number of applications of pectin based materials have been explored in the literature due to its
5
6 lavishing characteristics (Mohnen, 2008).
7

8
9 Sepehri and Sarrafzadeh both examined the membrane polluted in membrane bioreactors and
10
11 found that it usually depends on the microbial occupant's structure and microbial cell solidity. A
12
13 nitrifying-enriched activated sludge occurred in this examination during particular ammonium
14
15 nourishing of conventional activated sludge. Next, the predominance of autotrophic nitrifier
16
17 population in nitrifying-enriched activated sludge scheme was checked and evaluated with
18
19 conventional activated sludge scheme by its excellent nitrification efficiency (100% vs. 43%) and
20
21 low chemical oxygen demand exclusion (9% vs. 65%). Furthermore, the greatest quantity of N-
22
23 NO_3^- formed from same concentrations of ammonium in conventional activated sludge and
24
25 nitrifying-enriched activated sludge schemes were 6.6 mg L^{-1} and 37.5 mg L^{-1} respectively
26
27 (Sepehri and Sarrafzadeh, 2018). In this article, we will discuss about the potential of bio-waste
28
29 pectin for water treatment along with its structure and properties. The pectin based hydrogels for
30
31 water purification has been primarily reviewed in present article.
32
33
34
35
36
37

38 **2. Pectin**

39 **2.1. Pectin from bio-waste materials**

40
41 This part of the article will focus on explaining the effect of the bio-mass resources on the
42
43 structural characteristics which are representative of pectin-rich biomass, for examples: mango,
44
45 guava, and waste apples etc. The bio-wastes are examined in numerous investigations which are
46
47 an industrial waste produced in fruit waste materials like orange, apple, mango peels and so on
48
49 (Table 3). The fruits peel waste after juicing is effectively and abundantly obtained as a low
50
51 quality by-product. Researchers have examined the adsorptive migration of arsenic by
52
53 consuming a metal-stacked gel synthesized from orange fruit waste (Ghimire et al., 2002). An
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 orange waste composite occupies around 10 % pectin which prevails in the cell wall as an
5
6 intercellular creating material. Pectin is a natural polysaccharide material in which pectic acid
7
8 and some acidic polysaccharide units are partly esterified through methyl groups (Banerjee et al.,
9
10 2016; Fidalgo et al., 2016). It is easily changed into pectic acid through saponification with alkali
11
12 groups like calcium hydroxide. In the past work, it was shown that pectic acid and alginic acid
13
14 firmly connected with different heavy metals contributing to stable five member ring chelates
15
16 (Dhakal et al., 2005). **Figure 3** represent brief schematic on extraction of fruit waste material as
17
18 a pectin powder.
19
20
21
22
23

24 **2.2. Structure**

25
26 The pectin is hetero-polysaccharide found in essential cell walls of terrestrial/earthy plants
27
28 (Yapo, 2009). Pectin's were reported first via Henri Braconnot in 1825 (Yapo, 2010, 2011). It is
29
30 procured in commercial form mostly in light brown color and is mostly made by citrus fruits, and
31
32 most of the food is used as a jelling agent, mostly in jelly and jam. Pectin was introduced to the
33
34 foundation in 1825 via Henri Braconnot (Yapo, 2010, 2011), while the method of marmalade
35
36 and jam was being used by pectin already. To make good accumulated jam with fruit, mostly bad
37
38 pectin or other low-pectin fruits were added to the process. At the time of the Industrial
39
40 alteration, it was made in liquid form. After that, pectin was made and used in powder form since
41
42 the years of 1920 and 1930. It is very easy to utilize and handle the powder form (Ahlawat et al.,
43
44 2007). In plant biology, there is a strong group of polysaccharides in pectin, which is found in
45
46 the walls of most beginning cells as shown in **Figure 4** (Lodish et al., 2008). It is found in
47
48 excessive amounts in non-wooded part of terrestrial/earthy plants. Pectin is most valuable
49
50 constituent of middle lamella, where it supports to keep cells together, but it also exist in the wall
51
52 of the beginning. The amount of pectin and chemical structures are found separately in every
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 portion of plant. Pectin is one of the important cell wall polysaccharides extending the starting
5
6 cell wall and commands the plant to grow. At the time of fruit maturation, pectin is damaged by
7
8 enzyme pectinase and pectinesterases. In this biological activity, the fruits become soft (Grierson et
9
10 al., 1986) and pectin gives the property of a kind of soluble fiber (Huang et al., 2007; Lindinger
11
12 et al., 1997). Pectin in fruits and vegetables is present in the form of poly-molecular and poly-
13
14 disperse form in relation to its chemical constitution and molecular density (Mohnen, 2008b).
15
16 The statistical and percentage data of monomeric units of pectin may vary for various materials
17
18 that further depend upon the origin, the protocol used for isolation and subsequent analysis.
19
20 Different physical and chemical characteristics of pectin can be utilized for preparing its various
21
22 forms based on origin and isolation method (Laurent and Boulenguer, 2003). Pectin is a polymer
23
24 of rhamnogalacturonan-1 (RG-1). The basic point and main character of all pectin fragment is a
25
26 single chain of (1+4)-linked α -D-galactopyranosyluronic acid groups, forming it α -D-
27
28 galacturonan. Approximately "all earthy pectin's" few carboxyl units are in the form of methyl
29
30 ester (Yapo, 2011). Based on the conditions of isolation, the rest of free carboxylic acid units
31
32 may be half or fully neutralized, i.e., half or fully commenced as Na, K or ammonium acetate
33
34 groups. The relative density of partially esterifies sugar acid unit to complete sugar acid groups is
35
36 "Traversed the quality of esterification" (Ridley et al., 2001) and strongly effects the solvability,
37
38 capability to make gel, circumstances required for the gelation, gelling temperature and gel
39
40 characteristics for the synthesis (Mesbahi et al., 2005). In pectin from origins, few groups occur
41
42 as 0-2 or 0-3 acetates. All pectic polysaccharides are to a definite extent O-acetylated. The
43
44 acetyl-moieties are frequently involved to the 0-2 and 0-3 locations of the galacturonic acid
45
46 moiety of mutually homogalacturonic (HG) and RG-I. Acetylation of the pectin affects the
47
48 gelation characteristics of this category of the polymers, which is significant for the food
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 production industries. The acetate groups might unnecessarily interfere among the calcium
5 crosslinking among HG polymers by the use of steric hindrance. Such compounds change to
6 ester that prevents the gel formation, when one sugar acid unit out of eight sugar acid groups is
7 mono-esterified by 0-2 or 0-3 acetates (Kirby et al., 2006). The occurrence of acetyl groups,
8 hence, forms some potential origins of commercial pectin, e.g., (round red root vegetables) sugar
9 beet (Amaranth, spinach etc.), sunflower, fruits waste (orange, mango, banana etc. fruit peels)
10 and potato (less desirable). Neutral sugars, primarily L-rhamnose also occur, however, the
11 disunity over the arrangement in the bilinear chain (Leroux et al., 2003). As present in **Figure 5**,
12 structure of pectin shows three different pectic polysaccharides i.e. homo-galacturonan,
13 rhamnogalacturonan (RG-I) and rhamnogalacturonan II (RG-II) attached with each other
14 (Mohnen, 2008a; Minzanova et al., 2018). Pectic polysaccharides can be presented by three
15 different parts (Caffall and Mohnen, 2009; Ovodov, 2009; Pedrolli et al., 2009; Ridley et al.,
16 2001b) (Valdés García et al., 2015) (**Figure 6**). **Figure 6** demonstrates the classification of pectic
17 polysaccharides on the bases of D-galacturonic acid (Valdés García et al., 2015).
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38

39 **2.3. Physical properties**

40
41 Pectin is a group of substances which forms gels when dissolved in water under suitable
42 conditions. It is derived from the protopectin found in the middle lamellae of plant cells.
43 Protopectin is insoluble, but is converted to soluble pectin as fruit ripens. If dissolved at a high
44 temperature, mono-valent diazonium salts or alkali metal salts of pectic acids are normally
45 solvable only in water but not in case of any liquids; di-valent and tri-valent diazonium salts are
46 weakly solvable or insolvable (BeMiller, 1986). However, pectin is not taken as thickening
47 agents; pectin mediums acquire the non-Newtonian, Pseudo plastic properties of many poly-
48 saccharides. With solvability, density of pectin solution is connected to molecular/atomic weight,
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 degree of esterification (DE), concentration of the synthesized solution, the pH behavior and
5
6 occurrence of ions in prepared solution (Evageliou et al., 2000). Normally density, viscosity,
7
8 solvability and gel formation are correlated, i.e., parameters that increases the volume of gel, for
9
10 example, will rise the capacity to gel, lower solvability, and raise density/viscosity (Brigand et
11
12 al., 1990). All these physical characteristics of pectin are due to their configuration which is a bi-
13
14 linear poly-anion (poly-carboxylate) (Plaschina et al., 1978).
15
16

17
18 Three different methods are usually planned for the accomplishment of alkalinity enzymatic
19
20 alteration of polysaccharides: (i) single-chain method, whereby the necessary of the enzyme is
21
22 followed via exchange of all neighboring substrate positions on the polymer chain; (ii) multiple-
23
24 chain method, whereby the enzyme-substrate compound separates subsequent to every reaction,
25
26 resultant in the alteration of a particular residue for every attack; and (iii) multiple-attack
27
28 method, whereby the enzyme catalyzes the alteration of a restricted usual quantity of residues for
29
30 each dynamic enzyme-substrate compound produced. The usual number of developed residues
31
32 has been defined as the degree of multiple attacks (Duvetter and Fraeye, 2006).
33
34
35

36
37 Duvetter and Fraeye examined the mode of de-esterification of alkaline and acidic pectin methyl
38
39 esterase at different pH conditions. Extremely esterified citrus pectin was de-esterified at pH 4.5
40
41 and 8.0 through a fungal pectin methyl esterase. Interchain de-esterification pattern was
42
43 calculated by absorption of the pectin products with endo-poly-galacturonase and successive
44
45 study via size elimination and anion exchange chromatography. No effect of pH was seen on the
46
47 de-esterification method of both of the two proteins. Acidic, parasitic pectin methyl esterase
48
49 changed over pectin as indicated by different chain methods, with a restricted level of various
50
51 multiple attacks at the intra-chain level, both at pH 4.5 and at pH 8.0. A multiple-attack method,
52
53 with a high level of multiple attacks, was increasingly suitable to represent the activity mode of
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 alkaline, plant pectin methyl esterase, both at pH 4.5 and at pH 8.0 (Duvetter and Fraeye, 2006).
5
6 **Figure 7** presents the combination arrangement of a pectenic acid of DE (degree of
7
8 esterification) with the alkaline de-polymerization (BeMiller, 1986).
9

10 11 **2.4. Chemical properties**

12
13
14
15 The dissolved pectin undergoes depolymerization in aquatic systems. The greatest stability of
16
17 pectin is at pH 4. Below and above this pH, de-esterification of pectin occurs resulting in its
18
19 decreased stability. De-ionification rate is higher than the rate of depolymerization. The presence
20
21 of solvents, which reduces water activity, reduces the rate of both reactions. Depolymerization
22
23 of solvents, which reduces water activity, reduces the rate of both reactions. Depolymerization
24
25 occurs through the acid catalyst hydrolysis of glycosidic bonds at low pH values. Acid-activated
26
27 hydrolysis is preferentially on L-rhamnopyranosyl glycosidic bonds (BeMiller, 1967). The
28
29 galacturonanglycan chain is formed in hydrolysis of these links, which occur with
30
31 polymerisation of approximately 25 (Powell et al., 1982; Thibault et al., 1993) side chain,
32
33 especially with L-arabinofuranosyl unit. However, if the side catena are attached to
34
35 rhamnogalacturonan sequence (Guillon et al., 1989), the conversion to smooth surface is not
36
37 possible with acid treatment as the depolymerization of L-hamnopyanosyl bonds occurs at pH 5-
38
39 6 (BeMiller, 1967). Beta-eradication reaction of pectin chains, a reaction which is stimulated by
40
41 organic ions, it is the erosion of beta-eradication de-polymerisation reaction, which is only in
42
43 monosaccharide units esterifies by the indigestion of pectin. From 6 to the upper pH values, both
44
45 de-esterification and de-polymerization reaction proceed and there is also a rapid response at
46
47 atmospheric temperature (Schneider and Fritschi, 1936; BeMiller, 1986; Vollmert, 1949;
48
49 Whistler and BeMiller, 1958; Albersheim, 1959; LAUNER and TOMIMATSU, 1961). **Figure 8**
50
51 presents the repeating unit of functional groups; COOH (carboxylic group), ester group and also
52
53 presents amide group (-NH₂) in the frame of pectin chemical structure. All these groups are
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 attached in pectin chain (Sriamornsak, 2003). **Figure 9** demonstrates the schematic presentation
5
6 of rhamnose insertion cause occurrence of galacturonic acid (GA) chain, where S represents the
7
8 occurrence of neutral sugar (Sriamornsak, 2002, 2003).
9

10
11 The termination of carboxyl (COOH) group in hydroxyethyl groups has been carried out with
12
13 diborane (Smith and Stephen, 1960). It has also been found with hydroxyethyl and methyl ester
14
15 (Haaland, 1972). Reducing carboxyl groups with water soluble carbodiimides have been easily
16
17 activated (BeMiller, 1986b). When ammonia (BeMiller, 1986) is used to make modified low
18
19 methoxyl pectin from us-pectin, some methyl carboxylate groups are converted to carbon (C)
20
21 group, in which modified pectin is produced. In the presence of amide (-NH₂) group, the
22
23 molecule becomes less hydrophilic, the tendency of pectin gel increases and sensitivity to
24
25 calcium ions decreases (Deuel and Neukom, 1947).
26
27
28
29
30
31

32
33 Generally there are several types of such isomerase that actions on pectin molecules (BeMiller,
34
35 1986). Those enzymes produced by high plants have played an useful role in the reactions,
36
37 resulting in crust in fruits or vegetables, and the textual changes occurring during processing
38
39 (Bourne, 1989). The use of fungal enzyme by the fruit vitality industries increases the clarity of
40
41 the juice. Control of their operation is crucial for formation of pectin. Pectin esteraes induce
42
43 hydrolysis of methyl ester groups and they are usually undesirable for commercial uses
44
45 (McFeeters and Lovdal, 1987). However, some fungal pectinsteraes produce lm-pectins, which
46
47 are similar to that of pectins, which have the ability to gel with bases and acids and de-esterifies
48
49 with sensitivity to calcium ions. Fungal pectinesteraes from *Aspergillus japonicas* is capable to
50
51 exchange high methoxyl (hm) pectin into low methoxyl (lm) pectin able of producing strong gels
52
53 with calcium ions. Pectinesterase quickly changes high methoxyl pectin into low methoxyl
54
55 pectin below gentle situations with no de-polymerization of pectin particles. However, low
56
57
58
59
60
61
62
63
64
65

1
2
3
4 methoxyl pectins formed by pectinesterases (ELM-pectin) have been originated to the appearance
5
6 of weaker gels than those formed via extra techniques due to the non-random sharing of
7
8 methoxyl groups amongst particles of the pectin (Ishi et al., 2006). All act as a beta eradication
9
10 reaction for elevation, such as during base-induced depolymerization. The rate of
11
12 depolymerization is proportional to the degree of esterification (DE) and suggests a requirement
13
14 for a non-certified D-galacturonic acid unit (McFeeters and Lovdal, 1987).
15
16
17
18
19

20 **2.5. Pectin gelation**

21
22
23 Under acceptable circumstances, pectin poly-saccharides are capable of forming the gels,
24
25 irrespective of the useful groups such as amide, methyl, carboxyl, acetyl and hydroxyl exist on
26
27 the polymer. The method of branch establishment is totally dependent upon the class of
28
29 functional group. Although the gel characteristics are resolved via the microscopic arrangements
30
31 of pectin and gel constitutions (Evageliou et al., 2000, 2005). It means the use of pectin can give
32
33 products a formation of contributing network, thereby changing few physical applications and
34
35 chemical strength of (emulsifiers) emulsion-based edible materials. While normally the network
36
37 formation of emulsified oil results in establishment of network (Leroux et al., 2003). Hence, jelly
38
39 inconstancy, in emulsion-based edible material, the non-adsorbed pectin might form crystalline
40
41 polymer material to which oil drops are captured (dispersed).
42
43
44
45
46

47
48 Gelation of pectin arises in alkaline situations through KOH or NaOH in a concentration and
49
50 time dependent approach. Bernhard Wehr et al. suggested that alkaline environment show the
51
52 way to de-methoxylation of pectin and make complete dissociation of carboxyl group units.
53
54 Dissociation of carboxyl group outcome is highest revulsion of the pectin networks which must
55
56 prevent gelation. As gelation happens, it has to be accomplished that K and Na ions neutralize
57
58 the negative charge of pectin. As high concentrations of K or Na ions are essential to make
59
60
61
62
63
64
65

1
2
3
4 gelation, these ions also results in shielding of the carboxyl groups, thus assisting gelation. This
5
6 can also be realized from the study that the Na-pectin gels liquefy in the lead of broad dialysis.
7
8 This marks to a mutual charge neutralization and ionic strength achieved on the mono-valent
9
10 cation-produced gelation of pectin (Bernhard Wehr et al., 2004).
11
12

13 14 **3. Pectin based hydrogels for water purification**

15
16 Different kinds of pectin based hydrogels have been utilized to eliminate pollutants from
17
18 aqueous solution (Chauhan et al., 2007; Fares et al., 2011; Guilherme et al., 2010; Kumar et al.,
19
20 2009; Singha et al., 2017). (**Table 4**). Recently, Singh et al., synthesized interpenetrating
21
22 polymer network super adsorbent (IPNS) pectin-g-(sodium acrylate-co-N-isopropylacrylamide)
23
24 (PC-g-(SA-co-NIPA)) hydrogel, sodium acrylate (SA) as monomer and N,N'-methylene-bis-
25
26 acrylamide as cross-linker (Singha et al., 2017). The synthesized hydrogel was used for the
27
28 adsorption of dyes and metal ions from aqueous solution. Pectin-g-(sodium acrylate-co-N-iso-
29
30 propylacrylamide) hydrogel was synthesized via cross linking of sodiumacrylate (monomer)
31
32 using free radical polymerization reaction. Potassium per-sulfate (PPS) and sodium bisulfite
33
34 (SBS) were used in the reaction as a redox pair initiator under specific nitrogen (N₂) atmosphere
35
36 for the initiation of polymerization reaction (**Figure 10**). The peaks at $2\theta =$
37
38 $12.00^\circ/13.35^\circ/19.38^\circ/25.29^\circ/38.82^\circ/40.60^\circ$ and $23.48^\circ/32.02^\circ$, corresponded to PC and SA-co-
39
40 NIPA (Mishra et al., 2008; Sharma and Ahuja, 2011) respectively (**Figure 11a and inset**). The
41
42 peaks at 25.39, 27.07 and 31.83 corresponded to MB whereas peaks at 22.82, 31.96 and 45.78
43
44 ascribed to MV (**inset of Figure 11a**). The peak at $2\theta = 21.23^\circ$, assigned to IPNS (**Figure 11a**).
45
46 The increase in crystallinity after the dye adsorption was attributed to well order of dye packing
47
48 at surface of IPNS (Singha et al., 2013) (**Figure 11a**). The intensities of metal ions adsorbed
49
50 IPNS hydrogel were increased in the order: Pb (II) < Zn (II) < Cu (II) < Co (II) (**Figure 11b**). The
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 broad spectrum of IPNS–Pb (II) was due to the formation of different geometries (hemi). The
5
6 intense peak of IPNS–Cu (II) was due to lesser number of equal arrangements. As compared to
7
8 sodium acrylate-co-N-isopropyl acrylamide (SA-co-NIPA), interpenetrating polymer network
9
10 superabsorbent (IPNS) showed rougher surface indicating high phase mixing of the polymeric
11
12 chain in IPNS (**Figure 11c, d**). Phase domains of SA-co-NIPA were clearly distinguishable;
13
14 however phase boundaries were missing in case of IPNS due to the high cross-linking of chains.
15
16 Adsorption of M (II), on the decided surface zone of IPNS, was distinguished from the
17
18 predominant characteristics peaks of respectively EDX spectra (**Figure 11i-l**). Among the M(II)
19
20 consumed IPNS, Cu²⁺ were seen to store as greater crystals over the whole IPNS surface (**Figure**
21
22 **11f**), and were also approved from the sharp and intense peak in XRD (**Figure 11b**). In the IPNS-
23
24 Zn²⁺ (**Figure 11g**), the surface population of larger crystals appeared to be generally lower than
25
26 IPNS-Cu²⁺, additionally confirmed from the respective XRD spectra (**Figure 11b**). On the other
27
28 hand, similarly lesser amount of Pb²⁺ crystal of low dimension, at the IPNS surface (**Figure**
29
30 **11h**), overstated the presence of characteristic low intensity XRD peak of IPNS-Pb²⁺ (**Figure**
31
32 **11b**). Interestingly, surface statement of Co²⁺ crystal was the minimum (**Figure 11e**),
33
34 additionally caught from the expansive amorphous nature of the XRD range (**Figure 11b**).
35
36
37
38
39
40
41
42
43

44 In another work, the biosorption and desorption processes were reported for Cd²⁺ ion from
45
46 aqueous solution by using polyacrylic acid grafted pectin hydrogel (Fares et al., 2011). **Figure**
47
48 **12** present the reaction mechanism for polyacrylic acid grafted pectin hydrogel by using acrylic
49
50 acid (AA) as a monomer and glutaraldehyde (GA) as cross-linker. In this mechanism, the pectin
51
52 was treated with ceric ammonium nitrate to facilitate the formation of free radicals onto the
53
54 pectins moiety. Prominently electrostatic interactions were involved in the formation of
55
56 polyacrylic acid grafted pectin hydrogel. **Figure 13** shows the SEM images of pure pectin and
57
58
59
60
61
62
63
64
65

1
2
3
4 polyacrylic acid grafted pectin hydrogel with different magnifications. Pure pectin has been
5
6 found in the form of flakes having highly agglomerated structure. However, upon grafting of
7
8 acrylic acid onto pectin, due to the interaction between pectin and polyacrylic acid moieties, the
9
10 sheet becomes more flattened. Grafting helped in the formation of two dimensional sheet like
11
12 structure having thermally stable pectin moiety (Fares et al., 2011). The process of Cd^{2+} ion
13
14 adsorption was experimentally described on the basis of pseudo 2nd order kinetics. **Figure 14**
15
16 show the $^1\text{H-NMR}$ result for polyacrylic acid grafted pectin hydrogel, the adsorption peaks at $\delta=$
17
18 1.831 and $\delta=3.814$ were due to polyacrylic acid and CH_2 respectively. The CH_2 peak of
19
20 polyacrylic acid was found at δ value of 1.661, 1.831 and 3.841 ppm. However, the COOH
21
22 moiety peak was observed at $\delta=11.75$ ppm and for CH moiety peaks were allocated at $\delta = 2.5$
23
24 and 2.702 ppm. The different position of protons having different environment exhibited
25
26 numerous chemical shift as observed in case of pectin moiety at $\delta= 3.275, 3.589$ and 4.483 ppm.
27
28 Naushad et al. synthesized pectin based anion exchanger material to remove phosphate anions
29
30 from aqueous solution (Naushad et al., 2018). At 55°C , the maximum phosphate uptake was 75 %.
31
32 The occurrence of little intensity peaks indicated semi-crystalline behavior of pectin based
33
34 quaternary amino anion exchanger (Pc-QAE) material (**Figure 15**). **Figure 16** present the SEM
35
36 morphology of pectin based quaternary amino anion exchanger (Pc-QAE) material at different
37
38 magnifying scales which showed the irregular and rough morphology of the fabricated
39
40 pectin based quaternary amino anion exchange material (Naushad et al., 2018).

41
42 Reddy et al. synthesized pH sensitive semi-IPN pectin/poly(acrylamide-co-acrylamidoglycolic
43
44 acid) (PPAA), hydrogel for the adsorption of Cu^{2+} and Ni^{2+} ions (Reddy et al., 2016). The most
45
46 extreme adsorption limits of 203.7 mg g^{-1} and 121.7 mg g^{-1} were accounted for Cu^{2+} and Ni^{2+}
47
48 ions respectively. The FTIR spectra of PPAA semi-IPN hydrogel showed a strong amide band at
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 1,656 cm^{-1} which appeared usual for the C=O broadening vibrations of the amide units. A wide
5
6 and combined band at 3,000– 3,400 cm^{-1} demonstrated –OH and –NH stretching. In case of Cu^{2+}
7
8 stacked hydrogels, the intensities of all peaks winded up higher than PPAA hydrogels and
9
10 furthermore the peak of amide band moved from 1,656 to 1,662 cm^{-1} and peaks at 1,407 cm^{-1}
11
12 moved to 1,413 cm^{-1} . This was due to direct result of incredible measure of Cu^{2+} in the PPAA
13
14 semi-IPN hydrogels. Where as in the case of Ni^{2+} stacked hydrogel, there was a little increment
15
16 in the intensities of peak at 1,407 cm^{-1} , which was due to smaller amount of Ni^{2+} in the PPAA
17
18 semi-IPN hydrogel. This revealed that semi-IPN hydrogels had higher adsorption limit with Cu^{2+}
19
20 ion than the Ni^{2+} ion (Reddy et al., 2016). Lessa et al. prepared pectin/cellulose microfibers
21
22 composite beads for the removal of multi-metals from the aqueous medium (Lessa et al., 2017).
23
24 Reported adsorption capacities of Cd^{2+} , Cu^{2+} and Fe^{2+} ions were 192.3, 88.5 and 98.0 mgg^{-1}
25
26 respectively. Pectin cellulose microfibers (Pec-CF) beads demonstrated an irregular and porous
27
28 surface with high roughness. After the adsorption, the surface of the beads turned out to be less
29
30 rough. Moreover, the vacant spaces at surface reduced with respect to unexposed beads. Such
31
32 more regular and compact morphology resulted because of the interactions between the divalent
33
34 metals and Pec-CF. The acidic treatment in the metal desorption influenced the bead
35
36 morphology. The beads surface indicated high roughness and irregular outlook similar to that
37
38 observed for the unexposed beads. However, regenerated beads demonstrated tiny pores that led
39
40 to decreased adsorption limit. Modified-pectin-co-acrylamide-co-acrylic (M-Pec-co-AAm-co-
41
42 AAc) hydrogel was prepared and utilized for the removal of Cu^{2+} and Pb^{2+} ions from aqueous
43
44 solution (Guilherme et al., 2010). The adsorption tendency of 120 and 130 mg g^{-1} were obtained
45
46 for Cu^{2+} and Pb^{2+} ion respectively. Adsorptions studies were achieved for Cu^{2+} and Pb^{2+} ions
47
48 through batch method with concentration of 0.10-0.05 g ml^{-1} . The minimum swelling was
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 reported at 0.10 g ml^{-1} , while maximum swelling was observed at 0.05 g ml^{-1} (Guilherme et al.,
5
6
7 2010). Kumar et al. performed experiments to remove As (V) ions from the polluted water/water
8
9 using iron (II) loaded pectin based hydrogel. Iron (II) loaded pectin based hydrogel was
10
11 synthesized in the presence of 2-acrylamido-2-methylpropane sulphonic acid (Kumar et al.,
12
13 2009). Three types of pectin and acrylamide supported hydrogels were formed to eliminate
14
15 cationic/anionic ions from the water. The list of synthesized hydrogels (Chauhan et al., 2007): (i)
16
17 pectin-cl-poly-acrylamide hydrogel, (ii) pectin-cl-poly-N-isopropyl-acrylamide hydrogel and (iii)
18
19 pectin-cl-poly-2-acrylamido-2-methyl-1-propane-sulfonic hydrogel. These synthesized hydrogels
20
21 were utilized to eliminate Cr^{6+} , Cu^{2+} and Fe^{2+} ions from the waste water or water. These
22
23 hydrogels were reported with excellent sorption result for Cr^{6+} , Cu^{2+} and Fe^{2+} ions (Chauhan et
24
25 al., 2007).
26
27
28
29
30

31
32 At present, waste water is one of the most significant challenge that we are facing in our society.
33
34 Sustainable and low-cost contribution of clean water to the society is essential for universal
35
36 prosperity and health. In this direction, adsorption related skills and expertise will most probably
37
38 play an essential role in water remediation due to both cost-effectiveness and energy-efficiency.
39
40 To accomplish this, pectin based hydrogels are the most proficient alternatives to the foreseeable
41
42 sorbents for eliminating main contaminants from waste water; like dyes, pesticides and heavy
43
44 metal ions etc from water. A new opportunity can be opened for cracking the environmental
45
46 harms through the natural polymer based hydrogels for heavy-metal and dye adsorption to
47
48 preserve collective sustainable improvement. The future of pectin based hydrogels in water
49
50 remediation is bright, however it needs the mutual efforts of both non-government and
51
52 government regions to expand some sustainable and scale-up modern approaches to supply clean
53
54 water to the society. There are numerous requirements of pectin based hydrogels for water
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 treatment: (i) new categories of pectin based hydrogels with cheaper raw materials; (ii)
5
6 improving the mechanical properties of pectin based hydrogels and (iii) functionalization of
7
8 pectin based hydrogels to synthesise through ecologically approaches.
9

10
11 To summarize, in spite of significant interest in pectin-based hydrogels, the current technologies
12
13 available for their efficient use are quite limited. So research community around the globe should
14
15 explore a number of innovative strategies for the effective and efficient use of pectin based
16
17 hydrogels for water treatment.
18
19

20 21 22 **4. Conclusion and future directions** 23

24
25 Naturally occurring polymers are of essential significance amid which pectin occupies different
26
27 arrangement for its effortless accessibility, non-hazardous and eco-friendly nature. Pectin and its
28
29 compounds are prepared with various chemical and physical properties. Pectin attains its
30
31 complete thickness even in cold water different from other polymers that need constant hot water
32
33 treatment for accomplishing the similar thickness. It can be mixed together with other polymers
34
35 like karaya gum, gelatin, xanthan gum and other cellulosic polymers to attain synergistic
36
37 thickness product. The increasing acceptance of this polymer is supported by its non-poisonous
38
39 and ecological nature. The methods of forming pectin-based materials for different kinds of
40
41 applications and number of published articles with characterization results are constantly
42
43 increasing. In case of pectin, the number of published articles on natural bio-polymers is high,
44
45 however, there is limited work done on usage of pectin based hydrogels for water purification.
46
47 There are many reasons for this; as it has been found according to its non-poisoning and low
48
49 cost, it gives different gelling capacities due to differential size and differentiation in chemical
50
51 structure from different sources. To increase interest in pectin based content, technology can be
52
53 improved for the product of pectin. The mechanical strength and the adsorption efficiency of
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 pectin based hydrogels can be upgraded via integrating inorganic fillers into the matrix. Pectin
5
6 and pectin based materials have a very high potential to play an important role in different fields.
7
8 In pharmaceuticals, it can be used as emulsifying, suspending, stabilizing and binding agent for
9
10 predictable dose form. In tablet or capsule dose form, it can be used as a disintegrating and
11
12 potential binding agent.
13
14

15 16 17 18 19 **5. References**

- 20
21 Adesanya, K., Vanderleyden, E., Embrechts, A., Glazer, P., Mendes, E., Dubruel, P., 2014.
22
23 Properties of electrically responsive hydrogels as a potential dynamic tool for biomedical
24
25 applications. *J. Appl. Polym. Sci* 131.
26
27
28 Adsul, M., Tuli, D.K., Annamalai, P.K., Depan, D., Shankar, S., 2016. Polymers from biomass:
29
30 characterization, modification, degradation, and applications. *Int. J. Polym. Sci.* 2016.
31
32
33 Ahlawat, S., Battan, B., Dhiman, S.S., Sharma, J., Mandhan, R.P., 2007. Production of
34
35 thermostable pectinase and xylanase for their potential application in bleaching of kraft
36
37 pulp. *J. Ind. Microbiol. Biotechnol.* 34, 763–770.
38
39
40 Ahmed, E.M., 2015. Hydrogel: Preparation, characterization, and applications: A review. *J. Adv.*
41
42 *Res.* 6, 105–121.
43
44
45 Albersheim, P., 1959. Instability of pectin in neutral solutions.
46
47 *Biochem. Biophys. Res. Commun.* 1, 253–256.
48
49
50 Ali, I., Asim, M., Khan, T.A., 2012. Low cost adsorbents for the removal of organic pollutants
51
52 from wastewater. *J. Environ. Manage.* 113, 170–183.
53
54
55 Amini, A.A., Nair, L.S., 2012. Injectable hydrogels for bone and cartilage repair. *Biomedical*
56
57 *materials* 7, 024105.
58
59
60
61
62
63
64
65

- 1
2
3
4 Appel, E.A., Tibbitt, M.W., Webber, M.J., Mattix, B.A., Veiseh, O., Langer, R., 2015. Self-
5 assembled hydrogels utilizing polymer–nanoparticle interactions. *Nat. Commun.* 6, 6295.
6
7
8
9 Attallah, O.A., Al-Ghobashy, M.A., Nebsen, M., Salem, M.Y., 2017. Adsorptive Removal of
10 Fluoroquinolones from Water by Pectin-Functionalized Magnetic Nanoparticles: Process
11 Optimization Using a Spectrofluorimetric Assay. *ACS Sustain. Chem. Eng.* 5, 133–145.
12
13
14 Baciak, M., Sikorski, Ł., Piotrowicz-Cieślak, A.I., Adomas, B., 2016. Content of biogenic
15 amines in *Lemna minor* (common duckweed) growing in medium contaminated with
16 tetracycline. *Aquat. Toxicol.* 180, 95–102.
17
18
19
20
21
22
23 Bae, J.W., Choi, J.H., Lee, Y., Park, K.D., 2015. Horseradish peroxidase-catalysed in situ-
24 forming hydrogels for tissue-engineering applications.
25
26
27
28
29
30
31
32 Bajpai, A.K., Shukla, S.K., Bhanu, S., Kankane, S., 2008a. Responsive polymers in controlled
33 drugdelivery. *Prog. Polym. Sci.* 33, 1088–1118.
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
- Banerjee, J., Vijayaraghavan, R., Arora, A., MacFarlane, D.R., Patti, A.F., 2016. Lemon juice
based extraction of pectin from mango peels: waste to wealth by sustainable approaches.
ACS Sustainable Chem. Eng. 4, 5915–5920.
- Barrett, D.G., Fullenkamp, D.E., He, L., Holten-Andersen, N., Lee, K.Y.C., Messersmith, P.B.,
2013. pH-Based Regulation of Hydrogel Mechanical Properties Through Mussel-Inspired
Chemistry and Processing. *Adv. Funct. Mater.* 23, 1111–1119.
- BeMiller, J.N., 1986a. An Introduction to Pectins: Structure and Properties, in: Fishman, M.L.,
Jen, J.J. (Eds.), *Chemistry and Function of Pectins*. ACS, Washington, DC, pp. 2–12.
- BeMiller, J.N., 1967. Acid-catalyzed hydrolysis of glycosides. *Adv. Carbohydr. Chem.* 22, 25–
108.

- 1
2
3
4 Ben-Nissan, B., Choi, A.H., Macha, I.J., Cazalbou, S., 2016. Sol-gel Nanocoatings of
5
6 Bioceramics. *Handbook of Bioceramics and Biocomposites* 735–756.
7
8
9 Bernhard Wehr, J., Menzies, N.W., Blamey, F.P.C., 2004. Alkali hydroxide-induced gelation of
10
11 pectin. *Food Hydrocolloids* 18, 375–378.
12
13
14 Bian, H., Wei, L., Lin, C., Ma, Q., Dai, H., Zhu, J.Y., 2018. Lignin-Containing Cellulose
15
16 Nanofibril-Reinforced Polyvinyl Alcohol Hydrogels. *ACS Sustain. Chem. Eng.* 6, 4821–
17
18 4828.
19
20
21 Biswas, B.K., Inoue, K., Ghimire, K.N., Ohta, S., Harada, H., Ohto, K., Kawakita, H., 2007. The
22
23 adsorption of phosphate from an aquatic environment using metal-loaded orange waste. *J.*
24
25 *Colloid Interface Sci.* 312, 214–223.
26
27
28 Bourne, M.C., 1989. Applications of chemical kinetic theory to the rate of thermal softening of
29
30 vegetable tissue. ACS Publications.
31
32
33 Brigand, G., Denis, A., Grall, M., Lecacheux, D., 1990. Insight into the structure of pectin by
34
35 high performance chromatographic methods. *Carbohydr. Polym.* 12, 61–77.
36
37
38 Buchholz, F.L., Graham, A.T., 1998. Modern superabsorbent polymer technology. John Wiley &
39
40 Sons 279.
41
42
43 Caffall, K.H., Mohnen, D., 2009. The structure, function, and biosynthesis of plant cell wall
44
45 pectic polysaccharides. *Carbohydr. Res.* 344, 1879–1900.
46
47
48 Chauhan, G.S., Kumari, A., Sharma, R., 2007. Pectin and acrylamide based hydrogels for
49
50 environment management technologies: Synthesis, characterization, and metal ions
51
52 sorption. *J. Appl. Polym. Sci.* 106, 2158–2168.
53
54
55
56
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Chenite, A., Chaput, C., Wang, D., Combes, C., Buschmann, M.D., Hoemann, C.D., Leroux,
5
6 J.C., Atkinson, B.L., Binette, F., Selmani, A., 2000. Novel injectable neutral solutions of
7
8 chitosan form biodegradable gels in situ. *Biomaterials* 21, 2155–2161.
9
10
11 Dai, H., Huang, H., 2016. Modified pineapple peel cellulose hydrogels embedded with sepia ink
12
13 for effective removal of methylene blue. *Carbohydr. Polym.* 148, 1–10.
14
15
16 Deuel, H., Neukom, H., 1947. Derivatives of pectic acid as models of proteins. *Nature* 159, 882–
17
18 882.
19
20
21 Dhakal, R.P., Ghimire, K.N., Inoue, K., Yano, M., Makino, K., 2005. Acidic polysaccharide gels
22
23 for selective adsorption of lead (II) ion. *Sep. Purif. Technol.* 42, 219–225.
24
25
26 Dudu, T.E., Sahiner, M., Alpaslan, D., Demirci, S., Aktas, N., 2015. Removal of As (V), Cr (III)
27
28 and Cr (VI) from aqueous environments by poly (acrylonitril-co-acrylamidopropyl-
29
30 trimethyl ammonium chloride)-based hydrogels. *J. Environ. Manage.* 161, 243–251.
31
32
33 Duvetter, T., Fraeye, I., 2006. Mode of de-esterification of alkaline and acidic pectin methyl
34
35 esterases at different pH conditions. *J. Agric. Food Chem.* 54, 7825–7831.
36
37
38 Evageliou, V., Ptitchkina, N.M., Morris, E.R., 2005. Solution viscosity and structural
39
40 modification of pumpkin biopectin. *Food Hydrocolloids* 19, 1032–1036.
41
42
43 Evageliou, V., Richardson, R.K., Morris, E.R., 2000. Effect of pH, sugar type and thermal
44
45 annealing on high-methoxy pectin gels. *Carbohydr. Polym.* 42, 245–259.
46
47
48 Fang, R., He, W., Xue, H., Chen, W., 2016. Synthesis and characterization of a high-capacity
49
50 cationic hydrogel adsorbent and its application in the removal of Acid Black 1 from
51
52 aqueous solution. *React. Funct. Polym.* 102, 1–10.
53
54
55
56
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Fares, M.M., Tahboub, Y.R., Khatatbeh, S.T., Abul-Haija, Y.M., 2011. Eco-friendly, vascular
5 shape and interpenetrating poly (acrylic acid) grafted pectin hydrogels; biosorption and
6 desorption investigations. *J. Polym. Environ.* 19, 431.
7
8
9
10
11 Ferry, J.D., 1980. *Viscoelastic properties of polymers*. John Wiley & Sons.
12
13
14 Fidalgo, A., Ciriminna, R., Carnaroglio, D., Tamburino, A., Cravotto, G., Grillo, G., Ilharco,
15 L.M., Pagliaro, M., 2016. Eco-Friendly Extraction of Pectin and Essential Oils from
16 Orange and Lemon Peels. *ACS Sustain. Chem. Eng.* 4, 2243–2251.
17
18
19
20
21 Ghimire, K.N., Inoue, K., Makino, K., Miyajima, T., 2002. Adsorptive removal of arsenic using
22 orange juice residue. *Sep. Sci. Technol.* 37, 2785–2799.
23
24
25
26 Grierson, D., Maunders, M.J., Slater, A., Ray, J., Bird, C.R., Schuch, W., Holdsworth, M.J.,
27 Tucker, G.A., Knapp, J.E., 1986. Gene expression during tomato ripening. *Phil. Trans. R.*
28 *Soc. Lond. B* 314, 399–410.
29
30
31
32
33
34 Guilherme, M.R., Reis, A.V., Paulino, A.T., Moia, T.A., Mattoso, L.H., Tambourgi, E.B., 2010.
35 Pectin-based polymer hydrogel as a carrier for release of agricultural nutrients and
36 removal of heavy metals from wastewater. *J. Appl. Polym. Sci.* 117, 3146–3154.
37
38
39
40
41 Guillon, F., Thibault, J.-F., Rombouts, F.M., Voragen, A.G., Pilnik, W., 1989. Enzymic
42 hydrolysis of the “hairy” fragments of sugar-beet pectins. *Carbohydr. Res.* 190, 97–108.
43
44
45
46 Gulrez, S.K.H., Al-Assaf, S., Phillips, G.O., 2011. *Hydrogels: Methods of Preparation,*
47 *Characterisation and Applications.*
48
49
50
51 Haaland, E., 1972. Studies on pectins from the leaves of *Tussilago farfara* L. *Acta Chem Scand.*
52 26, 2322–8.
53
54
55
56
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Hao, Q., Chen, T., Wang, R., Feng, J., Chen, D., Yao, W., 2018. A separation-free
5
6 polyacrylamide/bentonite/graphitic carbon nitride hydrogel with excellent performance in
7
8 water treatment. *J. Cleaner Prod.* 197, 1222–1230.
9
10
11 Hogan, M.C., 2010. Water Pollution. *Encyclopedia of Earth*. Eed. Mark McGinley; ed. Chief C.
12
13 Cleveland. National Council on Science and the Environment, Washington, DC.
14
15
16 Huang, G., Gao, J., Hu, Z., John, J., Ponder, B., Moro, D., 2004. Controlled drug release from
17
18 hydrogel nanoparticle networks. *J. Cleaner Prod.* 94, 303–11.
19
20
21 Huang, Z., Boubriak, I., Osborne, D.J., Dong, M., Gutterman, Y., 2007. Possible role of pectin-
22
23 containing mucilage and dew in repairing embryo DNA of seeds adapted to desert
24
25 conditions. *National Council on Science and the Environment* 101, 277–283.
26
27
28 Ishi, S., Kiho, K., Sugiyama, S., Sugimoto, H., 2006. Low-methoxyl pectin prepared by
29
30 pectinesterase from *Aspergillus japonicus*. *J. Food Sci.* 22, 611–614.
31
32
33 Jagur-Grodzinski, J., 2010. Polymeric gels and hydrogels for biomedical and pharmaceutical
34
35 applications. *Polym. Adv. Technol.* 21, 27–47.
36
37
38 Ji, H., Song, X., Shi, Z., Tang, C., Xiong, L., Zhao, W., Zhao, C., 2018. Reinforced-Concrete
39
40 Structured Hydrogel Microspheres with Ultrahigh Mechanical Strength, Restricted Water
41
42 Uptake, and Superior Adsorption Capacity. *ACS Sustainable Chem. Eng.* 6, 5950–5958.
43
44
45 Kaveeshwar, A.R., Sanders, M., Ponnusamy, S.K., Depan, D., Subramaniam, R., 2018. Chitosan
46
47 as a biosorbent for adsorption of iron (II) from fracking wastewater. *Polym. Adv.*
48
49 *Technol.* 29, 961–969.
50
51
52
53 Khan, S., Ullah, K., Rehman, N., 2016. Insight into hydrogels. *Designed Monomers and*
54
55 *Polymers.* 19, 456–78.
56
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Kim, S.W., Bae, Y.H., Okano, T., 1992. Hydrogels: swelling, drug loading, and release.
5
6 Pharmaceutical research 9, 283–290.
7
8
9 Kirby, A.R., MacDougall, A.J., Morris, V.J., 2006. Sugar beet pectin–protein complexes. Food
10
11 Biophysics 1, 51.
12
13
14 Kumar, R., Kumar, A., Chauhan, K., Gupta, R., Ahn, J.-H., Chauhan, G.S., 2009. Removal of As
15
16 (V) from water by pectin based active hydrogels following geochemical approach.
17
18 Bioresource Technology 100, 1474–1477.
19
20
21 LAUNER, H.F., TOMIMATSU, Y., 1961. Alkali Sensitivity of Polysaccharides: Periodate
22
23 Starches, Periodate Dextran and a Polygalacturonide¹. The Journal of Organic Chemistry
24
25 26, 541–545.
26
27
28 Laurent, M.A., Boulenguer, P., 2003. Stabilization mechanism of acid dairy drinks (ADD)
29
30 induced by pectin. Food Hydrocolloids 17, 445–454.
31
32
33 Leroux, J., Langendorff, V., Schick, G., Vaishnav, V., Mazoyer, J., 2003. Emulsion stabilizing
34
35 properties of pectin. Food Hydrocolloids 17, 455–462.
36
37
38 Lessa, E.F., Medina, A.L., Ribeiro, A.S., Fajardo, A.R., 2017. Removal of multi-metals from
39
40 water using reusable pectin/cellulose microfibers composite beads. Arabian Journal of
41
42 Chemistry.
43
44
45 Li, D., Li, Q., Bai, N., Dong, H., Mao, D., 2017. One-step synthesis of cationic hydrogel for
46
47 efficient dye adsorption and its second use for emulsified oil separation. ACS Sustainable
48
49 Chem. Eng. 5, 5598–5607.
50
51
52
53 Li, Y., Huang, G., Zhang, X., Li, B., Chen, Y., Lu, T., Lu, T.J., Xu, F., 2013. Magnetic hydrogels
54
55 and their potential biomedical applications. Adv. Funct. Mater. 23, 660–672.
56
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Li, Y., Liu, C., Tan, Y., Xu, K., Lu, C., Wang, P., 2014. In situ hydrogel constructed by starch-
5 based nanoparticles via a Schiff base reaction. *Carbohydr. Polym.* 110, 87–94.
6
7
8
9 Lindinger, W., Taucher, J., Jordan, A., Hansel, A., Vogel, W., 1997. Endogenous production of
10 methanol after the consumption of fruit. *Alcoholism: Clinical and Experimental Research*
11 21, 939–943.
12
13
14
15
16 Liu, K., Pan, X., Chen, L., Huang, L., Ni, Y., Liu, J., Cao, S., Wang, H., 2018. Ultrasoft Self-
17 Healing Nanoparticle-Hydrogel Composites with Conductive and Magnetic Properties.
18 *ACS Sustainable Chem. Eng.* 6, 6395–6403.
19
20
21
22
23 Liu, L., Tang, X., Wang, Y., Guo, S., 2011. Smart gelation of chitosan solution in the presence of
24 NaHCO₃ for injectable drug delivery system. *International Journal of Pharmaceutics*
25 414, 6–15.
26
27
28
29
30
31 Lodish, H., Berk, A., Darnell, J., Kaiser, C., Krieger, M., Scott, M., Bretscher, A., Ploegh, H.,
32 Matsudaira, P., 2008. *Molecular cell biology*. Macmillan.
33
34
35
36 McFeeters, R.F., Lovdal, L.A., 1987. Sugar composition of cucumber cell walls during fruit
37 development. *J. Food Sci.* 52, 996–1001.
38
39
40
41 Mesbahi, G., Jamalian, J., Farahnaky, A., 2005. A comparative study on functional properties of
42 beet and citrus pectins in food systems. *Food Hydrocolloids* 19, 731–738.
43
44
45
46 Minzanova, S., Mironov, V., Arkhipova, D., Khabibullina, A., Mironova, L., Zakirova, Y.,
47 Milyukov, V., 2018. Biological Activity and Pharmacological Application of Pectic
48 Polysaccharides: A Review. *Polymers* 10, 1407.
49
50
51
52
53 Mishra, R.K., Datt, M., Banthia, A.K., 2008. Synthesis and characterization of pectin/PVP
54 hydrogel membranes for drug delivery system. *Aaps Pharmscitech* 9, 395–403.
55
56
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Mohnen, D., 2008a. Pectin structure and biosynthesis. *Current Opinion in Plant Biology*,
5
6
7 Physiology and Metabolism - Edited by Markus Pauly and Kenneth Keegstra 11, 266–
8
9 277.
- 10
11 Mohnen, D., 2008b. Pectin structure and biosynthesis. *Curr. Opin. Plant Biol.* 11, 266–277.
- 12
13
14 Naushad, M., Sharma, G., Kumar, A., Sharma, S., Ghfar, A.A., Bhatnagar, A., Stadler, F.J.,
15
16 Khan, M.R., 2018. Efficient removal of toxic phosphate anions from aqueous
17
18 environment using pectin based quaternary amino anion exchanger. *Int. J. Biol.*
19
20 *Macromol.* 106, 1–10.
- 21
22
23
24 Ovodov, Y.S., 2009. Current views on pectin substances. *Russ. J. Bioorg. Chem.* 35, 269.
- 25
26
27 Pakdel, P.M., Peighamardoust, S.J., 2018. A review on acrylic based hydrogels and their
28
29 applications in wastewater treatment. *J. Environ. Manage.* 217, 123–143.
- 30
31
32 Pakulska, M.M., Ballios, B.G., Shoichet, M.S., 2012. Injectable hydrogels for central nervous
33
34 system therapy. *Biomedical materials* 7, 024101.
- 35
36
37 Parisi-Amon, A., Mulyasmita, W., Chung, C., Heilshorn, S.C., 2013. Protein-Engineered
38
39 Injectable Hydrogel to Improve Retention of Transplanted Adipose-Derived Stem Cells.
40
41 *Adv. Healthcare Mater.* 2, 428–432.
- 42
43
44 Pedrolli, D.B., Monteiro, A.C., Gomes, E., Carmona, E.C., 2009. Pectin and pectinases:
45
46 production, characterization and industrial application of microbial pectinolytic enzymes.
47
48 *Open Biotechnol. J.* 9–18.
- 49
50
51 Peppas, N., Khare, A., 1993. Preparation, structure and diffusional behavior of hydrogels in
52
53 controlled release. *Adv. Drug Delivery Rev.* 11, 1–35.
- 54
55
56 Peppas, N.A., 2010. *Biomedical applications of hydrogels handbook*. Springer Science &
57
58 Business Media.

- 1
2
3
4 Pereira, A.S., Daniel-da-Silva, A.L., Trindade, T., 2011. From Nanoparticles to Nanocomposites:
5
6 a Brief Overview. *Nanocomposite Particles for Bio-Applications: Materials and Bio-*
7
8 *Interfaces* 1.
9
- 10
11 Plaschina, I.G., Braudo, E.E., Tolstoguzov, V.B., 1978. Circular-dichroism studies of pectin
12
13 solutions. *Carbohydr. Res.* 60, 1–8.
14
- 15
16 Powell, D.A., Morris, E.R., Gidley, M.J., Rees, D.A., 1982. Conformations and interactions of
17
18 pectins: II. Influence of residue sequence on chain association in calcium pectate gels. *J.*
19
20 *Mol. Biol.* 155, 517–531.
21
22
- 23
24 Raizada, P., Kumari, J., Shandilya, P., Dhiman, R., Singh, V.P., Singh, P., 2017. Magnetically
25
26 retrievable Bi₂WO₆/Fe₃O₄ immobilized on graphene sand composite for
27
28 investigation of photocatalytic mineralization of oxytetracycline and ampicillin. *Process*
29
30 *Saf. Environ. Prot.* 106, 104–116.
31
32
- 33
34 Reddy, N.S., Rao, K.M., Vani, T.J.S., Rao, K.S.V.K., Lee, Y.I., 2016. Pectin/poly(acrylamide-
35
36 co-acrylamidoglycolic acid) pH sensitive semi-IPN hydrogels: selective removal of Cu²⁺
37
38 and Ni²⁺, modeling, and kinetic studies. *Desalin. Water Treat.* 57, 6503–6514.
39
40
- 41
42 Ren, K., He, C., Cheng, Y., Li, G., Chen, X., 2014. Injectable enzymatically crosslinked
43
44 hydrogels based on a poly (l-glutamic acid) graft copolymer. *Polym. Chem.* 5, 5069–
45
46 5076.
47
- 48
49 Ridley, B.L., O’Neill, M.A., Mohnen, D., 2001a. Pectins: structure, biosynthesis, and
50
51 oligogalacturonide-related signaling. *Phytochemistry* 57, 929–967.
52
- 53
54 Rosiak, J.M., Yoshii, F., 1999. Hydrogels and their medical applications. *Nuclear Instruments*
55
56 *and Methods in Physics Research Section B: Beam Interactions with Materials and*
57
58 *Atoms* 151, 56–64.
59
60
61
62
63
64
65

- 1
2
3
4 Satarkar, N.S., Hilt, J.Z., 2008. Magnetic hydrogel nanocomposites for remote controlled
5
6 pulsatile drug release. *J. Controlled Release* 130, 246–251.
7
8
9 Schneider, G., Fritschi, U., 1936. Esterification of pectin substances. III. The molecular
10
11 magnitude of pectin substances. *Ber.* 69, 2537–2543.
12
13
14 Sepehri, A., Sarrafzadeh, M.-H., 2018. Effect of nitrifiers community on fouling mitigation and
15
16 nitrification efficiency in a membrane bioreactor. *Chem. Eng. Process.* 128, 10–18.
17
18
19 Shahmirzadi, M.A.A., Hosseini, S.S., Luo, J., Ortiz, I., 2018. Significance, evolution and recent
20
21 advances in adsorption technology, materials and processes for desalination, water
22
23 softening and salt removal. *J. Environ. Manage.* 215, 324–344.
24
25
26 Sharma, R., Ahuja, M., 2011. Thiolated pectin: Synthesis, characterization and evaluation as a
27
28 mucoadhesive polymer. *Carbohydr. Polym.* 85, 658–663.
29
30
31 Shin, M.K., Spinks, G.M., Shin, S.R., Kim, S.I., Kim, S.J., 2009a. Nanocomposite hydrogel with
32
33 high toughness for bioactuators. *Advanced Materials* 21, 1712–1715.
34
35
36 Shin, M.K., Spinks, G.M., Shin, S.R., Kim, S.I., Kim, S.J., 2009b. Artificial Muscles:
37
38 Nanocomposite Hydrogel with High Toughness for Bioactuators (*Adv. Mater.* 17/2009).
39
40 *Adv. Mater.* 21.
41
42
43 Singh, R., Singh, D., 2012. Radiation synthesis of PVP/alginate hydrogel containing nanosilver
44
45 as wound dressing. *Journal of Materials Science:*
46
47 *Mater. Med.* 23, 2649–2658.
48
49
50
51 Singha, N.R., Das, P., Ray, S.K., 2013. Recovery of pyridine from water by pervaporation using
52
53 filled and crosslinked EPDM membranes. *Ind. Eng. Chem.* 19, 2034–2045.
54
55
56 Singha, N.R., Karmakar, M., Mahapatra, M., Mondal, H., Dutta, A., Roy, C., Chattopadhyay,
57
58 P.K., 2017. Systematic synthesis of pectin-g-(sodium acrylate-co-N-isopropylacrylamide)
59
60
61
62
63
64
65

- 1
2
3
4 interpenetrating polymer network for superadsorption of dyes/M (ii): determination of
5
6 physicochemical changes in loaded hydrogels. *Polym. Chem.* 8, 3211–3237.
7
8
9 Smith, F., Stephen, A.M., 1960. Diborane reduction of carboxyl groups in carbohydrates.
10
11 Tetrahedron Letters 1, 17–23.
12
13
14 Sriamornsak, P., 2003. Chemistry of pectin and its pharmaceutical uses: A review. *Silpakorn*
15
16 *University International Journal* 3, 206–228.
17
18
19 Sriamornsak, P., 2002. Analysis of selected physico-chemical properties of pectin and alginate
20
21 gels intended for drug delivery. Charles Sturt University.
22
23
24 Steed, J.W., 2011. Supramolecular gel chemistry: developments over the last decade. *Chemical*
25
26 *Communications* 47, 1379–1383.
27
28
29 Teshager, A.D., Gassman, P.W., Secchi, S., Schoof, J.T., Misgna, G., 2016. Modeling
30
31 agricultural watersheds with the soil and water assessment tool (swat): Calibration and
32
33 validation with a novel procedure for spatially explicit hrus. *Environ.Manage.* 57, 894–
34
35 911.
36
37
38 Thakur, M.K., Thakur, V.K., Gupta, R.K., Pappu, A., 2015. Synthesis and applications of
39
40 biodegradable soy based graft copolymers: a review. *ACS Sustainable Chem. Eng.* 4, 1–
41
42 17.
43
44
45 Thakur, N., Sharma, B., Bishnoi, S., MISHRA, S., Nayak, D., Kumar, A., Sarma, T.K., 2018a.
46
47 Multifunctional Inosine Monophosphate Coordinated Metal-Organic Hydrogel: Multi-
48
49 stimuli Responsiveness, Self-healing Properties and Separation of Water from Organic
50
51 Solvents. *ACS Sustainable Chem. Eng.*
52
53
54
55 Thakur, S., Arotiba, O.A., n.d. Synthesis, swelling and adsorption studies of a pH-responsive
56
57 sodium alginate–poly (acrylic acid) superabsorbent hydrogel. *Polym. Bull.* 1–20.
58
59
60
61
62
63
64
65

- 1
2
3
4 Thakur, S., Govender, P.P., Mamo, M.A., Tamulevicius, S., Mishra, Y.K., Thakur, V.K., 2017a.
5
6 Progress in lignin hydrogels and nanocomposites for water purification: Future
7
8 perspectives. *Vacuum* 146, 342–355.
9
10
11 Thakur, S., Pandey, S., Arotiba, O.A., 2017b. Sol-gel derived xanthan gum/silica
12
13 nanocomposite—a highly efficient cationic dyes adsorbent in aqueous system. *Int. J.*
14
15 *Biol. Macromol.* 103, 596–604.
16
17
18 Thakur, S., Sharma, B., Verma, A., Chaudhary, J., Tamulevicius, S., Thakur, V.K., 2018b.
19
20 Recent approaches in guar gum hydrogel synthesis for water purification. *Int. J. Polym.*
21
22 *Anal. Ch.* 23, 621–632.
23
24
25 Thakur, S., Sharma, B., Verma, A., Chaudhary, J., Tamulevicius, S., Thakur, V.K., 2018c.
26
27 Recent progress in sodium alginate based sustainable hydrogels for environmental
28
29 applications. *J. Cleaner Prod.* 198, 143–159.
30
31
32 Thakur, V.K., Thakur, M.K., 2014. Recent trends in hydrogels based on psyllium
33
34 polysaccharide: a review. *J. Cleaner Prod.* 82, 1–15.
35
36
37 Thakur, V.K., Voicu, S.I., 2016. Recent advances in cellulose and chitosan based membranes for
38
39 water purification: a concise review. *Carbohydr. Polym.* 146, 148–165.
40
41
42 Thibault, J.-F., Renard, C.M., Axelos, M.A., Roger, P., Crépeau, M.-J., 1993. Studies of the
43
44 length of homogalacturonic regions in pectins by acid hydrolysis. *Carbohydr. Res.* 238,
45
46 271–286.
47
48
49 Tous, E., Purcell, B., Ifkovits, J.L., Burdick, J.A., 2011. Injectable acellular hydrogels for cardiac
50
51 repair. *Journal of Cardiovascular Translational Research* 4, 528–542.
52
53
54 Valdés García, A., Burgos Bolufer, N., Jiménez, A., Garrigós Selva, M. del C., 2015. Natural
55
56 pectin polysaccharides as edible coatings. *Coatings* 5, 865–86.
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Vollmert, B., 1949. UBER DEN ALKALISCHEN PEKTIN-ABBAU, in: ANGEWANDTE
5
6 CHEMIE. VCH PUBLISHERS INC 303 NW 12TH AVE, DEERFIELD BEACH, FL
7
8 33442-1788, pp. 329–329.
9
- 10
11 Wach, R.A., Mitomo, H., Yoshii, F., Kume, T., 2002. Hydrogel of Biodegradable Cellulose
12
13 Derivatives Radiation-Induced Crosslinking of HPC. *El* 1-T JJ ffi YE R 72*.
14
- 15
16 Wandrey, C., Bartkowiak, A., Harding, S.E., 2010. Materials for encapsulation, in:
17
18 Encapsulation Technologies for Active Food Ingredients and Food Processing. Springer,
19
20 pp. 31–100.
21
22
- 23
24 Wang, Q., Wilfong, W.C., Kail, B.W., Yu, Y., Gray, M.L., 2017. Novel Polyethylenimine–
25
26 Acrylamide/SiO₂ Hybrid Hydrogel Sorbent for Rare-Earth-Element Recycling from
27
28 Aqueous Sources. *ACS Sustainable Chem. Eng.* 5, 10947–10958.
29
30
- 31
32 Whistler, R.L., BeMiller, J.N., 1958. Alkaline degradation of polysaccharides. *Adv. Carbohydr.*
33
34 *Chem.* 13, 289–329.
35
- 36
37 Wichterle, O., Lim, D., 1960. Hydrophilic gels for biological use. *Nature* 185, 117–118.
38
- 39
40 Xia, L.-W., Xie, R., Ju, X.-J., Wang, W., Chen, Q., Chu, L.-Y., 2013. Nano-structured smart
41
42 hydrogels with rapid response and high elasticity. *Nat. Commun.* 4.
43
- 44
45 Yapo, B.M., 2011. Pectic substances: From simple pectic polysaccharides to complex pectins—
46
47 A new hypothetical model. *Carbohydr. Polym.* 86, 373–385.
48
- 49
50 Yapo, B.M., 2010. Improvement of the compositional quality of monocot pectin extracts
51
52 contaminated with glucuronic acid-containing components using a step-wise purification
53
54 procedure. *Food Bioprod. Process.* 88, 283–290.
55
56
57
58
59
60
61
62
63
64
65

- 1
2
3
4 Yapo, B.M., 2009. Pineapple and banana pectins comprise fewer homogalacturonan building
5
6 blocks with a smaller degree of polymerization as compared with yellow passion fruit
7
8 and lemon pectins: Implication for gelling properties. *Biomacromolecules* 10, 717–721.
9
10
11 Yoshimura, T., Sengoku, K., Fujioka, R., 2005. Pectin-based superabsorbent hydrogels
12
13 crosslinked by some chemicals: synthesis and characterization. *Polym. Bull.* 55, 123–9.
14
15
16 Zhang, H., Zhang, F., Wu, J., 2013. Physically crosslinked hydrogels from polysaccharides
17
18 prepared by freeze–thaw technique. *React. Funct. Polym.* 73, 923–928.
19
20
21 Zhao, L.Z., Zhou, C.H., Wang, J., Tong, D.S., Yu, W.H., Wang, H., 2015a. Recent advances in
22
23 clay mineral-containing nanocomposite hydrogels. *Soft Matter* 11, 9229–9246.
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65




Figure 1. Applications of biopolymer based hydrogels.




Figure 2. Different paths to synthesis of hydrogels.




Figure 3. Extraction of pectin from bio-waste (fruits peels like orange, apple, mango etc.) materials.

Plant Cell Wall Structure




Figure 4. Pictorial presentation of simple structure of the plants cell wall. Adopted from (Lodish et al., 2008).




Figure 5. Four different pectic poly-saccharides homo-galacturonan, xylogalacturonan, rhamnagalacturonan I and rhamnagalacturonan II. Adopted from (Mohnen, 2008a).




Figure 6. Three different kinds of pectic polysaccharides on the bases of D-galacturonic acid. Adopted from (Valdés García et al., 2015).




Figure 7. Arrangement of a pectenic acid of DE (degree of esterification) with the alkaline de-polymerization. Adopted from (BeMiller, 1986a).




Figure 8. (a) Repeating unit of functional group in the form of pectin chemical structure, occurrence of (b) carboxylic group, (c) ester group and (d) amide group in pectin chain.

Adopted from (Sriamornsak, 2003).




Figure 9. Rhamnose insertion cause occurrence of galacturonic acid chain (where nS shows the occurrence of neutral sugar) Adopted from (Sriamornsak, 2003, 2002).




Figure 10. Schematic reaction procedure for synthesis of pectin-g-(sodium acrylate-co-N-iso-propyl acrylamide) hydrogel (Singha et al., 2017). Reprinted with permission from (Singha et al., 2017). Copyright 2017 Royal Society of Chemistry.




Figure 11. XRD spectra of (a) copolymer, interpenetrating polymer network superadsorbent (IPNS) and methylene blue/methyl violet loaded IPNS, (inset of a) pectin, methylene blue(MB) and methyl violet(MV), (b) Co(II), Cu(II), Zn(II) and Pb(II) loaded IPNS and SEM images of (c) sodium acrylate-co-N-iso-propylacrylamide (SA-co-NIPA), (d) interpenetrating polymer network superadsorbent (IPNS) and SEM/respective EDX of (e)/(i) Co(II), (f)/(j) Cu(II), (g)/(k) Zn(II) and (h)/(l) Pb(II) loaded IPNS (Singha et al., 2017). Reprinted with permission from(Singha et al., 2017). Copyright 2017 Royal Society of Chemistry.




Figure 12. Synthesis of acrylic grafted pectin hydrogel by using acrylic acid (AA, 98%) as a monomer and glutar-aldehyde (GA) as a cross-linker (Fares et al., 2011). Reprinted with permission from (Fares et al., 2011). Copyright 2011 Springer.




Figure 13. SEM morphology of (a) pure pectin hydrogel and (b, c, d and e) acrylic grafted pectin hydrogel (Fares et al., 2011). Reprinted with permission from (Fares et al., 2011). Copyright 2011 Springer.




Figure 14. $^1\text{H-NMR}$ for acrylic grafted pectin hydrogel (Fares et al., 2011). Reprinted with permission from (Fares et al., 2011). Copyright 2011 Springer.




Figure 15. XRD of pectin based quaternary amino anion exchanger (Pc-QAE) material (Naushad et al., 2018). Reprinted with permission from (Naushad et al., 2018). Copyright 2018 Elsevier.




Figure 16. SEM images of pectin based quaternary amino anion exchanger (Pc-QAE) material at different magnification (Naushad et al., 2018). Reprinted with permission from (Naushad et al., 2018). Copyright 2018 Elsevier.

Table 1. Sol–gel (hydrosol–hydrogel) transition in chemical/organic and physical hydrogels.

Physical hydrogels	Chemical hydrogels
<ul style="list-style-type: none">• Hydrophobic relationship: iso-propyl units in poly (N-isopropyl acrylamide); methyl units in methyl cellulose; propylene oxide obstructs in (ethylene oxide)–(propylene oxide)–(ethylene oxide) terpolymers.• Ion–polymer complexation: acrylic-based hydrogel activated with Ca, Al, Fe; Na-alginate activated with Cl and Al; polyvinyl alcohol activated with borax.• Polymer–polymer complex formation: chitosan & alginate; gelatine& gum Arabic.• Chain summation; hydro-colloids heat treatment in water.• Hydrogen bonding: polyvinyl alcohol/polyvinyl alcohol chains bond; polyacrylic acid/polyacrylamide chains bond.	<ul style="list-style-type: none">• Covalent cross-linking via olefinic cross-linkers having unsaturated bonds or sensitive functional groups.• Simultaneous polymerization & cross-linking: acrylic acid cross-linked via methylene; bis-acrylamide ethylene via glycol di-acrylate, ethylene glycol via di-methacrylate, polyethylene glycol via di-methacrylate.• Post-polymerization chemical cross-linking: Acrylic-based hydrogel, cross-linked via glycerin; glutaraldehyde cross-linked via gelatin; polyvinyl alcohol crosslinked via an aldehyde.

Table 2. Hydrogels responsive to alteration in environmental factors.

Hydrogels responsive to:		
pH	Temperature	Liquid composition
<ul style="list-style-type: none"> • In that case when hydrogels are ionic. • As increase in pH value • The swelling capacity increases in the anionic hydrogel having carboxyl groups like poly-sodium alginate. • The swelling capacity decreases in the cationic hydrogel having amino group like acrylate (dimethyl aminoethyl) and chitosan 	<ul style="list-style-type: none"> • (In that case when hydrogels can form chain aggregation and can also form hydrophobic association) • as increase in temperature • in cellulose and in their derivatives, (like N-isopropyl Acrylamide and some cellulose based polymers) solubility decreases. • in hydro-colloids (like agar-agar and gelatin) solvability increases 	<ul style="list-style-type: none"> • (In that case when the non-ionic and salts are contain around the hydrogels environment) • as alterations in swelling medium (either water or any aqueous medium) • in ionic hydrogels (like poly-potassium-acrylate) the swelling capacity decreases instantly with increase concentration value of non-solvent and salts • in non-ionic hydrogels (like polyvinyl alcohol) swelling capacity decreases moderately.


Table 3. Extraction of various bio-waste materials as pectin.

Sr. No.	Extraction of bio-waste material as pectin	References
1.	Citrus Limetta	(Garg, 2017)
2.	Orange waste	(Lessa et al., 2017a)
3.	Mango peels	(Banerjee et al., 2016)
4.	Pineapple peel	(Dai and Huang, 2016)
5.	Pineapple and Banana waste	(Yapo, 2009)
6.	Orange waste	(Biswas et al., 2007)

Table 4. Various pectin based hydrogels used for waste-water treatment.

Sr.No.	Pectin Based hydrogels	Pollutants	References
1.	Pectin-g-sodiumAcrylate-co-N-iso-propyl acrylamide hydrogel	Methylene blue & Methyl violet.	(Singha et al., 2017)
2.	Pectin based quaternary amino anion exchanger	Phosphate anions	(Naushad et al., 2018)
3.	Pectin/cellulose microfibers gel beads	Cd ²⁺ , Cu ²⁺ and Fe ²⁺	(Lessa et al., 2017b)
4.	Pectin/poly(acrylamide-co-acrylamidoglycolic acid) pH sensitive semi-IPN hydrogels	Ni ²⁺ , Cu ²⁺ , Co ²⁺	(Reddy et al., 2016)
5.	Acrylic grafted pectin hydrogel	Cd ²⁺	(Fares et al., 2011)
6.	Methacrylate-Pectin-co-Acrylamide-co-acrylic hydrogel	Cu ²⁺	(Guilherme et al., 2010)
7.	Iron-loaded pectin based hydrogel	As(V)	(Kumar et al., 2009)
8.	(i) Pectin-cl-poly-Acrylamide hydrogel (ii) Pectin-cl-poly-N-isopropyl-Acrylamide hydrogel (iii)Pectin-cl-poly-2-Acrylamido-2-methyl-1-propane-sulphoic hydrogel.	Cr ⁶⁺ , Cu ²⁺ and Fe ²⁺	(Chauhan et al., 2007)

Graphical Abstract



Highlights

- Hydrogel is used as sustainable noble material.
- Structure and properties of pectin are described.
- Pectin is produced from bio-waste materials.
- Pectin based hydrogels are used in water purification.
- The mechanical strength of pectin based hydrogel can be improved by incorporation of nanoparticles.

2019-03-07

Progress in pectin based hydrogels for water purification: trends and challenges

Thakur, Sourbh

Elsevier

Thakur S, Chaudhary J, Kumar V, Thakur VK. Progress in pectin based hydrogels for water purification: trends and challenges. *Journal of Environmental Management*, Volume 238, 15 May 2019, pp. 210-223

<https://doi.org/10.1016/j.jenvman.2019.03.002>

Downloaded from Cranfield Library Services E-Repository